

# Technical Data

## ANTI-PICK 109

High Modulus Hybrid Sealant



### Description

ANTI PICK 109 is a one part, chemically curing solvent free sealant based on Everbuild Hybriflex technology, combining the best qualities of silicone and polyurethane. Anti Pick 109 has been specifically formulated to provide a degree of resistance to finger picking answering the need for a harder to pick by hand seal (in comparison to traditional sealants) where a small movement accommodation is required.

### Benefits

- Excellent impact and wear resistance.
- Resistant to picking by fingers.
- Excellent primerless adhesion to most surfaces, including metals, most plastics, glass, polyester.
- High UV and aggressive atmosphere resistance.
- Excellent resistance to Chemicals & petrol (10% dilute acids, alkalis, most solvent) Overpaintable with certain paints (compatibility test should be made).
- Can be applied on damp surfaces.
- Non hazardous to health.
- High mechanical properties.
- Passed for use on different home office, national offender management services and ministry of justice projects.

### Certification

CE Marked under EN15651 parts 1 and 4 classes F12.5E and use in cold climates.

### Recommended For

- Secure environments i.e. prisons & hospitals where the sealant is hard to reach or the person is under supervision..
- Municipal and public areas.
- Perimeter sealing of doors, windows.
- Joints in heavy cladding.
- Pedestrian Walkways



### Available in

300ml Cartridge, available in the following colours:

White  
Soft Linen  
Grey

### Storage

Store in cool, dry conditions between +5°C and +25°C. Storage outside these parameters will dramatically reduce shelf life.

### Shelf Life

12 months from date of manufacture when stored as directed.

## ANTI-PICK 109

High Modulus Hybrid Sealant

### Health & Safety

Data sheet available for professional user on request.

### Specific Data

Consistency	Paste
Density	1.45 ± 0.05
Application Temperature	5 to 35°C
Skin Formation @ 23°C and 50% RH	30 ± 10 Min
Sagging (ISO 7390)	Nil
Curing at @ 23°C and 50% RH	> 2mm / 24Hr
Shore A Hardness (ISO 868 - 3 seconds)	Approx 60
Modulus at 60% elongation (ISO 8339)	~1Mpa
Tensile Strength (ISO 8339)	> 2.6 N/mm <sup>2</sup>
Shrinkage (ISO 10563)	<5%
Resistance to UV Radiation	Excellent
Compatibility With Paints	Water Based: Yes (test compatibility) Solvent Based: No (with Alkyd Paints)
Service Temperature	-40 to +150°C
Coverage	Approximately 11 linear meters per cartridge
Movement Accommodation	±12.5%

### Joint Dimensions

For maximum movement accommodation, it is recommended that:

1. The sealant joint depth should be no less than 5mm
2. Joint depth should be 5mm for joints up to 10mm wide
3. Joints above 10mm in width should be half the width in depth up to 20mm and minimum 10mm for wider joints

Joint depth may be adjusted to the correct size using EVERBUILD JOINT BACKER ROD or BOND BREAKING TAPE in cases where there is not enough depth to use Backer Rod.

### Joint Width Calculation

Joint widths are calculated as in BS6213:

$$\text{Width} = \frac{M \times 100}{F} + M$$

Where M = movement and F = movement accommodation Factor

### Primer

Priming is not always necessary; but if in doubt use a suitable primer as directed prior to application; especially when joints are to be immersed or require a high movement capability.

Mortar/Concrete use Sika Primer 3-N. If desired use silicone Primer NP2 on non-porous substrates.

### Surface Preparation

All surfaces must be clean and dust free. Preliminary adhesion tests are strongly recommended prior to full scale application. Surfaces may be damp, but have no standing water. For most substrates, priming is not required, however, if in doubt contact our technical department.

### Limitations

- Adhesion (and overpaintability) trials are recommended prior to full scale application
- It is the user's responsibility to determine suitability for use. If in doubt, please contact Technical Services Department for advice.
- Yellowing can occur in predominantly dark conditions.
- In areas of high UV some darkening/ discolouration may occur. This does not affect product performance.

*The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.*