

# PRODUCT DATA SHEET

## Sikafloor®-390 N

### 2-PART FLEXIBLE AND CHEMICALLY RESISTANT EPOXY COATING

#### PRODUCT DESCRIPTION

Sikafloor®-390 N is a two part, flexible, coloured epoxy resin with high chemical resistance. "Total solid epoxy composition acc. to the test method Deutsche Bauchemie e.V. (German Association for construction chemicals)"

#### USES

Sikafloor®-390 N may only be used by experienced professionals.

Crack-bridging and chemically resistant coating for concrete and screed surfaces in bund areas for the protection against water contaminating liquids (according to the product chemical resistance table)

#### CHARACTERISTICS / ADVANTAGES

- High chemical resistance
- Crack-bridging
- Liquid proof

#### ENVIRONMENTAL INFORMATION

- Conformity with LEED v4 MRc 2 (Option 1): Building-Product Disclosure and Optimization – Environmental Product Declarations
- Conformity with LEED v4 MRc 4 (Option 2): Building-Product Disclosure and Optimization - Material Ingredients

#### APPROVALS / STANDARDS

- Fire classification in accordance with DIN 4102, class B1, Report-No. PZ-Hoch-130683-4, Germany, April 2014.
- Fire classification in accordance with DIN EN 13501-1:2010, class Bfl-S1, Report-No. KB-Hoch-141525, Germany, January, 2015
- Particle emission certificate Sikafloor-390 N CSM Statement of Qualification - ISO 14644-1, class 3 - Report No. SI 1403-695 and GMP class A, Report No. 1403-695
- Outgassing emission certificate Sikafloor-390 N CSM Statement of Qualification - ISO 14644-8, class -9.6 - Report No. SI 1403-695.
- Good biological Resistance in accordance with ISO 846, CSM Report No. SI 1403-695
- Fluorescent test contamination (Riboflavin test) : very good, CSM Statement of Qualification, Report No. SI 1403-695
- Approval as "Water protection system", Z-59.12-392, DIBt, Germany
- Synthetic resin screed material according to EN 13813:2002, Declaration of Performance 02 08 01 02 002 0 000006 1008, certified by notified factory production control certification body 0921, certificate of conformity of the factory production control 2017, and provided with the CE marking.
- Coating for surface protection of concrete according to EN 1504-2:2004, Declaration of Performance 02 08 01 02 002 0 000006 1008, certified by notified factory production control certification body 0921, certificate of conformity of the factory production control 2017, and provided with the CE marking.

## PRODUCT INFORMATION

<b>Chemical Base</b>	Epoxy	
<b>Packaging</b>	Part A	21,25 kg containers
	Part B	3,75 kg containers
	Part A+B	25 kg ready to mix units
<b>Appearance / Colour</b>	Resin - part A	coloured, liquid
	Hardener - part B	transparent, liquid
Almost unlimited choice of colour shades. Under direct sun radiation there may be some discolouration and colour deviation, this has no influence on the function and performance of the coating.		
<b>Shelf Life</b>	24 months from date of production.	
<b>Storage Conditions</b>	The packaging must be stored properly in original, unopened and undamaged sealed packaging, in dry conditions at temperatures between +5°C and +30°C.	
<b>Density</b>	Part A	~ 1.73 kg/l (DIN EN ISO 2811-1)
	Part B	~ 1.05 kg/l
	Mixed resin	~ 1.6 kg/l
All Density values at +23°C		
<b>Solid Content</b>	~ 100% (by volume) / ~ 100% (by weight)	

## TECHNICAL INFORMATION

<b>Shore Hardness</b>	Shore D: 60 (14 days / +23°C)	(DIN 53 505)
<b>Abrasion Resistance</b>	75 mg (CS 10/1000/1000) (7 days / +23°C)	(EN ISO 5470-1 Taber Abraser Test)
<b>Flexural Strength</b>	~ 10 N/mm <sup>2</sup> (7 days / +23°C)	(DIN 53455)
<b>Elongation at Break</b>	~ 20 % (7 days / +23°C)	(DIN EN ISO 527-2)
<b>Tensile Adhesion Strength</b>	> 1.5 N/mm <sup>2</sup> (failure in concrete)	(ISO 4624)
<b>Chemical Resistance</b>	Resistant to many chemicals. Please ask for a detailed chemical resistance table.	
<b>Thermal Resistance</b>	<b>Exposure*</b>	<b>Dry heat</b>
	Permanent	+50°C
	Short-term max. 7 d	+80°C
	Short-term max. 12 h	+100°C
Short-term moist/wet heat* up to +80°C where exposure is only occasional (i.e. during steam cleaning etc.) *No simultaneous chemical and mechanical exposure.		

## SYSTEM INFORMATION

<b>Systems</b>	Please refer to the system data sheet of :	
	Sikafloor® Multidur ES-39	Smooth unicolour epoxy floor covering with high chemical resistance
	Sikafloor® Multidur ES-39 V	Textured unicolour epoxy floor covering with high chemical resistance
<b>Mixing Ratio</b>	Part A : part B = 85 : 15 (by weight)	

<b>Consumption</b>	<p>~ 0,75-0,85 kg/m<sup>2</sup> applied as a roller coating  ~ 1,6 kg/m<sup>2</sup> applied as a self smoothing wearing course  ~ 1,2 kg/m<sup>2</sup> applied as a wearing course on vertical areas  These figures are theoretical and do not allow for any additional material due to surface porosity, surface profile, variations in level or wastage etc. For detailed info, please refer to the System data sheet Sikafloor® Multidur ES-39 and Sikafloor® Multidur ES-39 V.</p>														
<b>Ambient Air Temperature</b>	+10°C min. / +30°C max.														
<b>Relative Air Humidity</b>	80% r.h. max.														
<b>Dew Point</b>	<p>Beware of condensation!  The substrate and uncured floor must be at least 3°C above dew point to reduce the risk of condensation or blooming on the floor finish.  Note: Low temperatures and high humidity conditions increase the probability of blooming.</p>														
<b>Substrate Temperature</b>	+10°C min. / +30°C max.														
<b>Substrate Moisture Content</b>	<p>&lt; 4% pbw moisture content.  Test method: Sika®-Tramex meter, CM-measurement or Oven-dry-method. No rising moisture according to ASTM (Polyethylene-sheet).</p>														
<b>Pot Life</b>	<b>Temperature</b>	<b>Time</b>													
	+10°C	~ 60 minutes													
	+20°C	~ 30 minutes													
	+30°C	~ 10 minutes													
<b>Curing Time</b>	<p>Before applying Sikafloor®-390 N on Sikafloor®-390 N allow:</p> <table border="1"> <thead> <tr> <th>Substrate temperature</th> <th>Minimum</th> <th>Maximum</th> </tr> </thead> <tbody> <tr> <td>+10°C</td> <td>48 hours</td> <td>3 days</td> </tr> <tr> <td>+20°C</td> <td>30 hours</td> <td>2 days</td> </tr> <tr> <td>+30°C</td> <td>20 hours</td> <td>30 hours</td> </tr> </tbody> </table> <p>Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity.</p>			Substrate temperature	Minimum	Maximum	+10°C	48 hours	3 days	+20°C	30 hours	2 days	+30°C	20 hours	30 hours
Substrate temperature	Minimum	Maximum													
+10°C	48 hours	3 days													
+20°C	30 hours	2 days													
+30°C	20 hours	30 hours													
<b>Applied Product Ready for Use</b>	<b>Temperature</b>	<b>Foot traffic</b>	<b>Light traffic</b>												
	+10°C	~ 48 hours	~ 6 days												
	+20°C	~ 30 hours	~ 4 days												
	+30°C	~ 20 hours	~ 3 days												
			<b>Full cure</b>												
			~14 days												
			~10 days												
			~ 7 days												
	<p>Note: Times are approximate and will be affected by changing ambient conditions.</p>														

## APPLICATION INSTRUCTIONS

### SUBSTRATE QUALITY / PRE-TREATMENT

- The concrete substrate must be sound and of sufficient compressive strength (minimum 25 N/mm<sup>2</sup>) with a minimum pull off strength of 1.5 N/mm<sup>2</sup>.
- The substrate can be damp but must be free of standing water and free of all contaminants such as oil, grease, coatings and surface treatments etc. If in doubt, apply a test area first.
- Concrete substrates must be prepared mechanically using abrasive blast cleaning or scarifying equipment to remove cement laitance and achieve an open textured surface.
- Weak concrete must be removed and surface defects such as blow holes and voids must be fully exposed.
- Repairs to the substrate, filling of blowholes/voids and surface levelling must be carried out using appropriate products from the Sikafloor®, SikaDur® and

Sikagard® range of materials.

- All dust, loose and friable material must be completely removed from all surfaces before application of the product, preferably by brush or vacuum.

### MIXING

Prior to mixing, stir part A mechanically. When all of part B has been added to part A, mix continuously for 3 minutes until a uniform mix has been achieved. When parts A and B have been mixed, add the quartz sand and if required the Extender T and mix for a further 2 minutes until a uniform mix has been achieved. To ensure thorough mixing pour materials into another container and mix again to achieve a consistent mix. Over mixing must be avoided to minimise air entrainment.

### Mixing Tools

Sikafloor®-390 N must be thoroughly mixed using a low speed electric stirrer (300 - 400 rpm) or other suit-

able equipment. For the preparation of mortars use a forced action mixer of rotating pan, paddle or trough type. Free fall mixers should not be used.

## APPLICATION

Prior to application, confirm substrate moisture content, relative humidity and dew point.

If > 4% pbw moisture content, Sikafloor® EpoCem® should be applied as a T.M.B. (temporary moisture barrier) system.

### **Wearing course (horizontal areas):**

Sikafloor®-390 N is poured, spread evenly by means of a serrated trowel.

Roll immediately in two directions with a spiked roller to ensure even thickness.

### **Wearing course (vertical areas):**

The first layer of Sikafloor®-390 N, mixed with 2.5 - 4% Extender T, has to be applied by trowel. After curing, apply the second layer of Sikafloor®-390 N, mixed with 2.5 - 4% Extender T, by trowel.

### **Wearing course with slip resistance:**

Sikafloor®-390 N is poured, spread evenly by means of a serrated trowel and blind the fresh layer with silicon carbide or quartz sand to excess. After final drying the surplus silicon carbide / quartz sand must be swept off and the surface must be vacuumed. The seal coat (Sikafloor®-390 N + 5 wt.-% Thinner C) has to be applied evenly by short-piled roller or squeegee.

## CLEANING OF TOOLS

Clean all tools and application equipment with Thinner C immediately after use. Hardened and/or cured material can only be removed mechanically.

## FURTHER DOCUMENTS

### ▪ **Substrate quality & Preparation**

Please refer to Sika Information Manual: "EVALUATION AND PREPARATION OF SURFACES FOR FLOORING SYSTEMS".

### ▪ **Application instructions**

Please refer to Sika Information Manual: "MIXING & APPLICATION OF FLOORING SYSTEMS".

### ▪ **Maintenance**

Please refer to "Sikafloor®- CLEANING REGIME".

## LIMITATIONS

### **Please note:**

- Do not apply Sikafloor®-390 N on substrates with rising moisture.
- Do not blind the primer
- Freshly applied Sikafloor®-390 N should be protected from damp, condensation and water for at least 24 hours.
- For areas with limited exposure and normally absorbent concrete substrates priming with Sikafloor®-156/-161/-160 is not necessary for roller or textured coating systems.
- For roller / textured coatings: Uneven substrates as well as inclusions of dirt cannot and should not be covered by thin sealer coats. Therefore both substrate and adjacent areas must always be prepared and cleaned thoroughly prior to application.

The incorrect assessment and treatment of cracks may lead to a reduced service life and reflective cracking. For exact colour matching, ensure the Sikafloor®-390 N in each area is applied from the same control batch numbers. Under certain conditions, underfloor heating or high ambient temperatures combined with high point loading, may lead to imprints in the resin. If heating is required do not use gas, oil, paraffin or other fossil fuel heaters, these produce large quantities of both CO<sub>2</sub> and H<sub>2</sub>O water vapour, which may adversely affect the finish. For heating use only electric powered warm air blower systems

## VALUE BASE

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## ECOLOGY, HEALTH AND SAFETY

### **DIRECTIVE 2004/42/CE - LIMITATION OF EMISSIONS OF VOC**

According to the EU Directive 2004/42/CE, the maximum allowed content of VOC (product category IIA / x type xx) is 500 g/l (Limits 2010) for the ready to use product.

The maximum content of Sikafloor®-390 N is ≤ 500 g/l VOC for the ready to use product.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

**SIKA LIMITED**  
**Watchmead**  
Welwyn Garden City  
Hertfordshire, AL7 1BQ  
Tel: 01707 394444  
Web: [www.sika.co.uk](http://www.sika.co.uk)  
Twitter: @SikaLimited

**SIKA IRELAND LIMITED**  
**Ballymun Industrial Estate**  
Ballymun  
Dublin 11, Ireland  
Tel: +353 1 862 0709  
Web: [www.sika.ie](http://www.sika.ie)  
Twitter: @SikaIreland



Sikafloor-390N\_en\_GB\_(09-2017)\_3\_1.pdf

Product Data Sheet  
Sikafloor®-390 N  
September 2017, Version 03.01  
020811020020000036