

SikaGard®-6220 S

Sprayable, high penetrating cavity wax in aerosol can

Technical Product Data

Chemical base	Wax solution
Color	Amber
Cure mechanism	Air-drying
Density (liquid)	0.66 kg/l approx.
Solid content (CQP ¹ 002-2)	30% approx.
Application temperature	15 - 25°C
Film thickness	wet 100 µm dry 30 µm
Drying time ²	2 h approx.
Service temperature	-50 - 75°C
Shelf life (storage between 5°C and 25°C);	24 months

¹⁾ Corporate Quality Procedure

²⁾ 23°C / 50% r.h.

Description

SikaGard®-6220 S is an amber colored, easy to use, durable wax in an aerosol can with very good rust-proofing properties. It is suitable for an effective protection against corrosion in vehicle body cavities and convinces with very good application properties and final performance. Thanks to its very high creep capability, it perfectly protects even hardly accessible areas and tight sheet intervals.

After drying, a brown, slightly sticky wax coating remains that protects cavity areas from corrosion.

SikaGard®-6220 S is manufactured in accordance with ISO 9001 quality assurance system.

Product Benefits

- Equipment independent (aerosol)
- Very good film building property
- Excellent water displacing
- Good low temperature behavior
- Heat resistant
- Easy to use
- Excellent creep capability
- Road salt resistant
- Permanently elastic

Areas of Application

SikaGard®-6220 S is a spray applied anti-corrosion coating for repair and protection of open cavities and concealed areas of vehicles such as cavities of door skins, side panels, motor hoods, trunks, rear wing, sills, cross members and pillars.

The product penetrates finest hair-line cracks but does not drip off drainage holes.

SikaGard®-6220 shows very good adhesion on different paints, metal primers, metals and PVC without any pre-treatment.

The product is suitable for professional experienced users only. Tests with actual substrates and conditions have to be performed to ensure adhesion and material compatibility.

Industry



Chemical Resistance

SikaGard®-6220 S is resistant against water, seawater, salt spray, oil, soft bases and acids. The above information is offered for general guidance only. Advice on specific applications will be given on request.

Method of Application

Surface preparation

Surfaces must be clean, dry and free of rust, dust and grease. Bare metal must be pre-treated to enhance corrosion resistance (e.g. uncoated steel, etc).

Application

Shake can approx. 40 times before use. Cover adjacent surfaces prior the spray process. Spray at room temperature and from a distance of approx. 25 cm on the surface or in the cavities. To reach cavities use the additional actuator with flexible hose. Use the existing or drill access points in the car body. Spray a continuous coat. Hold the can in an upright position and do not spray on parts of the brake, engine or exhaust system. After use, invert can and spray in short bursts to clear nozzle. Due to the flammable propellant ventilate the cavities during the drying time or before closing the cavities.

Removal

Fresh SikaGard®-6220 S can be removed from tools and equipment with Sika® Remover-208. Once dried, the material can only be removed mechanically.

Hands and exposed skin should be washed immediately using Sika® Handclean towels or a suitable industrial hand cleaner and water. Do not use solvents!

Over painting

SikaGard®-6220 S is not over paintable.

Further Information

Copies of the following publication is available on request:

- Safety Data Sheet

Packaging Information

Aerosol can	500 ml
-------------	--------

Value Basis

All technical data stated in this Product Data Sheet is based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

Health and Safety Information

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

Legal Notes

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Further information available at:

www.sika.co.uk
www.sika.com

Sika Limited
Business Unit Industry
Watchmead, Welwyn Garden City
Herts, AL7 1BQ
United Kingdom
Tel. +44 (0)1707 394444

