

Sarna Cleaner

Cleaner for heavily soiled Sarnafil® G/S membranes and for Sarnafil® G/S membranes when using the Sarnafil® Liquid Detailing System

Product Description

Mixture of high volatile solvents

Uses

Sarna Cleaner is used to remove heavy soiling from the seam area of Sarnafil® G/S membranes. It is also used to prepare Sarnafil® G/S membranes prior to using Sikalastic®-600 PVC Primer. Sarna Cleaner can be used to clean tools and degrease metal sheets.

Caution:
Use as instructed as Sarna Cleaner will remove the lacquer coating from Sarnafil® G/S.

Characteristics / Advantages

- Evaporates quickly
- Suitable for heavily stained seam overlaps of Sarnafil® G/S membranes
- Cleans and degreases

Product Data

Form

Consistency liquid

Colour transparent

Packaging Tin: 5 litre tin

Storage

Storage Conditions Store in dry conditions at temperatures between 0 °C and + 30 °C.
The product is highly flammable: Regulatory requirements regarding storage and handling of dangerous goods must be observed.

Shelf-Life 24 months from date of production if stored properly in original, unopened and undamaged sealed container. Expiry date on container.



Technical Data

Chemical Basis Mixture of high volatile solvents

Density 0.9kg/l

System Information

Processing Requirements / Limits

Substrate Temperature At least -20 °C

Ambient Temperature At least -30 °C

Limits

- Dissolves thermoplastics not resistant to solvents (e.g. polystyrene, polycarbonate, acrylics)
- Do not use the cleaner to wash areas of roof surface.

Processing

Application Guideline Based on the valid installation instructions of the relevant roof waterproofing membrane.

Application Method **Application as cleaner for heavily soiled Sarnafil® G/S membranes:**
Soak a clean white T Prep cloth with Sarna Cleaner and then clean the membrane, tool or metal sheet. The cloths should be changed frequently to avoid the spreading of dirt. When cleaning seams a new T Prep cloth is to be used. In the seam areas allow Sarna Cleaner to evaporate completely before the welding of seams.

Sarna Cleaner may reduce the seam quality and should only be used on heavily soiled areas!

Notes of Application / Limits **Application as preparation of Sarnafil® G/S membranes when using Sikalastic®-600 PVC Primer:**

Sarna Cleaner should not be used to clean dirt from the membrane in this application. If the membrane requires cleaning then only water and a scrubbing brush must be used and the membrane wiped clean and dry with T Prep cloths. Any areas not receiving the Sikalastic®-600 PVC Primer must be masked!

Soak a clean white T Prep cloth with Sarna Cleaner and then prepare the membrane with one wipe – **No More!** The T Prep cloths should be changed frequently to avoid the spreading of dirt. Allow Sarna Cleaner to evaporate completely before application of Sikalastic®-600 PVC Primer. See the Product Data Sheet for Sikalastic®-600 PVC Primer for more information.

Repeatedly changing T Prep cloths will allow for effective absorption of dirt and the colour will not stain the membrane. Use solvent resistant gloves and eye protection glasses during application. Sarna Cleaner contains volatile and flammable solvents. Application in closed rooms is allowed only with sufficient room ventilation. Smoking and open flames are not permitted.

Sarna Cleaner will remove the lacquer so should only be used as instructed!

Tool Cleaning Tools and equipment must be cleaned immediately after use.

Roofing

Value Base	All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.
Local Restrictions	Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.
Health and Safety Information	For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (MSDS) containing physical, ecological, toxicological and other safety-related data. REACH relevant information is available in the most recent SDS.

All data in our product information are based on our current knowledge and experience. They do not release users from careful testing of the application and strict observation of the relevant processing regulations because of the wide range of possible influences during the application and use of our products. Legally valid assurances of specific characteristics or suitability for special purposes of application other than those provided in our documentation for the specific product cannot be inferred from our information. Any protective rights or existing laws and provisions must be followed by the recipient or processor of our products at their own responsibility. Moreover our general terms and conditions of sale and guarantee are valid.



Sika Ltd, Bankside 300, Peachman Way, Broadland Business Park,
Norwich, NR7 0WF.

Tel: 01603 709360 Fax: 01603 433436 Email: sarnafilroofing@uk.sika.com

Registered Office: Sika Ltd, Watchmead, Welwyn Garden City, Hertfordshire, AL7 1BQ
Registered in England: 226822

Sarnafil®