

PRODUCT DATA SHEET

Sikacryl®-625 Fire+

Fire resistant ablative coating for linear seals and penetrations

PRODUCT DESCRIPTION

Sikacryl®-625 Fire+ is a 1-part fire resistant, ablative acrylic coating used for the installation of SikaSeal®-626 Fire Board+.

USES

- Covers linear seals up to 120 mm in combination with mineral fibre backing.
- Edge coating of SikaSeal®-626 Fire Board+ when installed on the outer face of a wall or floor.

CHARACTERISTICS / ADVANTAGES

- Up to 4 hours fire resistance.
- 1-part ready to use, easy to apply.
- Easy to clean.

PRODUCT INFORMATION

| | |
|---------------------------|---|
| Chemical Base | Water based acrylic |
| Packaging | 3L Pail |
| Shelf Life | 12 months from the date of production. |
| Storage Conditions | The product must be stored in original, unopened and undamaged packaging in dry conditions at temperatures between +5 °C and +25 °C. Always refer to packaging. |
| Colour | White |
| Density | ~1.3 kg/l (ISO 1183-1) |

TECHNICAL INFORMATION

| | |
|----------------------------|---|
| Service Temperature | -20 °C min. / +70 °C max. |
| Resistance to fire | Refer to SikaSeal®-626 Fire Board 'Approvals / Certificates' or contact Sika Technical Services for specific information. |

APPLICATION INFORMATION

| | |
|-------------------------|---|
| Ambient Air Temperature | +5 °C min. / +40 °C max. |
| Substrate Temperature | +5 °C min. / +40 °C max., min. +3 °C above dew point temperature. |

VALUE BASE

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER DOCUMENTS

- Sika Application Manual: Sikacryl®-625 Fire+ for linear seals.
- Sika Application Manual: SikaSeal®-626 Fire Board+ for penetration seals.
- Brochure Sika Fire Protection Solutions.

LIMITATIONS

- Colour variations may occur due to exposure to chemicals, high temperatures and/or UV-radiation (especially with the colour shade white). However, a change in colour is purely of aesthetic nature and does not adversely influence the technical performance or durability of the product.
- Do not use Sikacryl®-625 Fire+ as glass sealer, for floor joints, sanitary joints or on natural stone.
- Do not use Sikacryl®-625 Fire+ on bituminous substrates, natural rubber, EPDM rubber or on any building materials which might leach oils, plasticizers or solvents that could attack the sealant.
- Do not use Sikacryl®-625 Fire+ for joints under water pressure or for permanent water immersion.
- Sikacryl®-625 Fire+ may only be used for applications and in combination with products it was tested for.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

SIKA LIMITED

Watchmead
Welwyn Garden City
Hertfordshire, AL7 1BQ
Tel: 01707 394444
Web: www.sika.co.uk
Twitter: @SikaLimited



Product Data Sheet
Sikacryl®-625 Fire+
January 2022, Version 01.01
020517010040000010

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

The substrate must be clean, dry, sound, free from oils, grease, dust and loose or friable particles. Sikacryl®-625 Fire+ adheres without primers and/or activators.

APPLICATION METHOD / TOOLS

Reference must be made to the relevant Sika Application Manual or contact Sika Technical Services for additional information.

CLEANING OF TOOLS

Clean all tools and application equipment with water immediately after use. Hardened material can only be removed mechanically.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sikacryl-625Fire+-en-GB-(01-2022)-1-1.pdf