

## PRODUCT DATA SHEET

# Sikagard®-63 N

Epoxy chemical resistant protective coating

### PRODUCT DESCRIPTION

Sikagard®-63 N is a 2-part, epoxy resin based, chemical resistant, protective coating. It can be used on many types of structures or elements for cementitious, metallic and epoxy resin binder substrates. The chemical resistant properties provides surface protection from aggressive chemicals that can cause rapid degradation.

### USES

Sikagard®-63 N may only be used by experienced professionals.

Chemical resistant protective coating on:

- Concrete
- Stone
- Cementitious mortars
- Renderings
- Epoxy cement
- Epoxy resin-based products
- Steel

Chemical resistant protective lining for:

- Silos
- Bund linings
- Chemical mixing tanks
- Chemical containment tanks
- Fuel and oil tanks
- Sludge tanks
- Industrial chemical areas

Anti-corrosion coating on steel elements within:

- Food processing plants
- Sewage treatment works
- Chemical and pharmaceutical facilities
- Beverage facilities

### CHARACTERISTICS / ADVANTAGES

- Good chemical resistance
- Good temperature resistance
- Low VOC emissions
- High build
- Impervious to liquids
- Easy to mix
- Applied by brush, roller or airless spray

### ENVIRONMENTAL INFORMATION

- Conformity with LEED v4 MRc 4 (Option 2): Building Product Disclosure and Optimization - Material Ingredients
- Conformity with LEED v2009 IEQc 4.2: Low-Emitting Materials - Paints and Coatings

### APPROVALS / STANDARDS

- CE Marking and Declaration of Performance to EN 1504-2 - Surface protection product for concrete - Coating

## PRODUCT INFORMATION

<b>Chemical Base</b>	Epoxy resin	
<b>Packaging</b>	Part A	8.70 kg container
	Part B	1.3 kg container
	Refer to current price list for packaging variations	
<b>Appearance / Colour</b>	Standard colour: ~RAL 7032 (pebble grey) Other colours on request.	
<b>Shelf Life</b>	12 months from date of production	
<b>Storage Conditions</b>	The product must be stored in original, unopened and undamaged packaging in dry conditions at temperatures between +5 °C and +30 °C. Always refer to packaging.	
<b>Density</b>	Resin mixed:~ 1.44 kg/l Value at +23 °C	(EN ISO 2811-1)
<b>Solid Content</b>	~100 %	
<b>Product Declaration</b>	EN 1504-2 - Surface protection product for concrete - Coating	

## TECHNICAL INFORMATION

<b>Tensile adhesion strength</b>	> 1.5 N/mm <sup>2</sup> to concrete	(ISO 4624)
	> 15 N/mm <sup>2</sup> to steel	(EN 24624)
	>10 N/mm <sup>2</sup> to aluminium	(EN 24624)
<b>Chemical Resistance</b>	Resistant to many chemicals. Contact Sika Technical Services for additional information.	
<b>Thermal Resistance</b>	<b>Exposure</b>	<b>Dry heat</b>
	Permanent	+40 °C
	Maximum 3 days	+60 °C
<b>Diffusion Resistance to Water Vapour</b>	μH <sub>2</sub> O ~100 000	(EN ISO 7783-1)

## APPLICATION INFORMATION

<b>Mixing Ratio</b>	Part A : Part B = 87 : 13 by weight	
<b>Consumption</b>	~0.15 kg/m <sup>2</sup> per layer	
<b>Layer Thickness</b>	~0.1 mm per layer	
<b>Ambient Air Temperature</b>	+10 °C min. / +30 °C max.	
<b>Relative Air Humidity</b>	≤ 80 %	
<b>Dew Point</b>	Beware of condensation. The substrate and uncured applied floor material must be at least +3 °C above dew point to reduce the risk of condensation or blooming on the finish.	
<b>Substrate Temperature</b>	+10 °C min. / +40 °C max	
<b>Pot Life</b>	<b>Temperature</b>	<b>Time</b>
	+10 °C	~30 minutes
	+20 °C	~20 minutes
	+30 °C	~10 minutes

## Waiting Time / Overcoating

Temperature	Min.	Max.	Full Cure
+10 °C	~9 hours	~3 days	~14 days
+20 °C	~5 hours	~2 days	~9 days
+30 °C	~4 hours	~1 day	~5 days

## VALUE BASE

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## LIMITATIONS

- Do not apply Sikagard®-63 N on moist substrates.
- Sag resistance on vertical surface is < 100 µm.
- Do not use to produce glass fibre reinforced linings.
- Protect freshly applied product from rain, condensation and water for at least 24 hours.
- For consistent colour matching, ensure the Sikagard®-63 N in each area is applied from the same control batch numbers.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

### DIRECTIVE 2004/42/CE - LIMITATION OF EMISSIONS OF VOC

According to the EU-Directive 2004/42, the maximum allowed content of VOC (Product category IIA / j type sb) is 500 g/l (Limits 2010) for the ready to use product. The maximum content of Sikagard®-63 N is <500 g/l VOC for the ready to use product.

## APPLICATION INSTRUCTIONS

### SUBSTRATE QUALITY

Substrates must be clean, dry and free of all contaminants such as dirt, oil, grease, coatings, laitance, surface treatments, loose friable materials and any other surface contaminants that could affect adhesion.

### SUBSTRATE PREPARATION

#### Concrete / Stone / Cementitious mortars & rendering

Concrete must be at least 3–6 weeks old.

Substrates must be prepared mechanically using suitable abrasive blast cleaning or planing / scarifying equipment to remove cement laitance and achieve an open textured gripping surface profile suitable for the product thickness.

High spots can be removed by grinding.

Weak substrates must be removed and surface defects such as blow holes and voids must be fully exposed.

Repairs to the substrate, filling of cracks, blowholes/voids and surface levelling must be carried out using products from the Sikafloor®, Sikadur®, Sik-

agard® and Sika Monotop® range of materials.

Products must be cured before applying Sikagard®-63 N.

### Steel / aluminium

Surfaces must be prepared mechanically using suitable abrasive blast cleaning, grinding, rotating wire brush or other suitable equipment to achieve a bright metal finish. Reference must be made to the preparation levels in the following standards if compliance is required:

ISO EN 12944-4: level Sa 2 ½

NACE International Standard: SSPC-SP 10 "near white metal blast cleaned"

EN 14879, part 1

Apply a suitable compatible primer on the prepared steel as soon as possible to prevent oxide development. Contact Sika Technical Services for additional

### Epoxy resin-based products

Surfaces must be prepared by abrading using suitable equipment.

### General

On high absorbent, non-cementitious based substrates a suitable primer must be used. Contact Sika Technical Services for additional information.

All dust, loose and friable material must be completely removed from all surfaces before application of the product and associated system products, preferably by vacuum extraction equipment.

Avoid dew point conditions before and during product application.

### MIXING

Prior to mixing all parts, mix part A (resin) using an electric single paddle mixer (300–400 rpm) or other similar equipment to mix liquid and all the coloured pigment until a uniform colour has been achieved. Add part B (hardener) to part A and mix part A + B continuously for 3,0 minutes until a uniformly coloured mix has been achieved. To ensure thorough mixing, pour materials into a clean container and mix again for at least 1,0 minute to achieve a smooth consistent mix. Excessive mixing must be avoided to minimise air entrainment. During the final mixing stage, scrape down the sides and bottom of the mixing container with a straight edge trowel or spatula at least once to ensure complete mixing. Mix full units only. Mixing time for A+B = ~4,0 minutes

### APPLICATION

Reference must be made to further documentation where applicable, such as relevant method statement, application manual and installation or working instructions.

Prior to application, confirm substrate moisture content, relative air humidity, dew point, substrate, air and product temperatures.

Apply Sikagard®-63 N onto the prepared substrate

evenly using a roller, brush or airless spray at the required consumption rate.

## CLEANING OF TOOLS

Clean all tools and application equipment with water immediately after use. Hardened material can only be removed mechanically.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### SIKA LIMITED

Watchmead  
Welwyn Garden City  
Hertfordshire, AL7 1BQ  
Tel: 01707 394444  
Web: [www.sika.co.uk](http://www.sika.co.uk)  
Twitter: @SikaLimited



### Product Data Sheet

Sikagard®-63 N  
January 2021, Version 03.01  
020606010030000001

Sikagard-63N-en-GB-(01-2021)-3-1.pdf