

PRODUCT DATA SHEET

Sikament[®]-700 (GB)

HIGH RANGE WATER REDUCING/SUPERPLASTICISING CONCRETE ADMIXTURE

PRODUCT DESCRIPTION

Sikament[®]-700 (GB) is a liquid admixture for concrete which is used as a high-range water reducer/superplasticiser. It meets the requirements of BS EN 934-2

USES

- Sikament[®]-700 (GB) is a unique product that is suitable for the production ready mixed flooring concretes
- Suitable for laser screed and hand laid floor slabs
- Applications that require high quality concrete
- Application that require high early strength

CHARACTERISTICS / ADVANTAGES

- High-range water reductions resulting in higher strengths and densities
- Improved cohesion
- Improved early and ultimate strengths
- Improved rheology
- Improved durability
- Reduced drying shrinkage
- Reduced mix costs
- Loss of consistence due to fibre reinforcement can be compensated.

APPROVALS / STANDARDS

Conforms to the requirements of BS EN 934-2 Table 3.1 & 3.2
DoP 00003284, certified by Factory Production Control Body 0086, Certificate 541325, and provided with the CE mark

PRODUCT INFORMATION

Chemical Base	Modified polycarboxylate
Packaging	200 litre drum and 1000 litre IBC
Appearance / Colour	Straw Liquid
Shelf Life	Store in dry conditions at temperatures between +5°C and +25°C. Protect from direct sunlight and frost.
Storage Conditions	12 months from date of production if stored properly in undamaged containers.
Specific Gravity	1.03 kg/l (at +20°C)
pH-Value	3.3 (+/- 1.0)
Total Chloride Ion Content	<0.1%

TECHNICAL INFORMATION

Specific Advice

Alkali Content: <0.2%
Freezing Point: +1°C
Air Entrainment: Negligible
Effect on Setting: Slight extension to normal setting
Effect of Overdosing: Increased workability and segregation

APPLICATION INFORMATION

Recommended Dosage	0.4 -1.5% by weight of cement
Compatibility	Sika® Admixtures: <ul style="list-style-type: none">▪ Compatibility information available on request Cements: <ul style="list-style-type: none">▪ All cement combination
Dispensing	Sikament®-700 (GB) should be dispensed through suitable calibrated dosing equipment.

APPLICATION INSTRUCTIONS

Application Method / Tools

- The standard rules of good concreting practice, concerning production as well as placing, are to be followed. Refer to relevant standards. Fresh concrete must be cured properly.
- Sikament®-700 (GB) should not be added to dry cement
- Sikament®-700 (GB) should be added with the mixing water

Notes on Application / Limitations

- When using Sikament®-700 (GB) a suitable mix design is required and local material sources should be evaluated.
- Support from our Technical Department is recommended

FURTHER DOCUMENTS

MECHANICAL / PHYSICAL PROPERTIES

Compressive Strength - Typical Data

	Control (350 kg/m ³)	Sikament®-700 (GB)
Dose (BWC%)	None	0.50
w/c ratio	0.45	0.38
Slump (mm)	70	70
Air cont %	1.1	1.6
28 day Compressive Strength N/mm ²	30.0	40.0

VALUE BASE

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from

country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA LIMITED

Watchmead
Welwyn Garden City
Hertfordshire, AL7 1BQ
Tel: 01707 394444
Web: www.sika.co.uk
Twitter: @SikaLimited

SIKA IRELAND LIMITED

Ballymun Industrial Estate
Ballymun
Dublin 11, Ireland
Tel: +353 1 862 0709
Web: www.sika.ie
Twitter: @SikaIreland



Product Data Sheet
Sikament®-700 (GB)
April 2019, Version 01.02
021301011000003284

Sikament-700GB-en-GB-(04-2019)-1-2.pdf

