

SYSTEM DATA SHEET

Sikafloor® MultiDur ES-30

Smooth, coloured epoxy floor system

PRODUCT DESCRIPTION

Sikafloor® MultiDur ES-30 is a self-smoothing, coloured, rigid epoxy flooring system. It provides a hard-wearing, seamless, low-maintenance gloss finish.

USES

Sikafloor® MultiDur ES-30 may only be used by experienced professionals.

Sikafloor® MultiDur ES-30 is used in industrial buildings such as:

- Logistics facilities and warehouses
- Manufacturing facilities and workshops
- Storage areas

Please note:

- The System may only be used for interior applications.

CHARACTERISTICS / ADVANTAGES

- Low odour
- Low VOC emissions
- Good resistance to abrasion
- Good resistance to specific chemicals
- Good mechanical resistance
- Seamless


APPROVALS / STANDARDS

- Slip resistance DIN EN 16165, Sikafloor®-150 Plus / -264 Plus, Roxeler, Test Report No. 020067-24-6
- Reaction to fire EN 13501-1, Sikafloor® MultiDur ES-30, GHENT, Test Report No. CR 24-0635-01

SYSTEM INFORMATION

System Structure

Sikafloor® MultiDur ES-30



	Layer	Product
	Primer	Sikafloor®-150 Plus, or Sikafloor®-151, or Sikafloor®-1590
	Wearing layer	Sikafloor®-264 Plus
	Contact Sika Technical Service for information on choosing the right primer for your project.	
Composition	Epoxy	
Appearance	Smooth, gloss finish	
Colour	Available in various colour shades	
Nominal thickness	1.5 mm to 3 mm	

TECHNICAL INFORMATION

Tensile adhesion strength	≥ 1.5 MPa	(EN 1542)
Reaction to Fire	Class B _{fl} -s1	(EN 13501-1)
Chemical Resistance	Laboratory-defined resistance to many individual chemicals. Before proceeding, contact Sika Technical Service for specific information.	

APPLICATION INFORMATION

Consumption	Layer	Product	Consumption
	Primer	Sikafloor®-150 Plus, or Sikafloor®-151, or Sikafloor®-1590	1–2 × 0.3–0.5 kg/m ²
	Wearing layer	Sikafloor®-264 Plus Filled with up to 1:1 with quartz sand (0.06–0.3 mm)	1.6–1.9 kg/m ² per mm
Note: Consumption data is theoretical and does not allow for any additional material due to surface porosity, surface profile, variations in level, wastage or any other variations. Apply the product to a test area to calculate the exact consumption of the specific substrate conditions and proposed application equipment.			
Ambient Air Temperature	Maximum	+30 °C	
	Minimum	+10 °C	
Relative Air Humidity	Maximum	80 % r.h.	
Dew Point	Refer to the individual Product Data Sheet.		
Substrate Temperature	Maximum	+30 °C	
	Minimum	+10 °C	

Substrate Moisture Content

Refer to the individual Product Data Sheet.

Waiting Time / Overcoating

When using Sikafloor®-1590 refer to the individual Product Data Sheet for specific information on waiting time to overcoating.

Before applying Sikafloor®-264 Plus on the primer allow:

Temperature	Minimum	Maximum
+10 °C	17 hours	3 days
+20 °C	9 hours	48 hours
+30 °C	7 hours	24 hours

Note: Times are approximate and will be affected by changing ambient conditions, particularly temperature and relative humidity.

Applied Product Ready for Use

Temperature	Foot traffic	Light traffic	Full cure
+10 °C	30 hours	6 days	10 days
+20 °C	24 hours	4 days	7 days
+30 °C	16 hours	2 days	5 days

Note: Times are approximate and will be affected by changing ambient conditions, particularly temperature and relative humidity.

VALUE BASE

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER DOCUMENTS

Refer to the following method statements:

- Sika Method Statement — Evaluation and preparation of surfaces for flooring systems
- Sika Method Statement — Sikafloor® mixing and application

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA LIMITED

Watchmead
Welwyn Garden City
Hertfordshire, AL7 1BQ
Tel: 01707 394444
Web: www.sika.co.uk
Twitter: @SikaLimited



System Data Sheet

Sikafloor® MultiDur ES-30
May 2025, Version 02.01
02081190000000234

SikafloorMultiDurES-30-en-GB-(05-2025)-2-1.pdf