

PRODUCT DATA SHEET

Sika® Bonding Primer

TWO-COMPONENT WATERBASED EPOXY PRIMER.

PRODUCT DESCRIPTION

Sika® Bonding Primer is a two-component, water-based epoxy primer to consolidate substrates and enhance the adhesion of Sikafloor® and Sikagard® products

USES

Versatile primer for use with:

- Sikafloor® balcony waterproofing systems
- Sikagard® hygiene coatings
- Suitable for use on concrete, masonry, tiles, insulation foams, bituminous surfaces, plaster, cementitious renders, screeds and mortars.

CHARACTERISTICS / ADVANTAGES

- Fast curing - overcoat possible after 1 - 2 hours
- Long pot life - up to 12 hours
- Low odour - water-based product
- Consolidates dusty or friable surfaces
- Uniforms the absorbency of the substrate
- Enhances adhesion to a broad range of substrates
- Easy application by brush or roller

PRODUCT INFORMATION

Chemical Base	Epoxy, waterborne and polyamine curative	
Packaging	5.0 l (~5.16 kg) unit	4 l component A 1 l component B
	15.0 l (~15.546 kg) unit	12 l component A 3 l component B
Shelf Life	24 months from date of production	
Storage Conditions	The product must be stored properly in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +25 °C. Higher storage temperatures may reduce shelf life of product. Reference shall also be made to the storage recommendations within the safety data sheet.	
Density	~1.03 kg/l (23 °C)	(EN ISO 2811-1)

APPLICATION INFORMATION

Mixing Ratio	Component A : Component B = 4:1 (by volume)																								
Ambient Air Temperature	+5 °C min. / +40 °C max.																								
Relative Air Humidity	80 % r.h. max.																								
Substrate Temperature	+5 °C min. / +40 °C max.																								
Dew Point	Beware of condensation. The substrate and uncured coating must be ≥ 3 °C above dew point.																								
Substrate Moisture Content	Visible damp free (maximum 18 % wood moisture equivalent). ≤ 6 % pbw moisture content Test method: Sika®-Tramex meter ≤ 4 % CM - measurement or Oven-dry-method. No rising moisture according to ASTM (Polyethylene-sheet).																								
Waiting Time / Overcoating	Before applying any recommended Sikafloor® products on Sika® Bonding Primer, allow: <table border="1" data-bbox="608 622 1434 750"> <thead> <tr> <th><u>Substrate temperature</u></th> <th><u>Minimum waiting time</u></th> <th><u>Maximum waiting time</u></th> </tr> </thead> <tbody> <tr> <td>+10 °C</td> <td>4 hours approx.</td> <td>7 days</td> </tr> <tr> <td>+20 °C</td> <td>2.5–3.5 hours approx.</td> <td>7 days</td> </tr> <tr> <td>+30 °C</td> <td>1 hour approx.</td> <td>7 days</td> </tr> </tbody> </table> <p>Before applying Sikagard® products on Sika® Bonding Primer allow:</p> <table border="1" data-bbox="608 795 1434 922"> <thead> <tr> <th><u>Substrate temperature</u></th> <th><u>Minimum waiting time</u></th> <th><u>Maximum waiting time</u></th> </tr> </thead> <tbody> <tr> <td>+10 °C</td> <td>24 hours approx.</td> <td>7 days</td> </tr> <tr> <td>+20 °C</td> <td>8 hours approx.</td> <td>7 days</td> </tr> <tr> <td>+30 °C</td> <td>6 hours approx.</td> <td>7 days</td> </tr> </tbody> </table> <p>Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity.</p>	<u>Substrate temperature</u>	<u>Minimum waiting time</u>	<u>Maximum waiting time</u>	+10 °C	4 hours approx.	7 days	+20 °C	2.5–3.5 hours approx.	7 days	+30 °C	1 hour approx.	7 days	<u>Substrate temperature</u>	<u>Minimum waiting time</u>	<u>Maximum waiting time</u>	+10 °C	24 hours approx.	7 days	+20 °C	8 hours approx.	7 days	+30 °C	6 hours approx.	7 days
<u>Substrate temperature</u>	<u>Minimum waiting time</u>	<u>Maximum waiting time</u>																							
+10 °C	4 hours approx.	7 days																							
+20 °C	2.5–3.5 hours approx.	7 days																							
+30 °C	1 hour approx.	7 days																							
<u>Substrate temperature</u>	<u>Minimum waiting time</u>	<u>Maximum waiting time</u>																							
+10 °C	24 hours approx.	7 days																							
+20 °C	8 hours approx.	7 days																							
+30 °C	6 hours approx.	7 days																							

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

All surfaces to be coated should be thoroughly cleaned by conventional means.

Inspect the substrate.

Spalling, flaking or damaged areas should be repaired using compatible materials to match surroundings or replaced as necessary.

If in doubt apply a test area first.

Tiles have to be prepared mechanically, glazing has to be removed.

Grinding may be necessary to level the surface.

For detailed information regarding substrate quality / preparation and primer chart please refer to Method Statement.

APPLICATION

Prepare Sika® Bonding Primer by adding component B into component A container, mix with an electric drill until a homogeneous light green colour is achieved and the product is free of streaks. The 1 l packaging can be mixed by spatula or flat stick.

Sika® Bonding Primer can be applied by short-piled roller, brush or airless spray.

Allow primer to dry sufficiently (see table waiting time / overcoating) before overcoating.

CLEANING OF TOOLS

Clean all tools and application equipment with water immediately after use. Hardened and/or cured material can only be removed mechanically.

LIMITATIONS

- Do not apply Sika® Bonding Primer on substrates with rising moisture.
- Always ensure good ventilation when using Sika® Bonding Primer in a confined space, to ensure drying and full curing.
- If the primer is damaged by rain, a chalky surface will result and the surface must be re-primed.
- The incorrect assessment and treatment of cracks may lead to a reduced service life and reflective cracking (for further information please contact Sika technical service).
- If heating is required do not use gas, oil, paraffin or

other fossil fuel heaters, these produce large quantities of both CO₂ and H₂O water vapour, which may adversely affect the finish. For heating use only electric powered warm air blower systems.

- New concrete should be allowed to cure/hydrate for a minimum of 10 days, preferably 28 days.

VALUE BASE

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

DIRECTIVE 2004/42/CE - LIMITATION OF EMISSIONS OF VOC

According to the EU-Directive 2004/42, the maximum allowed content of VOC (Product category IIA / j type wb) is 140 / 140 g/l (Limits 2007 / 2010) for the ready to use product.

The maximum content of Sika® Bonding Primer is <140 g/l VOC for the ready to use product.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika re-

serves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA LIMITED

Watchmead
Welwyn Garden City
Hertfordshire, AL7 1BQ
Tel: 01707 394444
Web: www.sika.co.uk
Twitter: @SikaLimited

SIKA IRELAND LIMITED

Ballymun Industrial Estate
Ballymun
Dublin 11, Ireland
Tel: +353 1 862 0709
Web: www.sika.ie
Twitter: @SikaIreland



Product Data Sheet

Sika® Bonding Primer
March 2020, Version 02.02
02091595100000009

SikaBondingPrimer-en-GB-(03-2020)-2-2.pdf