

## PRODUCT DATA SHEET

# Sikaplan®-1652 Bonded VOC Gas Barrier

A pre-applied, multi-layer, polyethylene membrane for below ground waterproofing and gas protection



### PRODUCT DESCRIPTION

Sikaplan®-1652 Bonded VOC Gas Barrier is a pre-applied fully bonded waterproofing membrane incorporating Sikaplan®-1651 Loose VOC Gas Barrier membrane and a heavy duty virgin polypropylene geotextile. The geotextile is laminated to the membrane to provide a dual function; protecting the membrane from damage and providing an integrated 'bond' to poured concrete, ensuring a fully bonded waterproofing barrier which has exceptionally high resistance to ground gas and VOCs. Sikaplan®-1652 Bonded VOC Gas Barrier is used for the Gas/Waterproofing/Tanking of underground structures where harmful ground gases are anticipated.

### USES

- Suitable for use as a ground gas hydrocarbon protection and waterproofing at ground level or below ground installations.

### PRODUCT INFORMATION

<b>Packaging</b>	1.9m x 25m roll Weld Strip - 100mm x 10m roll Edge Strip - 1m x 25m roll												
<b>Shelf Life</b>	Indefinite												
<b>Storage Conditions</b>	Must be stored horizontally, indoors in original packaging.												
<b>Overall Thickness</b>	<table border="1"> <tr> <td>Thickness</td> <td>2.0 mm</td> <td>(EN 1849-2)</td> </tr> <tr> <td>Width</td> <td>1.9 m</td> <td></td> </tr> <tr> <td>Length</td> <td>25 m</td> <td></td> </tr> <tr> <td>Weight</td> <td>650 G/M<sup>2</sup></td> <td></td> </tr> </table>	Thickness	2.0 mm	(EN 1849-2)	Width	1.9 m		Length	25 m		Weight	650 G/M <sup>2</sup>	
Thickness	2.0 mm	(EN 1849-2)											
Width	1.9 m												
Length	25 m												
Weight	650 G/M <sup>2</sup>												

### CHARACTERISTICS / ADVANTAGES

- Quick and easy installation
- A fully welded system
- High resistance to ground gases
- Exceptional chemical resistance
- Manufactured to meet the most up-to-date British Standards and guidance
- Long-term durability (performance guaranteed for the lifetime of the building)

### APPROVALS / STANDARDS

- Conforms to the requirements of EN13967:2012
- NHBC Standards Compliant
- BS 8485:2015 + A1:2019 Compliant (Methane and Carbon Dioxide Barrier)
- CIRIA C748 Compliant (VOC barrier)
- BS 8102:2022 Compliant (Type A Waterproofing Barrier)
- BBA Certified - Certificate No: 19/5681

## TECHNICAL INFORMATION

Resistance to Impact	> 1650 mm	(EN 12691-B)	
Resistance to Static Load	≥ 20 kg	(EN 12730-B)	
Resistance to Static Puncture	≥ 2.5 kN	(EN 12236)	
Tensile Strength	MD	> 550 N/50 mm	(EN 12311-1)
	CMD	> 400 N/50mm	
Elongation	Tensile Elongation (MD)	> 550%	(EN 12310-1)
	Tensile Elongation (CMD)	> 550%	
Adhesion in peel	Concrete Peel Adhesion	> 3.0 kN/m	(ASTM D903 (MOD))
Resistance to Tearing (nail shank)	> 300 N	(EN 12310-1)	
Water Tightness	(60 kPa) - PASS	(EN 1928)	
	(196 kPa - 20 m Water Head) (Basement Application) - PASS	(EN 1928)	
Water Vapour Transimission	0.11-0.18 G/M <sup>2</sup> /DAY	(EN 1931)	
Chemical Resistance	PASS	(EN 1847 / EN 1928)	

### Vapour Permeability 100% Concentration

Transmission rate of Benzene	<3.6 mg/m <sup>2</sup> /day	(EN ISO 15105-2)
Transmission rate of Toluene	<13.8 mg/m <sup>2</sup> /day	
Transmission rate of Ethyl Benzene	<2.7 mg/m <sup>2</sup> /day	
Transmission rate of Xylene (M,P,O)	<7.7 mg/m <sup>2</sup> /day	
Transmission rate of Hexane	<0.6 mg/m <sup>2</sup> /day	
Transmission rate of Vinyl Chloride	<0.05 mg/m <sup>2</sup> /day	
Transmission rate of Trichloroethene (TCE)	<54.7 mg/m <sup>2</sup> /day	
Transmission rate of Tetrachloroethene (PCE)	<26.2 mg/m <sup>2</sup> /day	
Transmission rate of Naphthalene	<0.0006 mg/m <sup>2</sup> /day	
Transmission rate of CIS-1,2-Dichloroethene	<1.1 mg/m <sup>2</sup> /day	

## Gas Permeability

Methane Permeability	0.13 ml/m <sup>2</sup> /day/atm	(EN ISO 15105-1)
Methane Permeability (jointed)	1.00 ml/m <sup>2</sup> /day/atm	
Carbon Dioxide Permeability	3.01 ml/m <sup>2</sup> /day/atm	
Vinyl Chloride Gas Permeability	0.04 ml/m <sup>2</sup> /day/atm	
Radon Permeability	1.0 x 10 <sup>-12</sup> M <sup>2</sup> /S	(K124/02/195)

FOR FULL DURABILITY AND CHEMICAL RESISTANCE INFORMATION, PLEASE CONTACT SIKA WATERPROOFING TECHNICAL

---

## Reaction to Fire

E Class

(EN 13501-1)

---

## VALUE BASE

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## ECOLOGY, HEALTH AND SAFETY

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in the product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0,1 % (w/w)

## APPLICATION INSTRUCTIONS

### INSTALLATION

Sikaplan®-1652 Bonded VOC Gas Barrier should be installed in accordance with the product installation guidelines, and in accordance with BS 8485:2015 + A1:2019 and Ciria C748.

### JOINTING AND SEALING

Sikaplan®-1652 Bonded VOC Gas Barrier must be heat welded on all laps, with welding carried out by competent personnel with suitable qualifications in accordance with best practice, and guidance contained within BS 8485:2015 + A1:2019. Sikaplan®-1652 Bonded VOC Gas Barrier should be overlapped by at least 50mm. Pre-formed corner pieces are available for sealing corners. A separate strip is available for detailing.

### LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

### LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which

will be supplied on request.

**SIKA LIMITED**

Watchmead  
Welwyn Garden City  
Hertfordshire, AL7 1BQ  
Tel: 01707 394444  
Web: [www.sika.co.uk](http://www.sika.co.uk)  
Twitter: @SikaLimited



**Product Data Sheet**  
Sikaplan®-1652 Bonded VOC Gas Barrier  
June 2022, Version 02.02  
020720201000000047

Sikaplan-1652BondedVOCGasBarrier-en-GB-(06-2022)-2-2.pdf

