

**BUILDING TRUST** 

# SYSTEM DATA SHEET Sikafloor<sup>®</sup> MultiDur EB-12 ECC

## SLIP RESISTANT BROADCAST COLOURED EPOXY FLOOR COATING SYSTEM FOR DAMP SUB-STRATES

## **PRODUCT DESCRIPTION**

Sikafloor<sup>®</sup> MultiDur EB-12 ECC is a 2-part epoxy coloured resin based floor coating system that can provide a hard wearing, seamless, low maintenance, slip resistant gloss finish when broadcast with different aggregate grades on damp substrates. For medium - heavy wear conditions. Thickness 2.0–4.0 mm. Internal use.

### USES

Sikafloor<sup>®</sup> MultiDur EB-12 ECC may only be used by experienced professionals.

- On concrete and cementitious screeds with normal up to medium heavy wear e.g. storage and assembly halls, maintenance workshops, garages and loading ramps.
- On multi-storey and underground car park decks and for wet process areas, e.g. beverage and food industry

- **CHARACTERISTICS / ADVANTAGES**
- Seamless
- Good chemical and mechanical resistance
- Easy application
- Waterproof
- Gloss finish
- Easy cleanability
- Low maintenance
- Good bond to green or hardened damp/dry concrete

## **APPROVALS / STANDARDS**

• Refer to individual Product Data Sheet within System Structure

System Data Sheet Sikafloor® MultiDur EB-12 ECC February 2020, Version 01.02 02081190000000079 System Structure

Sikafloor<sup>®</sup> MultiDur EB-12 ECC (~ 2–4 mm)

					— 3
Ne	ALL				— 2 1
				21	1
	all the second	a factor	1		
		al ales			

Layer	Product
1. Primer	Sikafloor®-155 WN
2. Levelling screed and sand broad-	Sikafloor <sup>®</sup> -81 EpoCem <sup>®</sup> , quartz sand
cast	0.3–0.8 mm to excess
3. Seal / Top coat	Sikafloor <sup>®</sup> -264 N

Composition	Ероху
Appearance	Slip resistant gloss finish
Colour	RAL 1001, 6021, 7030, 7032, 7035, 7037, 7038, 7040, 7042, 9002 Other colours on request.
Nominal Thickness	~ 2.0–4.0 mm

## **TECHNICAL INFORMATION**

Abrasion Resistance	~35 mg (CS 10/1000/1000) (8 days / +23 °C) (DIN 53 109 (Taber Abraser Test))		
Compressive Strength	60 N/mm <sup>2</sup> ( 28 days at 23 °C / 50 % R.H.) (EN 1389		
Tensile Strength	14 N/mm <sup>2</sup> (28 days at 23 °C / 50 % R.H.) (EN 13		
Tensile Adhesion Strength	> 1.5 N/mm <sup>2</sup> (failure in concrete) (		
Chemical Resistance	Resistant to many chemicals. Contact Sika Technical Service for specific in- formation.		
Coefficient of Friction	μ = 0,54	(DIN 51131)	
Skid / Slip Resistance	R11 V4	(DIN 51130)	

## **APPLICATION INFORMATION**

Consumption	Layer	Product	Consumption	
	1.Primer	1 × Sikafloor <sup>®</sup> -155 WN	~ 0.3–0.5 kg/m <sup>2</sup> thinned with 10 % water	
	2.Levelling screed	Sikafloor <sup>®</sup> -81 EpoCem <sup>®</sup>	~2.25 kg/m <sup>2</sup> /mm	
	3.Sand Broadcast	Quartz Sand 0.3-0.8 mm	~ 4–6 kg/m²	
		to excess		
	4.Seal / Top coat	1–2 × Sikafloor <sup>®</sup> -264 N	~ 0.6–0.8 kg/m <sup>2</sup>	
Ambient Air Temperature	+10 °C min / +30 °C m	าลx		
Relative Air Humidity	80 % r.h. max.			

System Data Sheet Sikafloor® MultiDur EB-12 ECC

February 2020, Version 01.02 020811900000000079



Dew Point	Beware of condensation! The substrate and uncured floor temperature must be at least 3 °C above the dew point to reduce the risk of condensation or blooming on the floor finish.				
Substrate Temperature	+10 °C min. / +30 °C max.				
Substrate Moisture Content	Can be applied on green or damp concrete, with no standing water. Although the system can be applied onto green concrete surfaces (> 24 hours), it is advised to allow at least 3 days for early concrete shrinkage to occur in order to prevent shrinkage cracks from appearing on the wearing surface.				
Waiting Time / Overcoating	Before applying Sikafloor <sup>®</sup> -81 EpoCem <sup>®</sup> on Sikafloor <sup>®</sup> -155 WN allow:				
	Substrate Temperature Minimum		<u> </u>	/laximum	
	+10 °C 12 hours		72 hours		
	+20 °C	+20 °C 6 hours		48 hours	
	+30 °C	+30 °C 4 hours		24 hours	
	Sikafloor <sup>®</sup> -81 EpoCem <sup>®</sup> can be overcoated with vapour impermeable coat- ings when the surface humidity falls below 4% Not earlier than :				
	Substrate Temperature			Waiting Time	
	+10 °C		2 days		
	+20 °C		1 day		
	+30 °C			<u>1 day</u>	
Applied Product Ready for Use	Temperature	Foot T	raffic	Light Traffic	Full Cure
	+10 °C	~ 72 h	ours	~ 6 days	~ 10 days
	+20 °C	~ 24 hours		~ 4 days	~ 7 days
	+30 °C	~ 18 hours		~ 2 days	~ 5 days
	Note: Times are conditions.	e approxin	nate and v	vill be affected by	r changing ambient

## **PRODUCT INFORMATION**

Packaging	Refer to the individual Product Data Sheet
Shelf Life	Refer to the individual Product Data Sheet
Storage Conditions	Refer to the individual Product Data Sheet

## MAINTENANCE

#### CLEANING

Refer to the Information Manual Sikafloor®-Cleaning Regime

## FURTHER DOCUMENTS

- Sika<sup>®</sup> Information Manual Mixing and Applications of Flooring systems
- Sika<sup>®</sup> Information Manual Evaluation and Prepara-

tion of Surfaces for Flooring systems

## LIMITATIONS

- Sikafloor®-155 WN and Sikafloor®-81 Epo-Cem®: Refer to individual product limitations.
- Freshly applied Sikafloor<sup>®</sup> MultiDur EB-12 ECC must be protected from damp, condensation and water for at least 24 hours.
- The incorrect assessment and treatment of cracks may lead to a reduced service life and reflective cracking.

**BUILDING TRUST** 

For exact colour matching, ensure the Sikafloor<sup>®</sup>-264

System Data Sheet Sikafloor® MultiDur EB-12 ECC February 2020, Version 01.02 02081190000000079



N in each area is applied from the same control batch numbers.

- Under certain conditions, underfloor heating or high ambient temperatures combined with high point loading, may lead to indentations in the resin.
- If heating is required do not use gas, oil, paraffin or other fossil fuel heaters, these produce large quantities of both CO<sub>2</sub> and H<sub>2</sub>O water vapour, which may adversely affect the finish. For heating use only electric powered warm air blower systems.

### VALUE BASE

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

## **LEGAL NOTES**

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product



Watchmead Welwyn Garden City Hertfordshire, AL7 1BQ Tel: 01707 394444 Web: www.sika.co.uk Twitter: @SikaLimited



#### System Data Sheet Sikafloor® MultiDur EB-12 ECC February 2020, Version 01.02

Data Sheet for the product concerned, copies of which will be supplied on request.

SikafloorMultiDurEB-12ECC-en-GB-(02-2020)-1-2.pdf



**BUILDING TRUST**