

PRODUCT DATA SHEET Sarnafil[®] G 410-18 EL Felt

PVC adhered membrane for roof waterproofing

PRODUCT DESCRIPTION

Sarnafil[®] G 410-18 EL Felt is a PVC, multi-layer, fully adhered, lacquered matt finish, weldable sheet membrane with a glass fibre reinforcing inlay and polyester fleece backing for roof waterproofing. Contains ultraviolet light stabilizers and flame retardants to provide a colour stable, fast installation, low maintenance and durable membrane. Thickness 1,8 mm.

USES

• Fully bonded, roof waterproofing membrane for exposed roofs

CHARACTERISTICS / ADVANTAGES

- Proven performance over decades
- Lacquer coated surface
- Various colours available
- Fast installation with Sarnacol[®] adhesives
- Resistant to UV exposure
- High dimensional stability due to glass fleece inlay
- High water vapour permeability
- Resistant to all common environmental influences
- Felt backing compatible with old bitumen surfaces
- Heat weldable

ENVIRONMENTAL INFORMATION

- Conformity with LEED v4 SSc 5 (Option 1): Heat Island Reduction Roof (only traffic white (SR))
- Conformity with LEED v4 MRc 2 (Option 1): Building Product Disclosure and Optimization – Environmental Product Declarations
- Conformity with LEED v4 MRc 3 (Option 2): Building Product Disclosure and Optimization - Sourcing of Raw Materials
- Conformity with LEED v4 MRc 4 (Option 2): Building Product Disclosure and Optimization - Material Ingredients
- BRE Environmental Product Declaration (EPD)

APPROVALS / STANDARDS

- CE Marking and Declaration of Performance to EN 13956 - Polymeric sheets for roof waterproofing
- FM Approved, Certificate of Compliance, Sarnafil® G 410 EL Felt, Approval Identification No. 3047304

Product Data Sheet Sarnafil® G 410-18 EL Felt August 2020, Version 01.01 020905052170181001

PRODUCT INFORMATION

Packaging	-	Standard rolls are wrapped individually in a blue PE-foil.						
	Roll size Length:	Roll size						
	Width:	2,00 m						
	Weigh:							
Appearance / Colour	Surface: Colours:							
	Top surface:	light grey (RAL 7047) lead grey (Sika colour no. 9500) copper patina (Sika colour no. 6525 window grey (RAL 7040) copper brown (RAL 8004) traffic white, (RAL 9016)						
	Bottom surface:							
	Top surface colour available in other colours subject to minimum order quantities.							
Shelf Life	5 years from date of pro	5 years from date of production						
Storage Conditions	Product must be stored in original unopened and undamaged packaging in dry conditions and temperatures between +5 °C and +30 °C. Store in a ho- rizontal position. Do not stack pallets of the rolls on top of each other, or under pallets of any other materials during transport or storage. Always refer to packaging.							
Product Declaration	EN 13956: Polymeric sheets for roof waterproofing							
Visible Defects	Pass	Pass						
Length	15 m (-0 % / +5 %)	15 m (-0 % / +5 %)						
Width	2 m (-0,5 % / +1 %)	2 m (-0,5 % / +1 %)						
Effective Thickness	1,8 mm (-5 % / +10 %)	1,8 mm (-5 % / +10 %)						
Straightness	≤ 30 mm		(EN 1848-2)					
Flatness	≤ 10 mm	≤ 10 mm						
Mass per unit area	2,6 kg/m² (-5 % / +10 %)	(EN 1849-2)					
TECHNICAL INFORMATION	N							
Resistance to Impact	hard substrate soft substrate	≥ 800 mm ≥ 1750 mm	(EN 12691)					
Hail Resistance	rigid substrate flexible substrate	≥ 25 m/s ≥ 33 m/s	(EN 13583)					
Resistance to Static Load	soft substrate rigid substrate	≥ 20 kg ≥ 20 kg	(EN 12730)					
Tensile Strength	longitudinal (md)1) transversal (cmd)2)	≥ 750 N/50 mm ≥ 750 N/50 mm	(EN 12311-2)					

1) md = machine direction

2) cmd = cross machine direction

Product Data Sheet Sarnafil[®] G 410-18 EL Felt August 2020, Version 01.01 020905052170181001



Elongation	longitudinal (md)1) transversal (cmd)2)			≥ 65 %			(EN 12311-2)	
	transversal	(cma)	2)	≥ 65 %				
	 md = machine cmd = cross m 							
Dimensional Stability	longitudinal (md)1)			≤ 0,2 %			(EN 1107-2)	
	transversal	(cmd)	2)	≤ 0,1 %				
	1) md = machine direction 2) cmd = cross machine direction							
Joint Peel Resistance	≥ 300 N/50 mm						(EN 12316-2)	
Joint Shear Resistance	≥ 600 N/50 mm						(EN 12317-2)	
Foldability at Low Temperature	≤ -25°C						(EN 495-5)	
Reaction to Fire	Class E (EN ISO 11925-2, classific						ation to EN 13501-1)	
Effect of Liquid Chemicals, Including Water	Resistant to many chemicals. Contact Sika Technical Services for additional informatior						(EN 1847) n	
UV Exposure	Pass (> 5'000 h / grade 0)						(EN 1297)	
Water Vapour Transimission	μ = 15'000	(EN 1931)						
Water Tightness	Pass (EN 1928)							
Solar Reflectance Index	Colour	Init	ial	3-years a	ged	Test Insti- tute	(ASTM E 1980)	
	RAL 9016	106	5	77		CRRC		
	Nr. 9525	55				Sika		
	Nr. 9500	4				Sika		
	CRRC testec data base.	l prod	ucts are lis	sted in Coc	l Ro	of Rating Coun	cil (CRRC) product	
USGBC LEED Rating	Colour RAL 9016 SR				ears aged	(ASTM E 1980)		
					SRI > 64			
	RAL 9016 traffic white		SRI > 82 S		SRI > 64			

APPLICATION INFORMATION

 Ambient Air Temperature
 -20 °C min. / +60 °C max.

 Substrate Temperature
 -30 °C min. / +60 °C max.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

The substrate surface/supporting layer must be uniform, smooth and free of any sharp protrusion or burrs, clean, dry and free of grease, bitumen, oil and dust. All layers of the roof build-up and substrate must be secured against wind uplift. Metal sheets must be degreased with Sarna Cleaner before adhesive application.

APPLICATION METHOD / TOOLS

Strictly follow installation procedures as defined in method statements, application manuals and working instructions which must always be adjusted to the actual site conditions.

Installation procedure

Reference must be made to the installation instructions: Sarnafil® G 410-EL types system fully bonded for exposed roofs.

Fully bonded roof surfaces and detailing

The membrane is bonded to the substrate by Sarnacol[®] 2170 / 2172/2142V adhesive depending on the type of substrate and slope.

Welding overlap seams

All membrane seam overlaps must be welded by using hand welding guns and pressure rollers or automatic heat welding machines, with individually adjustable and electronically controlled welding temperatures. **Recommended welding equipment**

Manual - Leister Triac PID. Automatic - Sarnamatic 681. Welding parameters, such as speed and temperature must be established with trials on site, prior to any welding works. The effective width of welded





overlaps by hot air must be minimum 20 mm. The seams must be mechanically tested with a screw driver (rounded edges) to ensure the integrity / completion of the weld. Any imperfections must be rectified by hot air welding.

Bonding to flashings

Sarnafil[®] G 410-18 EL Felt (CH_CE) is bonded to flashing surfaces using Sarnacol[®] 2170 / 2172 Spray adhesive.

FURTHER DOCUMENTS

• Installation instructions: Sarnafil[®] G 410-EL types system fully bonded for exposed roofs.

LIMITATIONS

Installation work must only be carried out by Sika[®] trained and approved contractors experienced in this type of application.

- Do not apply to wet, damp or unclean surfaces
- Installation of some ancillary products, e.g. contact adhesives / cleaners are limited to temperatures above +5 °C. (Refer to appropriate Product Data Sheet).
- Be aware special measures may be compulsory for certain installations below +5 °C ambient temperature due to safety and national regulations.

VALUE BASE

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

Fresh air ventilation must be ensured, when working (welding) in closed rooms.

REGULATION (EC) NO 1907/2006 - REACH

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in the product data sheet.Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0,1 % (w/w)

Product Data Sheet Sarnafil® G 410-18 EL Felt August 2020, Version 01.01 020905052170181001



LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

TECHNICAL ENQUIRIES Tel: 01707 358500 Web: www.sarnafil.co.uk Twitter: @SikaSarnafilUK



000 "Зика"

Россия

141730, г. Лобня

Тел. +7 (495) 5 777 333 Email: info@ru.sika.com www.sika.com

Product Data Sheet Sarnafil® G 410-18 EL Felt August 2020, Version 01.01 020905052170181001 SarnafilG410-18ELFelt-en-GBSARNA-(08-2020)-1-1.pdf

