

PRODUCT DATA SHEET

Sikalastic® D-10 RoofPro

ONE-COMPONENT, LIQUID APPLIED POLYURETHANE WATERPROOFING MEMBRANE

PRODUCT DESCRIPTION

Sikalastic® D-10 RoofPro is a one-component, cold applied, moisture-triggered polyurethane membrane. It cures to form a seamless and durable waterproofing solution for exposed roof areas and structures.

USES

Sikalastic® D-10 RoofPro may only be used by experienced professionals.

- For roof waterproofing solutions in both new construction and refurbishment projects
- For roofs displaying complex detail areas, even when accessibility is limited
- For cost efficient life cycle extension of failing roofs

CHARACTERISTICS / ADVANTAGES

- Single component No mixing, easy and ready to use
- Cold applied requires no heat or flame
- Seamless membrane
- Compatible with Sika® Reemat Premium easy to detail
- Easily recoated when needed no stripping required
- Economic provides a cost efficient life cycle extension of failing roofs
- Vapour permeable allows substrate to breathe
- Elastic retains flexibility even at low temperatures
- Good adhesion to most substrates see table
- Fast curing Free from rain damage almost immediately on application

APPROVALS / STANDARDS

- UK Technical Assessment (No. UKTA-0836-23/6852)
- Declaration of Performance No. 79168137

PRODUCT INFORMATION

Chemical Base	One-component, moisture-triggered aromatic polyurethane		
Packaging	15 Litre tin		
Colour	Standard colours available are RAL 7045 (Cloud Grey) and RAL 7011 (Storm Grey). Non-standard colours may be available subject to minimum order quantities and extended lead times.		
Shelf Life	9 months from date of production		
Storage Conditions	The product must be stored properly in original, unopened and undamaged sealed packaging in dry conditions at temperatures >0 °C and <+25 °C. Higher storage temperatures may reduce shelf life of product. Reference shall also be made to the storage recommendations within the safety data sheet.		
Density	~1.38 kg/l (23 °C)	(EN ISO 2811-1)	
Solid content by mass	~79 % (+23 °C / 50 % r.h.)		
Solid content by volume	~67 % (+23 °C / 50 % r.h.)		

Product Data Sheet Sikalastic® D-10 RoofPro June 2025, Version 01.06 020915205000000083

Tensile Strength	Not Reinforced ~ 4.6 N/mm2	Reinfor ~ 18 N/		(EN ISO 527-3)
Elongation at Break	Not Reinforced ~150 %	Reinfor ~20 %	ced	(EN ISO 527-3)
Reaction to Fire	Euroclass E Ext F.AA rating Non Comb	oustible sub	ostrates	(EN 13501) (BS 476-3)
Service Temperature	–20 °C min./ +90 °C max.	−20 °C min./ +90 °C max.		
APPLICATION INFORMAT	TION			
Ambient Air Temperature	+5 °C min. / +40 °C max.			
Relative Air Humidity	5 % r.h. min. / 85 % r.h. n	nax.		
Substrate Temperature	+5 °C min. / +60 °C max. ≥ 3 °C above dew point			
Substrate Moisture Content	≤ 4 % pbw moisture content. Test method: Sika®-Tramex meter No rising moisture according to ASTM (Polyethylene-sheet).			
Substrate Pre-Treatment	Substrate		Primer	
	Cementitious substrates		Sika® Concrete P Sika® Bonding Pr	
	Brick and Stone		Not required	
	Ceramic tiles (unglazed),	and con-	Sika® Concrete Primer LO or	
	crete slabs		Sika® Bonding Pr	
	Asphalt		Not required, subject to surface assessment tests	
	Bituminous felt		Not required, only fully reinforced systems	
	Single Ply		Adhesion to single ply may vary according to type, age etc. Adhesion test required	
	Bituminous Coating		Not required	
	Metals		Sikalastic® Meta	l Primer N or Sika®
	Ferrous or galvanised me copper, aluminium, brass less steel		Primer 207	
	Wooden substrates		Timber based roof decks require a complete layer of Sikalastic® Carrier. For small exposed timber sections, use Sika® Concrete Primer LO or Sika® Bonding Primer	
	Paints		_	ion and compatib-
	Existing Sika Liquid Plastic	cs System	Sika® Reactivation	on Primer
	For the consumption rates and waiting time / overcoating you should refer to the PDS of the appropriate cleaner and primer. Other substrates must be tested for their compatibility. If in doubt, apply a test area first.			
Pot Life	Sikalastic® D-10 RoofPro is designed for fast drying. High temperatures combined with high air humidity will increase the curing process. Thus, material in opened containers should be applied immediately. In opened containers, the material will form a film after 1 hour approx. (+20 °C / 50 % r.h.)			





Waiting Time / Overcoating

Ambient conditions	Minimum waiting time*
+5 °C / 50 % r.h.	18 hours
+10 °C / 50 % r.h.	8 hours
+20 °C / 50 % r.h.	6 hours
+30 °C / 50 % r.h.	4 hours

Note: Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity.

After four days the surface must be cleaned and primer with Sika® Reactivation Primer before continuing.

Applied Product Ready for Use

Ambient conditions	Rain resistant*	Touch dry	Full cure
+5 °C / 50 % r.h.	10 minutes	10 hours	19 hours
+10 °C / 50 % r.h.	10 minutes	6 hours	10 hours
+20 °C / 50 % r.h.	10 minutes	4.5 hours	6 hours
+30 °C / 50 % r.h.	10 minutes	2 hours	4 hours

*Be aware that impact of heavy rain or rain showers can physically damage the still liquid membrane. Note: Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity.

System Structure

Reinforced Roof Waterproofing

Sikalastic® D-10 RoofPro is applied in one coat reinforced with Sika® Reemat Premium and sealed with a further coat of Sikalastic® D-10 RoofPro

Product	Consumption
Please refer to sub-	Refer to primer data
strate pre-treatment	sheet
Sikalastic® D-10	≥ 1.0 l/m2
RoofPro	(≥ 1.42 kg/m2)
Sika® Reemat Premium	-
Sikalastic® D-10	≥ 0.75 l/m2
RoofPro	(≥ 1.06 kg/m2)
	Please refer to sub- strate pre-treatment Sikalastic® D-10 RoofPro Sika® Reemat Premium Sikalastic® D-10

Note: These figures are theoretical and do not include for any additional material required due to surface porosity, surface profile, variations in level and wastage.

VALUE BASE

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LIMITATIONS

- Do not apply Sikalastic® D-10 RoofPro on substrates with rising moisture.
- Sikalastic D-10 RoofPro is not suitable for permanent water immersion.
- On substrates likely to exhibit out-gassing, apply during falling ambient and substrate temperature. If applied during rising temperatures "pin holing" may occur from rising air.
- Do not dilute Sikalastic® D-10 RoofPro with any solvent.
- Do not use Sikalastic® D-10 RoofPro for indoor applications.
- Do not apply close to the air intake vent of a running air conditioning unit.
- Do not apply Sikalastic® D-10 RoofPro directly on Sika® Insulation boards. Instead use a Sika® Carrier between Sika® Insulation board and Sikalastic® D-10 RoofPro.

- Volatile bituminous materials may stain and or soften below the coating.
- Areas with high movement, irregular substrates, or timber based roof decks require a complete layer of Sikalastic® Carrier.
- Do not apply cementitious products (e.g. tile mortar) directly onto Sikalastic® D-10 RoofPro.
- Sikalastic® D-10 RoofPro may exhibit slight chalking at the surface – do not use run off water for live fish tanks, etc.
- Volatile bituminous materials may stain and or soften below the coating.
- Low melting point bituminous materials may need priming – using a darker shade also helps hide any staining from the volatiles.

Product Data Sheet Sikalastic® D-10 RoofPro June 2025, Version 01.06 020915205000000083



ECOLOGY, HEALTH AND SAFETY

SUBSTRATE PREPARATION

The surface must be sound, of sufficient strength, clean, dry and free of dirt, oil, grease and other contamination. Depending on the material the substrate must be primed or mechanically cleaned. Grinding may be necessary to level the surface. Suitable substrates are such as: concrete, bituminous felts and coatings, metal, brickwork, asbestos cement, ceramic tiles, wooden substrates.

MIXING

Mixing is not required, however if the product is settled or separated on opening, stir Sikalastic® D-10 RoofPro gently but thoroughly in order to achieve a uniform colour. Stirring gently will minimise air entrainment.

APPLICATION

Prior the application of Sikalastic® D-10 RoofPro the priming coat if used must have cured tack-free. For the Waiting Time / Overcoating please refer to the PDS of the appropriate primer. Damageable areas (handrails, etc) have to be protected with tape or plastic wrapping.

Reinforced Roof Waterproofing:

Sikalastic® RoofPro is applied in combination with Sika Reemat Premium.

- Apply first coat of approximately 1 l/m2 of Sikalastic® D-10 RoofPro. Work only so far in advance that the material stays liquid.
- 2. Roll in the Sikalastic® Reemat Premium. Overlap it a minimum 5 cm and ensure overlaps are sufficiently wet to bond both layers.
- 3. The roller may require only a little extra material to keep wet but no further significant material needs to be added at this stage.
- 4. After the coat is dry enough to walk on, seal the roof area with second coat of Sikalastic® D-10 RoofPro at a minimum 0.75 l/m2 per coat.

Please note, always begin with details prior starting with waterproofing the horizontal surface. For details follow step 1-4.

CLEANING OF TOOLS

Clean all tools and application equipment with Thinner C immediately after use. Hardened and/or cured material can only be removed mechanically.

SIKA LIMITED

Watchmead Welwyn Garden City Hertfordshire, AL7 1BQ Tel: 01707 394444 Web: www.sika.co.uk Twitter: @SikaLimited







Product Data Sheet Sikalastic® D-10 RoofPro June 2025, Version 01.06 020915205000000083

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SikalasticD-10RoofPro-en-GB-(06-2025)-1-6.pdf

