

## PRODUCT DATA SHEET

# Sika® Fibermesh®-300 (GB)

### Micro-Synthetic Fibrillated Fibre

#### PRODUCT DESCRIPTION

Sika® Fibermesh®-300 (GB), micro-reinforcement system for concrete is made up of 100 percent virgin polypropylene fibrillated fibres, containing no reprocessed materials. Engineered and manufactured in an ISO 9001 certified manufacturing facility for use in concrete.

#### USES

Sika® Fibermesh®-300 (GB) is a micro fiber that acts mechanically by supporting the aggregate within the concrete with multidimensional fibre network and helps to develop a uniform bleed in the concrete system. The fibre does not affect the curing process chemically and it does not absorb water. Sika® Fibermesh®-300 (GB) can be used in all types of concrete applications to control plastic shrinkage and settlement cracking.

Typical applications include:

- Footpaths, driveways, decks, curbs
- Overlays & toppings
- Roads & pavements
- Tanks & pools

#### CHARACTERISTICS / ADVANTAGES

- Reduces plastic shrinkage and settlement cracking.
- Improves impact, shatter and abrasion resistance
- Enhances durability
- Promotes uniform bleed and reduces bleed water
- Reduces freeze / thaw damage
- Increases cohesion and reduces segregation

#### APPROVALS / STANDARDS

Conforms to the requirements of EN 14889-2:2006, Fibres for Concrete - Polymer Fibres, Class Ib. Sika® Fibermesh®-300 (GB) e3: DoP 10676944, certified by Factory Production Control Body 1136 and provided with the CE mark

#### PRODUCT INFORMATION

<b>Packaging</b>	Sika® Fibermesh®-300 (GB) e3 is available in 0.9 kg degradable bags. The bags are packed into boxes and palletized.
<b>Appearance / Colour</b>	Fibrillated micro synthetic fibre
<b>Shelf Life</b>	5 years from date of production if stored in dry, unopened and undamaged packaging.
<b>Storage Conditions</b>	Protected from moisture and direct sunlight
<b>Dimensions</b>	Sika® Fibermesh®-300 (GB) e3 <ul style="list-style-type: none"> <li>▪ Length: 12-19 mm graded</li> <li>▪ Equivalent Diameter (unfibrillated tape): 0.917 mm</li> </ul>
<b>Melting Point</b>	162°C (324°F)

## TECHNICAL INFORMATION

Resistance to Alkalinity	Excellent
--------------------------	-----------

## APPLICATION INFORMATION

Recommended Dosage	Typical dosage 0.9 - 1.8 kg/m <sup>3</sup>
--------------------	--

Dispensing	Sika® Fibermesh®-300 (GB) in degradable bags can be added directly to the plant mixer or concrete mixer truck after the batching of the other ingredients and mixed for 4 to 5 minutes or 70 revolutions.
------------	---

## VALUE BASE

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## ECOLOGY, HEALTH AND SAFETY

### REGULATION (EC) NO 1907/2006 - REACH

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in the product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0,1 % (w/w).

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### SIKA LIMITED

Watchmead  
Welwyn Garden City  
Hertfordshire, AL7 1BQ  
Tel: 01707 394444  
Web: [www.sika.co.uk](http://www.sika.co.uk)  
Twitter: @SikaLimited



Product Data Sheet  
Sika® Fibermesh®-300 (GB)  
March 2023, Version 01.01  
021408021010000165

SikaFibermesh-300GB-en-GB-(03-2023)-1-1.pdf