

## PRODUCT DATA SHEET

# Sikaplan® WP 1100-30 HL

3.0 mm thick PVC sheet waterproofing membrane for basements and tunnels

### PRODUCT DESCRIPTION

Sikaplan® WP 1100-30 HL is a flexible, 3.0 mm thick, homogeneous sheet waterproofing membrane. It contains a signal layer and is based on high-quality polyvinylchloride (PVC-p).

### USES

The Product is designed for:

- Waterproofing of basements against water ingress
- Waterproofing of tunnels against water ingress

### CHARACTERISTICS / ADVANTAGES

- Part of the complete waterproofing membrane system
- Proven performance over decades
- Contains no recycled materials and no DEHP (DOP) plasticisers
- High resistance to ageing

- Good resistance to microbial degradation
- Good resistance to root penetration
- Suitable for contact with acidic (soft) water and alkaline environments
- Optimised flexibility, tensile strength and multi-axial elongation
- Optimised workability and thermally weldable

### APPROVALS / STANDARDS

- CE Marking and Declaration of Performance to EN 13491 - Geosynthetic barriers — Characteristics required for use as a fluid barrier in the construction of tunnels and underground structures
- CE Marking and Declaration of Performance to EN 13967 — Flexible sheets for waterproofing - Damp proofing and basement tanking

### PRODUCT INFORMATION

<b>Chemical Base</b>	PVC-p	
<b>Packaging</b>	Roll width	2.2 m
	Roll length	20 m or specified
<b>Shelf Life</b>	5 years from date of production	
<b>Storage Conditions</b>	The Product must be stored in original unopened and undamaged sealed packaging in dry conditions and temperatures between +5 °C and +35 °C. Protect the Product from direct weather exposure. Store in a horizontal position. Do not stack pallets of the rolls on top of each other, or under pallets of any other materials during transport or storage. Always refer to packaging.	
<b>Appearance / Colour</b>	Surface texture	smooth
	Signal layer colour	yellow
	Bottom layer colour	black

<b>Effective Thickness</b>	3.00 mm (-0.15 mm / +0.30 mm)		(EN 1849-2)
<b>Mass per unit area</b>	3.90 kg/m <sup>2</sup> (-0.19 kg/m <sup>2</sup> / +0.39 kg/m <sup>2</sup> )		(EN 1849-2)
<b>TECHNICAL INFORMATION</b>			
<b>Resistance to Static Load</b>	No perforation at 20 kg for 24 h		(EN 12730)
<b>Resistance to Static Puncture</b>	3.4 kN ± 0.3 kN		(EN ISO 12236)
<b>Long Term Compression Strength</b>	Water tightness, aged 48 hours	Watertight at 7.0 N/mm <sup>2</sup>	(ÖBV Annex 1)
<b>Tensile Strength</b>	Longitudinal (MD)	17 N/mm <sup>2</sup> ± 2 N/mm <sup>2</sup>	(EN ISO 527-3)
	Transversal (CMD)	16 N/mm <sup>2</sup> ± 2 N/mm <sup>2</sup>	
	Longitudinal (MD)	17 N/mm <sup>2</sup> ± 2 N/mm <sup>2</sup>	(EN 12311-2)
	Transversal (CMD)	16 N/mm <sup>2</sup> ± 2 N/mm <sup>2</sup>	
<b>Elongation</b>	At break, longitudinal (MD)	> 300 %	(EN ISO 527-3)
	At break, transversal (CMD)	> 300 %	
<b>Burst Strength</b>	D = 1.0 m	≥ 80 %	(EN 14151)
<b>Joint Shear Resistance</b>	> 1350 N / 50 mm		(EN 12317-2)
<b>Service Temperature</b>	Minimum	-10 °C	
	Maximum	+35 °C	
<b>Ambient Maximum Temperature of Liquids</b>	+35 °C		

<b>Foldability at Low Temperature</b>	No cracks at -20 °C	(EN 495–5)
<b>Water Tightness</b>	Tested 24 hours at 60 kPa pass	(EN 1928)
<b>Chemical Resistance</b>	Change in tensile strength, 5–6 % sulphurous acid test, aged 90 days at +23 °C	< 20 % (EN 1847)
	Foldability at low temperatures, 5–6 % sulphurous acid test, aged 90 days at +23 °C	No cracks at -20 °C
	Change in impact load, saturated lime wash, aged 360 days at +50 °C	≤ 30 % (EN 1847; EN 12691)
	Change in tensile strength and elongation, saturated lime wash, aged 360 days at +50 °C	< 20 % (EN 14415)
	Change in mass, saturated lime wash, aged 360 days at +50 °C	< 4 %
<b>Behaviour after Storage in Warm Water</b>	Change in tensile strength, aged 360 days at +70 °C	< 20 % (EN 14415)
	Change in elongation, aged 360 days at +70 °C	< 20 %
	Change in mass, aged 360 days at +70 °C	< 4 %
	Reduction of impact load, aged 360 days at +70 °C	≤ 30 %
	Dimensional change, aged 360 days at +70 °C	< 2 %
<b>Resistance to Oxidation</b>	Change in tensile strength, aged 120 days at +80 °C	< 10 % (EN 14575)
	Change in elongation, aged 120 days at +80 °C	< 10 %
	Foldability at low temperatures, aged 120 days at +80 °C	No cracks at -20 °C
<b>Microbiological Resistance</b>	Change in tensile strength, aged 16 weeks	< 15 % (EN 12225)
	Change in elongation, aged 16 weeks	< 15 %
<b>Durability of Water Tightness against Chemicals</b>	Aged 28 days at +23 °C, tested 24 hours at 60 kPa pass	(EN 1847)
<b>UV Exposure</b>	Not permanently UV stable	
<b>Resistance to Weathering</b>	Not resistant to permanent weathering	
<b>Dimensional Change after Heat</b>	Longitudinal (MD), aged 6 hours at +80 °C	< 2 % (EN 1107-2)
	Transversal (CMD), aged 6 hours at +80 °C	< 2 %
<b>Durability of Water Tightness against Ageing</b>	Aged 12 weeks, tested 24 hours at 60 kPa pass	(EN 1296)

## SYSTEM INFORMATION

### System Structure

#### Ancillary Products:

- Sika® FlexoDrain
- Sikaplan® Geotextiles
- Sika® Drains
- Sika® W Tundrains
- Sikaplan® WP Drainage Angles
- Sikaplan® WP Disc
- Sika® Waterbars WP
- Sikaplan® WP Tape
- Sikaplan® WP Control Sockets
- Sikaplan®-8 Separation
- Sikaplan® WP Trumpet Flange
- Sika® Anchors
- Sikaplan® WP Protection Sheets

## VALUE BASE

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## ECOLOGY, HEALTH AND SAFETY

### REGULATION (EC) NO 1907/2006 - REACH

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in the product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0,1 % (w/w).

## APPLICATION INSTRUCTIONS

### IMPORTANT

#### Strictly follow installation procedures

Strictly follow installation procedures as defined in Method Statements, application manuals and working instructions which must always be adjusted to the actual site conditions.

### SUBSTRATE QUALITY

For information on substrate quality / pre-treatment, refer to the following Sika® method statement:

- Sikaplan® WP sheet membrane (PVC) system for waterproofing basements and other below ground structures
- Sikaplan® WP sheet membrane (PVC) system for waterproofing tunnel

## APPLICATION METHOD / TOOLS

For information on application, refer to the following Sika® method statement:

- Sikaplan® WP sheet membrane (PVC) system for waterproofing basements and other below ground structures
- Sikaplan® WP sheet membrane (PVC) system for waterproofing tunnels

### IMPORTANT

#### Application by trained personnel

The application of this Product must only be carried out by Sika® trained and/or approved contractors, experienced in this type of application.

### IMPORTANT

#### Ventilation in confined spaces

Always ensure good ventilation when applying the Product in a confined space.

### IMPORTANT

#### Not resistant to bitumen and plastics

The Product is not resistant to permanent contact with bitumen and some types of plastics other than PVC.

1. For use over or adjacent to these materials, apply a separation layer of polypropylene geotextile ( $\geq 150$  g/m<sup>2</sup>).

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### SIKA LIMITED

Watchmead  
Welwyn Garden City  
Hertfordshire, AL7 1BQ  
Tel: 01707 394444  
Web: [www.sika.co.uk](http://www.sika.co.uk)  
Twitter: @SikaLimited



**Product Data Sheet**  
Sikaplan® WP 1100-30 HL  
December 2021, Version 04.01  
020720101000000011

SikaplanWP1100-30HL-en-GB-(12-2021)-4-1.pdf