

BUILDING TRUST

PRODUCT DATA SHEET

SikaWrap®-900 C

STITCHED UNIDIRECTIONAL CARBON FIBRE FABRIC, DESIGNED FOR STRUCTURAL STRENGTHEN-ING APPLICATIONS AS PART OF THE SIKA® STRENGTHENING SYSTEM

PRODUCT DESCRIPTION

SikaWrap®-900 C is a unidirectional, fleece stabilised stitched heavy carbon fibre fabric made of mid-range strength carbon fibres, designed for installation using the wet application process.

USES

SikaWrap®-900 C may only be used by experienced professionals.

Structural strengthening of reinforced concrete, masonry, brickwork and timber elements or structures, to increase flexural and shear loading capacity for:

- Improved seismic performance of masonry walls
- Replacing missing steel reinforcement
- Increasing the strength and ductility of columns
- Increasing the loading capacity of structural elements
- Enabling changes in use / alterations and refurbishment
- Correcting structural design and / or construction defects
- Increasing resistance to seismic movement
- Improving service life and durability
- Structural upgrading to comply with current standards

CHARACTERISTICS / ADVANTAGES

- Multifunctional fabric for use in many different strengthening applications
- Flexible and accommodating of different surface planes and geometry (beams, columns, chimneys, piles, walls, soffits, silos etc.)
- Low density for minimal additional weight
- Extremely cost effective in comparison to traditional strengthening techniques

APPROVALS / STANDARDS

- USA: ACI 440.2R-08, Guide for the Design and construction of Externally Bonded FRP Systems for strengthening concrete structures, July 2008
- UK: Concrete Society Technical Report No. 55, Design guidance for strengthening concrete structures using fibre composite material, 2012.

PRODUCT INFORMATION

| Construction | Fibre orientation | 0° (unidire | 0° (unidirectional) Black carbon fibres 96 % | | |
|--------------|---|---|--|--|--|
| | Warp | Black carb | | | |
| | Fleece/Stitch | Stabilising fleece white stitch yarn 4 % | | | |
| Fibre type | Selected mid-range strength carbon fibres | | | | |
| Packaging | | Fabric length per roll | Fabric width | | |
| | 2 rolls in cardboard box | ≥ 30 m | 300 mm | | |

Product Data Sheet

SikaWrap®-900 CFebruary 2020, Version 01.02
020206020010000044

| Shelf Life | 24 months from date of production | | | | |
|--|--|-----------------------|---------------------------------|---------------|--|
| Storage Conditions | Store in undamaged, original sealed packaging, in dry conditions at temperatures between +5 °C and +35 °C. Protect from direct sunlight. | | | | |
| Dry Fibre Density | 1.81 g/cm ³ | | | | |
| Dry Fibre Thickness | 0.478 mm (based on fibre content) | | | | |
| Area Density | 865 g/m ² ± 45 g/m ² (carbon fibres only) | | | | |
| Dry Fibre Tensile Strength | 3 800 N/mm² | | | (ASTM D 4018) | |
| Dry Fibre Modulus of Elasticity in Tension | 242 000 N/mm ² | | | (ASTM D 4018) | |
| Dry Fibre Elongation at Break | 1.43 % | | | (ASTM D 4018) | |
| TECHNICAL INFORMATION | | | | | |
| Laminate Nominal Thickness | 0.478 mm | | | | |
| Laminate Nominal Cross Section | 478 mm² per m width | | | | |
| Laminate Tensile Strength | Average 3 000 N/mm² | Charac 2 400 N | | (EN 2561*) | |
| Laminate Tensile Modulus of Elasticity | Average 225 kN/mm ² | Charac 200 kN | | (EN 2561*) | |
| | * modification: sample with 50 Values in the longitudinal direc Single layer, minimum 27 samp | tion of the fibres | | | |
| Tensile Resistance | Average | | Characteristic | | |
| | 1 434 N/mm | | 1 147 N/mm | | |
| Tensile Stiffness | Average | | Characteristic | | |
| | 107.6 MN/m | | 95.6 MN/m | | |
| CVCTENA INICODNANTION | 107.6 kN/m per ‰ el | ongation | 95.6 kN/m per ‰ 6 | eiongation | |
| SYSTEM INFORMATION | | | | | |
| System Structure | The system build-up and configuration as described must be fully complied with and may not be changed. | | | | |
| | Concrete substrate adhesive primer Sikadur®-330 | | _ | | |
| | Impregnating / laminating resin Structural strengthening fabric | | Sikadur®-300 SikaWrap®-900 C | | |
| | For detailed informati the resin and fabric a Sikadur®-300 Product | oplication deta | | . • | |
| APPLICATION INFORMATION | N | | | | |
| Consumption | Wet application with Sikadur®-300, primer Sikadur®-330 | | | | |
| | $ \begin{array}{c} \underline{\text{Primer layer}} & \underline{\text{0.6-0.8 kg/m}^2} \\ \underline{\text{Fabric layers}} & \underline{\text{1.0 kg/m}^2} \end{array} $ | | | | |
| | Refer to the relevant Technical Information Manual for further informa- | | | | |

| Consumption | Wet application with Sikadur®-300, primer Sikadur®-330 | | | |
|-------------|---|---------------------------|--|--|
| | Primer layer | 0.6-0.8 kg/m ² | | |
| | Fabric layers | 1.0 kg/m ² | | |
| | Refer to the relevant Technical Information Manual for further information. | | | |



APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

Minimum substrate tensile strength: 1.0 N/mm² or as specified in the strengthening design.
Refer to the relevant Technical Information Manual

for further information.

SUBSTRATE PREPARATION

Concrete must be cleaned and prepared to achieve a laitance and contaminant free, open textured surface. Refer to the relevant Technical Information Manual for further information.

APPLICATION METHOD / TOOLS

The fabric can be cut with special scissors or a Stanley knife (razor knife / box-cutter knife). Never fold the fabric

SikaWrap®-900 C is applied using the wet application process.

Refer to the relevant Technical Information Manual for details on the impregnating / laminating procedure

FURTHER DOCUMENTS

Technical Information Manuals

Ref. 850 41 03: SikaWrap® manual wet application Ref. 850 41 04: SikaWrap® machine wet application

LIMITATIONS

- SikaWrap®-900 C shall only be applied by trained and experienced professionals.
- A specialist structural engineer must be consulted for any structural strengthening design calculation.
- SikaWrap®-900 C fabric is coated to ensure maximum bond and durability with the Sikadur® adhesives / impregnating / laminating resins. To maintain and ensure full system compatibility, do not interchange different system components.
- SikaWrap®-900 C can be over coated with a cementitious overlay or other coatings for aesthetic and / or protective purposes. The over coating system selection is dependent on the exposure and the project specific requirements. For additional protection against UV light in exposed areas use Sikagard®-550 W Elastic, Sikagard® ElastoColor-675 W GB or Sikagard®-680 S.
- Rfer to Technical Information Manual of SikaWrap® manual wet application (Ref. 850 41 03) or SikaWrap® machine wet application (Ref. 850 41 04) for further information, guidelines and limitations.

SIKA LIMITED

Watchmead Welwyn Garden City Hertfordshire, AL7 1BQ Tel: 01707 394444 Web: www.sika.co.uk Twitter: @SikaLimited







Product Data Sheet SikaWrap®-900 C February 2020, Version 01.02 020206020010000044

VALUE BASE

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

ECOLOGY, HEALTH AND SAFETY

REGULATION (EC) NO 1907/2006 - REACH

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in this product data sheet.Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0.1 % (w/w)

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SikaWrap-900C-en-GB-(02-2020)-1-2.pdf

