

SYSTEM DATA SHEET

Sikafloor® MultiDur EB-27

SLIP RESISTANT BROADCAST COLOURED EPOXY FLOOR SYSTEM

PRODUCT DESCRIPTION

Sikafloor® MultiDur EB-27 is a 2-part epoxy coloured resin based flooring system that can provide a hard wearing, seamless, low maintenance, slip resistant finish when broadcast with different aggregate grades. For medium - heavy wear conditions. Thickness 2.0–4.0 mm. Internal use

USES

Sikafloor® MultiDur EB-27 may only be used by experienced professionals.

- On concrete and cementitious screeds with normal up to medium heavy wear e.g. storage and assembly halls, maintenance workshops, garages and loading ramps.
- On multi-storey and underground car park decks and for wet process areas, e.g. beverage and food industry

CHARACTERISTICS / ADVANTAGES


- Seamless
- High wear resistance
- Good chemical and mechanical resistance
- Easy application
- Waterproof
- Gloss finish
- Slip resistant
- Low maintenance

APPROVALS / STANDARDS

Fire classification test, Bfl-S1 according to DIN EN 13501-1.

SYSTEM INFORMATION

System Structure



Sikafloor® MultiDur EB-27 system (~ 2–4 mm)

Layer	Product	
1. Primer	Sikafloor®-150/-151	
2. Wearing finish	Sikafloor®-263 SL N or Sikafloor®- 264 N broadcast with quartz sand in	
	excess	
3. Seal /Top coat	Sikafloor®-264 N	

Composition	Ероху
Appearance	Slip resistant, gloss finish
Colour	Available in many colours
Nominal Thickness	~2.0– 4.0 mm

TECHNICAL INFORMATION

Reaction to Fire	Bfl-S1 (DIN EN 13501-	
Chemical Resistance	Resistant to many chemicals. formation.	Contact Sika Technical Service for specific in-
Thermal Resistance	Exposure*	Dry heat
	Permanent	+50 °C
	Short-term max. 7 d	+80 °C
	Short-term max. 12 h	+100 °C
	Short-term moist/wet heat* up to +80 °C where exposure is only occasional (i.e. during steam cleaning etc.) *No simultaneous chemical and mechanical exposure.	
Skid / Slip Resistance	R11 V4 (Quartz Sand 0.3–0.8	mm) (DIN 51130)
	R12 V6 (Quartz Sand 0.6–1.2	mm) (DIN 51130)



APPLICATION INFORMATION

Consumption	Sikafloor® MultiDur EB-27 system (~ 2–4mm)					
	Flooring System	Product		onsumption		
	Primer	1 × Sikafloor®-1		0.3-0.5 kg/m ²		
	Wearing layer	Sikafloor®-263		~ 4 kg /m² (2 kg/m²		
		Sikafloor®-264		binder + 2 kg/m² quartz sand)		
		1:1 with quartz	sand sa			
	0.06-0.3mm					
	Sand broadcast	Quartz sand 0.3 mm	3 – 0.8 ~	4–6 kg/m²		
	Seal / Top coat	1–2 × Sikafloor	®-264 N ~(0.6–0.8 kg/m²		
Product Temperature	Please refer to the individual Product Data Sheet					
Ambient Air Temperature	+10 °C min. / +30 °C max.					
Relative Air Humidity	80 % r.h. max.					
Dew Point	Beware of conde	nsation!				
		d uncured floor must be		•		
	reduce the risk o	f condensation or bloon	ning on the f	loor finish.		
Substrate Temperature	+10 °C min. / +30	°C max.				
Substrate Moisture Content	≤ 4% pbw					
	Test method: Sik	a®-Tramex meter, CM -	measureme	nt or Oven-dry-meth-		
	od.					
	No rising moistur	e according to ASTM (P	olyethylene-	-sheet).		
Waiting Time / Overcoating	Before applying S	Sikafloor®-263 SL N/-264	Non Sikaflo	oor®-150/-151 allow:		
	Substrate tempe	Substrate temperature Minimum		Maximum		
		in a care		iaximum		
	+10 °C	24 hours		days		
			3			
	+10 °C	24 hours	3 2	days		
	+10 °C +20 °C +30 °C	24 hours 12 hours 8 hours	3 2 1	days days day		
	+10 °C +20 °C +30 °C Before applying S	24 hours 12 hours 8 hours Sikafloor®-264 N on Sika	3 2 1 floor®-263 S	days days day		
	+10 °C +20 °C +30 °C Before applying S Substrate tempe	24 hours 12 hours 8 hours sikafloor®-264 N on Sika rature Minimum	3 2 1 floor®-263 S	days days day SL N /-264 N allow: laximum		
	+10 °C +20 °C +30 °C Before applying S	24 hours 12 hours 8 hours Sikafloor®-264 N on Sika	3 2 1 1 floor®-263 \$ W 48	days days day SL N /-264 N allow:		
	+10 °C +20 °C +30 °C Before applying S Substrate tempe +10 °C	24 hours 12 hours 8 hours Sikafloor®-264 N on Sika rature Minimum 30 hours	3 2 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1	days days day SL N /-264 N allow: laximum 8 hours		
	+10 °C +20 °C +30 °C Before applying S Substrate tempe +10 °C +20 °C +30 °C	24 hours 12 hours 8 hours Sikafloor®-264 N on Sika rature Minimum 30 hours 24 hours 16 hours	3 2 1 floor®-263 S <u>M</u> 48 30 24	days days day SL N /-264 N allow: laximum 8 hours 0 hours 4 hours		
	+10 °C +20 °C +30 °C Before applying S Substrate tempe +10 °C +20 °C +30 °C	24 hours 12 hours 8 hours sikafloor®-264 N on Sika rature Minimum 30 hours 24 hours	3 2 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1	days days day SL N /-264 N allow: laximum 8 hours 0 hours 4 hours		
Applied Product Ready for Use	+10 °C +20 °C +30 °C Before applying S Substrate tempe +10 °C +20 °C +30 °C	24 hours 12 hours 8 hours Sikafloor®-264 N on Sika rature Minimum 30 hours 24 hours 16 hours timate and will be affect temperature and relati	3 2 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1	days days day SL N /-264 N allow: laximum 8 hours 0 hours 4 hours		
Applied Product Ready for Use	+10 °C +20 °C +30 °C Before applying S Substrate tempe +10 °C +20 °C +30 °C Times are approxions particularly Temperature +10 °C	24 hours 12 hours 8 hours Sikafloor®-264 N on Sikarature Minimum 30 hours 24 hours 16 hours Simate and will be affect temperature and relation Foot traffic Ligarian	floor®-263 S M 48 30 24 seed by change by humidity the traffic of days	days days day SL N /-264 N allow: laximum 8 hours 0 hours 4 hours ging ambient condi- Full cure ~ 10 days		
Applied Product Ready for Use	+10 °C +20 °C +30 °C Before applying S Substrate tempe +10 °C +20 °C +30 °C Times are approxions particularly Temperature	24 hours 12 hours 8 hours Sikafloor®-264 N on Sikarature Minimum 30 hours 24 hours 16 hours Simate and will be affect temperature and relation Foot traffic Ligarian	floor®-263 S M 48 24 seed by change by humidity the traffic	days days day SL N /-264 N allow: laximum 8 hours 0 hours 4 hours ging ambient condi-		
Applied Product Ready for Use	+10 °C +20 °C +30 °C Before applying S Substrate tempe +10 °C +20 °C +30 °C Times are approxions particularly Temperature +10 °C	24 hours 12 hours 8 hours Sikafloor®-264 N on Sikarature Minimum 30 hours 24 hours 16 hours simate and will be affect temperature and relative Foot traffic 72 hours 24 hours 26 27 28 29 20 20 20 20 20 20 20 20 20 20 20 20 20	floor®-263 S M 48 30 24 seed by change by humidity the traffic of days	days days day SL N /-264 N allow: laximum 8 hours 0 hours 4 hours ging ambient condi- Full cure ~ 10 days		
	+10 °C +20 °C +30 °C Before applying S Substrate tempe +10 °C +20 °C +30 °C Times are approxitions particularly Temperature +10 °C +20 °C	24 hours 12 hours 8 hours Sikafloor®-264 N on Sikarature Minimum 30 hours 24 hours 16 hours simate and will be affect temperature and relative Foot traffic 72 hours 24 hours 26 27 28 29 20 20 20 20 20 20 20 20 20 20 20 20 20	floor®-263 S M 48 30 20 20 48 30 20 20 20 20 20 20 20 20 20	days days days day SL N /-264 N allow: laximum 8 hours 0 hours 4 hours ging ambient condi- Full cure ~ 10 days ~ 7 days		
Applied Product Ready for Use PRODUCT INFORMATION Packaging	+10 °C +20 °C +30 °C Before applying S Substrate tempe +10 °C +20 °C +30 °C Times are approxitions particularly Temperature +10 °C +20 °C +30 °C	24 hours 12 hours 8 hours Sikafloor®-264 N on Sikarature Minimum 30 hours 24 hours 16 hours simate and will be affect temperature and relative Foot traffic 72 hours 24 hours 26 27 28 29 20 20 20 20 20 20 20 20 20 20 20 20 20	floor®-263 S M 48 30 24 seed by change by humidity that traffic 5 days 4 days 4 days 4 days 4 days	days days days day SL N /-264 N allow: laximum 8 hours 0 hours 4 hours ging ambient condi- Full cure ~ 10 days ~ 7 days		
PRODUCT INFORMATION	+10 °C +20 °C +30 °C Before applying S Substrate tempe +10 °C +20 °C +30 °C Times are approxions particularly Temperature +10 °C +20 °C +30 °C Refer to the indiv	24 hours 12 hours 8 hours Sikafloor®-264 N on Sikarature Minimum 30 hours 24 hours 16 hours Simate and will be affect temperature and relative Foot traffic 72 hours 74 hours 78 hours 74 hours 76 77 hours 77 hours 78 hours 79 77 hours 70 77 hours 70 77 hours 71 18 hours 71 18 hours	floor®-263 S M 44 30 24 reed by change by humidity the traffic of days 1 days 2 days 2 days	days days days day SL N /-264 N allow: laximum 8 hours 0 hours 4 hours ging ambient condi- Full cure ~ 10 days ~ 7 days		





MAINTENANCE

CLEANING

Refer to the Information Manual Sikafloor®- Cleaning Regime

FURTHER DOCUMENTS

Refer to:

- Sika® Information Manual Mixing & Applications of Flooring systems
- Sika® Information Manual Evaluation and Preparation of Surfaces for Flooring systems

LIMITATIONS

- Do not apply Sikafloor® MultiDur EB-27 on substrates with rising moisture.
- Freshly applied Sikafloor® MultiDur EB-27 must be protected from damp, condensation and water for at least 24 hours.
- The incorrect assessment and treatment of cracks may lead to a reduced service life and reflective cracking.
- For exact colour matching, ensure the Sikafloor®-264 N in each area is applied from the same control batch numbers.
- Under certain conditions, underfloor heating or high ambient temperatures combined with high point loading, may lead to indentations in the resin.
- If heating is required do not use gas, oil, paraffin or other fossil fuel heaters, these produce large quantities of both CO₂ and H₂O water vapour, which may adversely affect the finish. For heating use only electric powered warm air blower systems.

VALUE BASE

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

SIKA LIMITED

Watchmead Welwyn Garden City Hertfordshire, AL7 1BQ Tel: 01707 394444 Web: www.sika.co.uk Twitter: @SikaLimited







System Data Sheet
Sikafloor® MultiDur EB-27
February 2020, Version 01.02
02081190000000078

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SikafloorMultiDurEB-27-en-GB-(02-2020)-1-2.pdf

