

BUILDING TRUST

Everbuild® 203 Accelerator &

Frostproofer

ATION OF PERFORMANCE

10906124

UNIQUE IDENTIFICATION 1 **CODE OF THE PRODUCT-**TYPE:

10906124

2 **INTENDED USE/S**

Hardening and accelerating admixture

3 **MANUFACTURER:** Sika Services AG Tüffenwies 16 8064 Zürich

4 **AUTHORISED REPRESENTATIVE:**

Not Applicable

5 **SYSTEM/S OF AVCP:**

System 2+

6a **DESIGNATED STANDARD:** BS EN934-2:2009 +A1:2012

Conformity Assessment

body/ies:

0120

Declaration of Performance

Everbuild® 203 Accelerator & Frostproofer 10906124 2024/01, ver. 02 1213

7 DECLARED PERFORMANCE/S

Essential Characteristics	Performance	AVCP	Designated Technical Specification
Chloride ion content	<0.1% w/w		
Alkali Content	<2% w/w		
Corrosion Behaviour	Contains the following components from En934-1:2008 Annex A.2; Calcium Nitrate		
Compressive Strength	>120% of control 20°C and 24 hours		
	>90% of control 20°C and 28 days	-	BS EN934-
	>130% of control 5°C and 48 hours		2:2009
Air Content in Fresh Concrete	≤2% by volume above control		
Dangerous Substances	None (see MSDS)		

8 APPROPRIATE TECHNICAL DOCUMENTATION AND/OR - SPECIFIC TECHNICAL DOCUMENTATION

The performance of the product identified above is in conformity with the set of declared performance/s. This declaration of performance is issued, in accordance with Regulation, under the sole responsibility of the manufacturer identified above.

Signed for and on behalf of the manufacturer by:

Name: Paul Thomas

Function: Technical Product Co-

ordinator

At Leeds on 24 January 2024

Name: Mariam Maqsood Function: Product Manager At Leeds on 24 January 2024

 $\label{lem:equivalence} \mbox{End of information as required by Regulation}$





BS EN934-2:2009 +A1:2012 Conformity Assessment Body 0120 Hardening and accelerating admixture Chloride ion content <0.1% w/w Alkali Content <2% w/w Corrosion Behaviour Contains the following components from En 1:2008 Annex A.2; Calcium Nitrate Compressive Strength >120% of control 20°C and 24 hours >90% of control 20°C and 28 days >130% of control 5°C and 48 hours Air Content in Fresh Concrete ≤2% by volume above control Dangerous Substances None (see MSDS)	Sika Service	s AG, Zurich, Switzerland	
Conformity Assessment Body 0120 Hardening and accelerating admixture Chloride ion content <0.1% w/w Alkali Content <2% w/w Corrosion Behaviour Contains the following components from Endicated the second strength >12008 Annex A.2; Calcium Nitrate Compressive Strength >120% of control 20°C and 24 hours >90% of control 20°C and 28 days >130% of control 5°C and 48 hours Air Content in Fresh Concrete ≤2% by volume above control	Dol	P No. 10906124	
Hardening and accelerating admixture Chloride ion content Alkali Content Corrosion Behaviour Compressive Strength Compressive Strength >120% of control 20°C and 24 hours >90% of control 20°C and 28 days >130% of control 5°C and 48 hours Air Content in Fresh Concrete ≤2% by volume above control	BS EN9	34-2:2009 +A1:2012	
Chloride ion content Alkali Content Corrosion Behaviour Compressive Strength Compressive Strength Compressive Strength >120% of control 20°C and 24 hours >90% of control 20°C and 28 days >130% of control 5°C and 48 hours Air Content in Fresh Concrete ≤2% by volume above control	Conformity	Assessment Body 0120	
Alkali Content Corrosion Behaviour Compressive Strength Compressive Strength >12008 Annex A.2; Calcium Nitrate >120% of control 20°C and 24 hours >90% of control 20°C and 28 days >130% of control 5°C and 48 hours Air Content in Fresh Concrete ≤2% by volume above control	Hardening an	d accelerating admixture	
Corrosion Behaviour Compressive Strength Compressive Strength >120% of control 20°C and 24 hours >90% of control 20°C and 28 days >130% of control 5°C and 48 hours Air Content in Fresh Concrete ≤2% by volume above control	Chloride ion content	<0.1% w/w	
Corrosion Benaviour 1:2008 Annex A.2; Calcium Nitrate >1:2008 Annex A.2; Calcium Nitrate	Alkali Content	<2% w/w	
>90% of control 20°C and 28 days >130% of control 5°C and 48 hours Air Content in Fresh Concrete ≤2% by volume above control	Corrosion Behaviour	Contains the following components from En 1:2008 Annex A.2; Calcium Nitrate	
>130% of control 5°C and 48 hours Air Content in Fresh Concrete ≤2% by volume above control	Compressive Strength	>120% of control 20°C and 24 hours	
Air Content in Fresh Concrete ≤2% by volume above control		>90% of control 20°C and 28 days	
· · · · · · · · · · · · · · · · · · ·		>130% of control 5°C and 48 hours	
Dangerous Substances None (see MSDS)	Air Content in Fresh Concrete	≤2% by volume above control	
	Dangerous Substances	None (see MSDS)	

eclarations of Performance Downloads | Sika Limited

ECOLOGY, HEALTH AND SAFETY INFORMATION (REACH)

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

LEGAL NOTE

Any information provided in this Declaration of Performance ("DoP"), including any descriptions and recommendations relating to the application and end-use of any Sika products ("Products"), are given in good faith based on Sika's current knowledge and experience of the Products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. Please note that the materials, substrates and actual site conditions may vary considerably, and therefore Sika makes no warranty for merchantability or fitness for a particular purpose, and accepts no liability for the application and use of the Products, for any recommendations, or for any advice offered. Prior to using, the Product must be tested for its suitability for the intended application and purpose, and the most recent version of the Product Data Sheet must be consulted. Sika reserves the right to change the properties of its Products any time without prior notice. Any orders for Products or services provided by Sika are subject to Sika's current terms and conditions of sale.

Declaration of Performance

Everbuild® 203 Accelerator & Frostproofer 10906124 2024/01, ver. 02 1213

