

PRODUCT DATA SHEET Sarnafil[®] TG 66-15

POLYMERIC MEMBRANE FOR BALLASTED ROOF WATERPROOFING

PRODUCT DESCRIPTION

Sarnafil[®] TG 66-15 (thickness 1.5 mm) is a multi-layer, synthetic roof waterproofing sheet based on premiumquality flexible polyolefins (FPO), with inlay of glass non-woven according to EN 13956.

Sarnafil[®] TG 66-15 is a hot air weldable, UV-resistant roof membrane, designed for use in all global climatic conditions.

USES

Roof waterproofing membrane for roofs with ballast (e.g. gravel, concrete slabs, green roof) and / or exposed flat roofs:

- Loosely laid and ballasted roofs
- Green roofs
- Utility roofs
- Inverted roofs

Roof waterproofing membrane for exposed roof junction zones:

- Roof waterproofing for junctions and flashings, e.g. wall and parapet junctions, roof lights, etc., which are permanently exposed in installations of Sarnafil® TG 66-15 roof waterproofing systems with ballast.
- Roof waterproofing for junctions and flashings in installations of all types of Sarnafil[®] TS 77 and TG 76 Felt exposed roof waterproofing systems.

CHARACTERISTICS / ADVANTAGES

- Proven performance over decades
- Resistant to micro-organisms
- Resistant to root penetration
- High dimensional stability due to glass fleece inlay
- Compatible to bitumen
- Resistant to permanent UV exposure
- Resistant against impact load and hail
- Resistant to all common environmental influences
- Resistant to mechanical influences
- Hot air welding without use of open flame
- Recyclable

APPROVALS / STANDARDS

Sarnafil[®] TG 66-15 is designed and manufactured to meet most international recognised standards.

- Polymeric sheets for roof waterproofing according to EN 13956, certified by notified body 1213-CPD-3914 and provided with the CE-mark.
- Reaction to fire according to EN 13501-1.
- Official Quality Approvals and Agrement Certificates and approvals.
- Monitoring and assessment by approved laboratories.
- Quality Management system in accordance with EN ISO 9001/14001.
- Root penetration resistance tested according to FLL-Test Procedure.

Product Data Sheet Sarnafil® TG 66-15 April 2017, Version 01.02 020910032000151001

PRODUCT INFORMATION

Packaging	Sarnafil [®] TG 66-15 standard rolls are wrapped individually in a blue PE-foil.		
	Packing unit:	see price list	
	Roll length:	20.00 m	
	Roll width:	2.00 m	
	Roll weight:	60.00 kg	
Appearance / Colour	Surface:	matt	
	Colours:		
	Top surface:	beige	
	·	grey (nearest RAL 7040)	
	Bottom surface:	black	
Shelf Life	Product does not expire i	Product does not expire if correctly stored.	
Storage Conditions		Rolls must be stored in a horizontal position on pallet and protected from direct sunlight, rain and snow. Do not stack pallets of rolls during transport or storage.	
Product Declaration	EN 13956		
Visible Defects	Pass	(EN 1850-2)	
Length	20 m (-0 % / +5 %)	(EN 1848-2)	
Width	2 m (- 0.5 % / + 1 %)	(EN 1848-2)	
Effective Thickness	1.5 mm (-5 % / +10 %)	(EN 1849-2)	
Straightness	≤ 30 mm	(EN 1848-2)	
Flatness	≤ 10 mm	(EN 1848-2)	
Mass per unit area	1.5 kg/m² (- 5 % / + 10 %)	(EN 1849-2)	
TECHNICAL INFORMA	TION		
Resistance to Impact	hard substrate	≥ 800 mm (EN 12691)	

hard substrate	≥ 800 mm	(EN 12691)
soft substrate	≥ 1000 mm	
soft substrate	≥ 20 kg	(EN 12730)
rigid substrate	≥ 20 kg	
Pass		(EN 13948)
longitudinal (md) ¹⁾	≥ 9 N/mm²	(EN 12311-2)
transversal (cmd) ²⁾	≥ 7 N/mm²	
¹⁾ md = machine direction ²⁾ cmd = cross machine direction		
longitudinal (md) ¹⁾	≥ 550 %	(EN 12311-2)
transversal (cmd) ²⁾	≥ 550 %	
¹⁾ md = machine direction ²⁾ cmd = cross machine direction		
longitudinal (md) ¹⁾	≤ 0.2 %	(EN 1107-2)
transversal (cmd) ²⁾	≤ 0.1 %	
¹⁾ md = machine direction ²⁾ cmd = cross machine direction		
≥ 500 N/50 mm		(EN 12317-2)
≤ -45 °C		(EN 495-5)
Class E	(EN ISO 11925-2, cla	assification to EN 13501-1)
	soft substrate soft substrate rigid substrate Pass longitudinal (md) ¹) transversal (cmd) ²) ¹⁾ md = machine direction ²⁾ cmd = cross machine direction longitudinal (md) ¹) transversal (cmd) ²) ¹⁾ md = machine direction ²⁾ cmd = cross machine direction ¹⁾ md = machine direction ²⁾ cmd = cross machine direction ¹⁾ md = machine direction ²⁾ cmd = cross machine direction	Induction $\geq 1000 \text{ mm}$ soft substrate $\geq 1000 \text{ mm}$ $\stackrel{\text{soft substrate}}{\text{rigid substrate}}$ $\geq 20 \text{ kg}$ Pass $\geq 20 \text{ kg}$ Pass $\stackrel{\text{longitudinal (md)1}}{\text{transversal (cmd)2}}$ $\geq 9 \text{ N/mm^2}$ $\stackrel{1)}{\text{md}}$ = machine direction $\geq 7 \text{ N/mm^2}$ $\stackrel{1)}{\text{md}}$ = machine direction $\geq 550 \%$ $\stackrel{10}{\text{transversal (cmd)2}}$ $\geq 550 \%$ $\stackrel{10}{\text{md}}$ = machine direction $\geq 550 \%$ $\stackrel{10}{\text{md}}$ = machine direction $\geq 10.2 \text{ mm}$ $\stackrel{10}{\text{transversal (cmd)2}}$ $\leq 0.2 \text{ mm}$ $\stackrel{10}{\text{transversal (cmd)2}}$ $\leq 0.2 \text{ mm}$ $\stackrel{10}{\text{transversal (cmd)2}}$ $\leq 0.1 \text{ mm}$ $\stackrel{10}{\text{transversal (cmd)2}}$ $\leq 0.2 \text{ mm}$ $\stackrel{10}{\text{transversal (cmd)2}}$ $\leq 0.1 \text{ mm}$ $\stackrel{10}{\text{sc}}$

 Product Data Sheet

 Sarnafil® TG 66-15

 April 2017, Version 01.02

 020910032000151001



Effect of Liquid Chemicals, Including Water	On request	(EN 1847)
Exposure to Bitumen	Pass ³⁾ ³⁾ Sarnafil® T is compatible to old bitumen	(EN 1548)
UV Exposure	Pass (> 5000 h / grade 0)	(EN 1297)
Water Vapour Transimission	μ = 150'000	(EN 1931)
Water Tightness	Pass	(EN 1928)

SYSTEM INFORMATION

System Structure	Wide range of accessories is available e.g. prefabricated parts, roof drains, scuppers, protection sheets and separation layers. The following accessories shall be used: • Sarnafil® T 66-15 D Sheet for detailing • Sarnafil® T Metal Sheet • Sarnabar • Sarnafil® T Welding Cord • Sarnafil® T Prep / Sarnafil® T Wet Task Set • Sarnacol® T 660 • Solvent T 660
Compatibility	 Sarnafil[®] T Clean Sarnafil[®] TG 66-15 may be installed on all thermal insulations and levelling layers suitable for roofing. No additional separation layer is required. Sarnafil[®] TG 66-15 is suitable for installation directly on top of existing, carefully cleaned, level bituminous roofing, e.g. re-roofing over old flat roofs. Colour changes in membrane surface may occur in case of direct contact with bitumen.

APPLICATION INFORMATION

Ambient Air Temperature	-20 °C min. / +60 °C max.
Substrate Temperature	-30 °C min. / +60 °C max.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

The substrate surface must be uniform, smooth and free of any sharp protrusions or burrs, etc. The supporting layer must be compatible to the membrane, solvent resistant, clean, dry and free of grease and dust. Metal sheets must be degreased with Sarna-fil® Cleaner before adhesive is applied.

APPLICATION

Installation works must be carried out only by Sika instructed contractors for roofing.

Installation of some ancillary products, e.g. contact adhesives / cleaners is limited to temperatures above +5 °C. Please observe information given by Product Data Sheets.

Special measures may be compulsory for installation below +5 °C ambient temperature due to safety requirements in accordance with national regulations.

APPLICATION METHOD / TOOLS

Installation procedure:

According to the valid installation instructions of manufacturer for Sarnafil[®] TG 66-types system for ballasted or fully adhered roofs.

Fixing Method:

Loosely laid and covered with ballast. Mechanical fixing at the roof perimeter with Sarnabar including Sarnafil® T Welding Cord is obligatory to keep membrane in place. Roof waterproofing membrane is installed by loose laid and covered with ballast according to local wind load situation.

Adhered roof junction areas and flashings: Sarnafil® TG 66-18 is adhered to substrate layers such as reinforced concrete rendering, timber panels, metal sheets, etc. by contact adhesive Sarnacol® T 660. Seam overlaps are welded by hot air.

Product Data Sheet Sarnafil® TG 66-15 April 2017, Version 01.02 020910032000151001



Welding Method:

Before welding the seams are prepared with Sarnafil® T Prep. Overlap seams are welded by electric hot air welding equipment, such as manual hot air welding machines and pressure rollers or automatic hot air welding machines with controlled hot air temperature.

Recommended type of equipment:

Leister Triac PID for manual welding

Sarnamatic 661^{plus} for automatic welding

Welding parameters including temperature, machine speed, air flow, pressure and machine settings must be evaluated, adapted and checked on site according to the type of equipment and the climatic situation prior to welding. The effective width of welded overlaps by hot air should be minimum 20 mm.

The seams must be mechanically tested with screw driver to ensure the integrity / completion of the weld. Any imperfections must be rectified by hot air welding.

LIMITATIONS

Geographical / Climate

The use of Sarnafil® TG 66-15 membrane is limited to geographical locations with average monthly minimum temperatures of -50 °C.

Permanent ambient temperature during use is limited to +50 °C.

VALUE BASE

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses

ECOLOGY, HEALTH AND SAFETY

REGULATION (EC) NO 1907/2006 - REACH

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in the product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0,1 % (w/w)

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

TECHNICAL ENQUIRIES Tel: 01707 358500 Web: www.sarnafil.co.uk Twitter: @SikaSarnafilUK



Product Data Sheet Sarnafil® TG 66-15 April 2017, Version 01.02 020910032000151001

SarnafilTG66-15-en-GBSARNA-(04-2017)-1-2.pdf



Watchmead

SIKA LIMITED

Welwyn Garden City Hertfordshire, AL7 1BQ Tel: 01707 394444 Web: www.sika.co.uk Twitter: @SikaLimited