

**BUILDING TRUST** 

# SYSTEM DATA SHEET

## Sikafloor<sup>®</sup> EasyFinish CS-30

#### Concrete flooring system combining a dry shake hardener and special finishing aid

#### **PRODUCT DESCRIPTION**

Sikafloor<sup>®</sup> EasyFinish CS-30 is a dryshake hardener flooring system incorporating a special finishing aid. The patented method enables application of multiple layers of dry shake. The finishing aid provides more reliable surface finishing, densifying and improving the surface hardness.

#### USES

Sikafloor® EasyFinish CS-30 is used for:

Medium to heavy wear new concrete floors

Sikafloor<sup>®</sup> EasyFinish CS-30 is used for the following application areas:

- Car park decks
- Loading ramps
- Logistics facilities and warehouses
- Manufacturing facilities and workshops
- Storage areas
- Industrial buildings

- Wood processing industry
- Automotive facilities
- Commercial and public buildings
- Railway and metro stations
- Agricultural facilities
- Mining and metal processing facilities
- Recycling plants
- Please note:
- The System may only be used by experienced professionals.

#### **CHARACTERISTICS / ADVANTAGES**

- Very good mechanical and wear resistance
- Cost effective
- Separate liquid hardener not needed after application
- Reduced moisture loss in early phase
- Easy application and finishing
- Quality improved final finish
- Increased resistance to oils and grease
- Wide range of colours available

#### SYSTEM INFORMATION

Layer	Product	
Dry shake hardener	Sikafloor®-3 QuartzTop, or Sikafloor®-2 SynTop	
Finishing aid	Sikafloor®-931 Finishing Aid	
Sealer	Sikafloor <sup>®</sup> ProSeal-12, or	
. <u></u>	Sikafloor <sup>®</sup> ProSeal W	
Available in a wide range of colours.		
2.5 mm to 4 mm		
	Dry shake hardener Finishing aid Sealer Available in a wide range of d	

System Data Sheet Sikafloor® EasyFinish CS-30 April 2025, Version 02.01 02081590000000014

#### **TECHNICAL INFORMATION**

Abrasion Resistance	System	Result
	Concrete C25/30 w/c ratio 0.55	reference
	Concrete C25/30 w/c ratio 0.55 +	20 % less wear
	Sikafloor <sup>®</sup> EasyFinish CS-30	

#### **APPLICATION INFORMATION**

Layer	Product	Consumption
Dry shake hardener	Sikafloor®-3 QuartzTop,	4-6 kg/m <sup>2</sup>
	or	
	Sikafloor <sup>®</sup> -2 SynTop	
Finishing aid	Sikafloor <sup>®</sup> -931 Finishing	25–50 g/m <sup>2</sup> per applica-
2	Aid	tion
Sealer	Sikafloor <sup>®</sup> ProSeal-12,	100–200 g/m <sup>2</sup> per coat
	or	
	Sikafloor <sup>®</sup> ProSeal W	

#### **PRODUCT INFORMATION**

Packaging	Refer to individual Product Data Sheet.
Shelf Life	Refer to individual Product Data Sheet.
Storage Conditions	Refer to individual Product Data Sheet.

#### VALUE BASE

Consumption

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

#### FURTHER DOCUMENTS

Please refer to the individual product data sheets for the mentioned products as part of the system.

For the application details, please refer to "Sika Method Statement: Sikafloor® EasyFinish CS -30 & Terrazzo CS -31/32"

#### ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.





#### System Data Sheet Sikafloor® EasyFinish CS-30 April 2025, Version 02.01 02081590000000014

### LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

#### LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SikafloorEasyFinishCS-30-en-GB-(04-2025)-2-1.pdf



**BUILDING TRUST**