

## SYSTEM DATA SHEET

# Sikafloor® MultiFlex PS-37

Smooth-finish, crack-bridging polyurethane flooring system

## PRODUCT DESCRIPTION

Sikafloor® MultiFlex PS-37 is a smooth-finish polyurethane flooring system. It is part of the Sikafloor® Multiflex flooring range.

## USES

Sikafloor® MultiFlex PS-37 may only be used by experienced professionals.

Sikafloor® MultiFlex PS-37 is used in industrial buildings such as:

- Automotive facilities
- Food and beverage facilities
- Logistics facilities and warehouses

Please note:

The System may only be used for interior applications.

## CHARACTERISTICS / ADVANTAGES

- Good mechanical resistance
- Good crack-bridging ability
- Low maintenance
- Good resistance to specific chemicals
- Seamless

## APPROVALS / STANDARDS

Fire Classification Report EN 13501-1, GHENT, No. CR 24-0147-01

## SYSTEM INFORMATION

System Structure	Layer	Product
	1. Primer	Sikafloor®-150 Plus, or Sikafloor®-151, or Sikafloor®-1590
	2. Wearing layer	Sikafloor® BC 375 N filled 1:0.25 Quartz sand (0.06–0.3 mm) by weight
Contact Sika technical service for information on choosing the right primer for your project.		
Composition	Polyurethane	
Appearance	Smooth gloss finish	
Colour	Available in various colour shades.	
Nominal thickness	~2.0 mm	

## TECHNICAL INFORMATION

Tensile adhesion strength	≥ 1.5 MPa	(EN 1542)
Reaction to Fire	Class Bfl-s1	(EN 13501-1)

## APPLICATION INFORMATION

Consumption	Layer	Product	Consumption	
	Primer	Sikafloor®-150 Plus, or Sikafloor®-151, or Sikafloor®-1590	1-2 × 0.3–0.5 kg/m²	
	Leveling (if required)	Sikafloor®-150, or Sikafloor®-151, or Sikafloor®-1590	Refer to the individual Product Data Sheet.	
	Wearing layer	Sikafloor® BC 375 N filled 1:0.25 with Quartz Sand (0.06–0.3 mm) by weight	1 × 2.0 kg/m²	
Ambient Air Temperature	Minimum	+10 °C		
	Maximum	+30 °C		
Relative Air Humidity	Maximum	80 % r.h.		
Dew Point	Refer to the individual Product Data Sheet.			
Substrate Temperature	Minimum	+10 °C		
	Maximum	+30 °C		
Substrate Moisture Content	Refer to the individual Product Data Sheet.			
Waiting Time / Overcoating	When using Sikafloor®-1590 refer to the individual Product Data Sheet for specific information on waiting time to overcoating. Before applying Sikafloor® BC 375 N over the primer, allow:			
	Temperature	Minimum	Maximum	
	+10 °C	17 hours	4 days	
	+20 °C	9 hours	2 days	
	+30 °C	7 hours	1 day	
	Note: Times are approximate and will be affected by changing ambient conditions, particularly temperature and relative humidity.			
Applied Product Ready for Use	Temperature	Foot traffic	Light traffic	Full cure
	+10 °C	72 hours	6 days	10 days
	+20 °C	24 hours	4 days	7 days
	+30 °C	18 hours	2 days	5 days
Note: Times apply when the last layer of the system has been applied. Times are affected by changing ambient conditions, particularly temperature and relative humidity.				

## VALUE BASE

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## FURTHER DOCUMENTS

Refer to the following method statements:

- Sika Method Statement — Evaluation and preparation of surfaces for flooring systems
- Sika Method Statement — Sikafloor® mixing and application

## ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### SIKA LIMITED

Watchmead  
Welwyn Garden City  
Hertfordshire, AL7 1BQ  
Tel: 01707 394444  
Web: [www.sika.co.uk](http://www.sika.co.uk)  
Twitter: @SikaLimited



System Data Sheet  
Sikafloor® MultiFlex PS-37  
March 2025, Version 01.01  
02081290000000136

SikafloorMultiFlexPS-37-en-GB-(03-2025)-1-1.pdf