

## PRODUCT DATA SHEET

## Sikaflex®-953 L30

Long open time, fast-curing, 2-component STP assembly adhesive / sealant

## TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)

Properties	Sikaflex®-953 L30 A	Sikaflex®-905 B
Chemical base	2-component silane terminated polymer (STP)	
Colour (CQP001-1)	White	white
Density (uncured)	1.41 kg/l	1.20 kg/l
	mixed	1.39 kg/l
Mixing ratio	A:B by volume	10 : 1
	A:B by weight	11.7 : 1
Non-sag properties (CQP061-1)	Fair	
Application temperature	product, ambient	5 – 40 °C
Skin time (CQP019-1)	40 minutes <sup>A</sup>	
Open time (CQP526-1)	30 minutes <sup>A</sup>	
Curing speed (CQP046-1)	(see table) <sup>A</sup>	
Shrinkage (CQP014-1)	2 %	
Shore A hardness (CQP023-1 / ISO 48-4)	50	
Tensile strength (CQP036-1 / ISO 527)	2.5 MPa	
Elongation at break (CQP036-1 / ISO 527)	450 %	
Tear propagation resistance (CQP045-1 / ISO 34)	15 N/mm	
Tensile lap-shear strength (CQP046-1 / ISO 4587)	1.5 MPa	
Thermal resistance (CQP 513-1)	1 hour	160 °C
Service temperature (CQP513-1)	-45 – 90 °C	
Shelf life (CQP016-1)	9 months <sup>B</sup>	
Mixer	for dispensing systems	Statomix® MS 13-18-G

CQP = Corporate Quality Procedure

<sup>A)</sup> 23 °C / 50 % r. h.<sup>B)</sup> storage between 5 and 25 °C, comp. (B) is frost sensitive

## DESCRIPTION

Sikaflex®-953 L30 is a 2-component Silane Terminated Polymer (STP) assembly adhesive which cures by chemical reaction of the two components. The L30 version is designed for bonding large components where a longer open time is required.

Owing to its good weathering resistance and gap-filling performance it can also be used for exterior sealing joints. It's especially suitable for pumping over long distances.

## PRODUCT BENEFITS

- Pumpable over long distances
- Minimal pre-treatment required for most common substrates
- Solvent- and isocyanate-free
- Good gap-filling capabilities
- Great weathering and ageing resistance

## AREAS OF APPLICATION

Sikaflex®-953 L30 is suitable for bonding large components exposed to dynamic stress and where the attainment of early strength is required. Common substrates are metals, particularly aluminium (including anodised), steel (including phosphated, chromated, galvanised), metal primers and paint coatings (2-part systems), ceramic materials and plastics. Seek manufacturer's advice and perform tests on original substrates before using Sikaflex®-953 L30 on materials prone to stress cracking. This product is suitable for experienced professional users only. Tests with actual substrates and conditions have to be performed ensuring adhesion and material compatibility.

## PRODUCT DATA SHEET

Sikaflex®-953 L30

Version 03.01 (03 - 2023), en\_GB

012301219530001200

## CURE MECHANISM

The curing of Sikaflex®-953 L30 takes place by chemical reaction of the two components.

Time [h]	Strength [MPa]
2	0.2
4	0.6
6	0.8

Table 1: Lap-shear strength (CQP 046-1) at 23 °C / 50 % r.h.

## CHEMICAL RESISTANCE

Sikaflex®-953 L30 is generally resistant to fresh water, seawater, diluted acids and diluted caustic solutions; temporarily resistant to fuels, mineral oils, vegetable and animal fats and oils; not resistant to organic acids, glycolic alcohol, concentrated mineral acids and caustic solutions or solvents.

## METHOD OF APPLICATION

### Surface Preparation

Surfaces must be clean, dry and free from grease, oil, dust and contaminants. Surface treatment depends on the specific nature of the substrates and is crucial for a long lasting bond.

All pre-treatment steps must be confirmed by preliminary tests on original substrates considering specific conditions in the assembly process.

### Application

Sikaflex®-953 L30 can be processed by cartridge or with a suitable dispensing system. The mixer type needs to be respected. For dispensing systems the mixer type is stated in the Typical Product Data table, whereas for cartridges it is stated under Packaging Information.

Sikaflex®-953 L30 can be applied between 5 °C and 40 °C but changes in reactivity and application properties have to be considered. The optimum temperature for substrate and the Product is between 15 °C and 25 °C.

To ensure a uniform thickness of the bondline it is recommended to apply the adhesive in form of a triangular bead (see figure 1).




Figure 1: Recommended bead configuration

The open time is significantly shorter in hot and humid climate. The parts must always be joint within the open time. As a rule of thumb, a change of + 10 °C reduces the open time by half.

For advice on selecting and setting up a suitable pump system, contact the System Engineering Department of Sika Industry.

## Tooling and finishing

Tooling and finishing must be carried out within the open time of the adhesive. We recommend the use of Sika® Tooling Agent N. Other finishing agents must be tested for suitability and compatibility.

## Removal

Uncured Sikaflex®-953 L30 can be removed from tools and equipment with Sika® Remover-208 or another suitable solvent. Once cured, the material can only be removed mechanically. Hands and exposed skin have to be washed immediately using hand wipes such as Sika® Cleaner-350H or a suitable industrial hand cleaner and water. Do not use solvents on skin.

## Overpainting

Sikaflex®-953 L30 can be best painted within the skin formation time. If painting process takes place after the sealant has built a skin, adhesion could be improved by treating the joint surface with Sika® Aktivator-100 or Sika® Aktivator-205 prior to paint process. If the paint requires a baking process (> 80 °C), best performance is achieved by allowing the sealant to fully cure first.

All paints have to be tested by carrying preliminary trials under manufacturing conditions.

The elasticity of paints is usually lower than that of sealants. This could lead to cracking of the paint in the joint area.

## FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are available on request:

- Safety Data Sheets
- General Guidelines  
Bonding and Sealing with 1-component Sikaflex®

## PACKAGING INFORMATION

Dual cartridge	490 ml
Mixer: MFHX 13-18T by medmix	

## BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## HEALTH AND SAFETY INFORMATION

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

## DISCLAIMER

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

## PRODUCT DATA SHEET

Sikaflex®-953 L30  
Version 03.01 (03 - 2023), en\_GB  
012301219530001200

## SIKA LIMITED

Watchmead  
Welwyn Garden City  
Hertfordshire, AL7 1BQ  
Tel: 01707 394444  
Web: www.sika.co.uk  
Twitter: @SikaLimited

