

# SikaGard®-6220

Sprayable, high penetrating cavity wax

## Technical Product Data

Chemical base	Wax solution
Colour	Amber
Cure mechanism	Air-drying
Density (liquid)	0.87 kg/l approx.
Solid content (CQP <sup>1</sup> 002-2)	53% approx.
Application temperature	15 - 25°C
Film thickness	wet 100 µm dry 50 µm
Drying time <sup>2</sup>	3 h approx.
Service temperature	-50 - 75°C
Shelf life (storage between 5°C and 25°C);	24 months

<sup>1)</sup> Corporate Quality Procedure

<sup>2)</sup> 23°C / 50% r.h.

### Description

SikaGard®-6220 is an amber colored, durable wax with excellent rust-proofing properties. It is suitable for an effective protection against corrosion in vehicle body cavities and convinces with its outstanding application properties and excellent final performance. Thanks to its very high creep capability, it perfectly protects even hardly accessible areas and tight sheet intervals.

After drying, a brown, slightly sticky wax coating remains that protects cavity areas from corrosion.

SikaGard®-6220 is manufactured in accordance with ISO 9001 quality assurance system.

### Product Benefits

- High road salt resistance
- Excellent film building property
- Outstanding water displacing
- Good low temperature behavior
- Heat resistant
- No hazing during application
- Excellent creep capability
- Permanently elastic
- Lower solvent content

### Areas of Application

SikaGard®-6220 is a spray applied anti-corrosion coating for repair and protection of concealed areas of vehicles such as cavities of door skins, side panels, motor hoods, trunks, rear wing, sills, cross members and pillars.

The product can be sprayed haze free, penetrates finest hair-line cracks but does not drip off drainage holes.

SikaGard®-6220 shows very good adhesion on different paints, metal primers, metals and PVC without any pre-treatment.

The product is suitable for professional experienced users only. Tests with actual substrates and conditions have to be performed to ensure adhesion and material compatibility.



### Chemical Resistance

SikaGard®-6220 is resistant against water, seawater, salt spray, oil, soft bases and acids. The above information is offered for general guidance only. Advice on specific applications will be given on request.

### Method of Application

#### Surface preparation

Surfaces must be clean, dry and free of rust, dust and grease. Bare metal must be pre-treated to enhance corrosion resistance (e.g. uncoated steel, etc).

#### Application

SikaGard®-6220 can be applied by light airless spray equipment or by air-mix guns with an air pressure of approx. 3 - 6 bar. Use either the Sika® CW Gun (pressure cup type) or the Sika® UBC+ Gun (vacuum type) to apply the product.

Shake can approx. 40 times before use. Cover adjacent surfaces prior the spray process. Spray at room temperature and from a distance of approx. 25 cm on the surface or in the cavity using a flexible hose. Use the existing or drill access points in the car body. Spray a continuous coat and do not spray on parts of the brake, engine or exhaust system.

### Removal

Fresh SikaGard®-6220 can be removed from tools and equipment with Sika® Remover-208. Once dried, the material can only be removed mechanically.

Hands and exposed skin should be washed immediately using Sika® Handclean towels or a suitable industrial hand cleaner and water. Do not use solvents!

### Over painting

SikaGard®-6220 is not over paintable.

### Further Information

Copies of the following publication is available on request:  
- Safety Data Sheet

### Packaging Information

Can	1 l
Jerry can	10 l
Drum	60 l

### Value Basis

All technical data stated in this Product Data Sheet is based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

### Health and Safety Information

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Material Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

### Legal Notes

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Further information available at:  
[www.sika.co.uk](http://www.sika.co.uk)  
[www.sika.com](http://www.sika.com)

Sika Limited  
Business Unit Industry  
Watchmead, Welwyn Garden City  
Herts, AL7 1BQ  
United Kingdom  
Tel. +44 (0)1707 394444

