

## PRODUCT DATA SHEET

# SikaWall®-571 One Coat Dash Receiver

## PRODUCT DESCRIPTION

SikaWall-571 One Coat Dash Receiver is a factory batched cement based render.

## USES

As a one coat dry dash receiver.

## CHARACTERISTICS / ADVANTAGES

- Through coloured
- One coat application saving time on site
- Can be hand or pump applied

## PRODUCT INFORMATION

Packaging	25 kg bag
Shelf Life	12 months from date of manufacture
Storage Conditions	Dry frost free conditions
Appearance / Colour	Choice of White, Magnolia or Cream
Reaction to Fire	A1

## APPLICATION INFORMATION

Consumption	When applied to a correctly prepared even substrate at a thickness of 16 mm (recommended thickness). A 25 kg bag covers approximately 1 m <sup>2</sup> .
Mixing Ratio	3.8-4.4 L of water per 25 kg bag

## VALUE BASE

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## ECOLOGY, HEALTH AND SAFETY

Wear suitable protective clothing, gloves and eye / face protection. This product contains materials which may cause an allergic reaction, is irritating to eyes and harmful if swallowed. In case of contact, seek medical advice. Keep out of the reach of children. Read and follow the guidelines in the Health and Safety data sheet for this product

## APPLICATION INSTRUCTIONS

### SUBSTRATE QUALITY / PRE-TREATMENT

#### Suitable Substrates

This product has been designed as a one coat dash receiver for application onto masonry substrates.

#### Unsuitable Substrates

- Insulation boards
- Over coating of existing render
- Painted surfaces
- Cement Particle boards
- Gypsum & Thermalite Type Blockwork

## MIXING

A 25 kg bag of SikaWall 571 One Coat Dash Receiver should be:

- Mixed with 3.8-4.4 litres of clean potable water, no other material should be added.
- Mixed by a concrete mixer or paddle mixer for hand application or mixed and applied through a render pump for machine application.
- Mix for approximately five minutes

## APPLICATION

- Apply one coat in two passes, each pass should be 8-10 mm thick
- Care should be taken not to over mix or over trowel as this will reduce the adhesion properties of the material
- Standard rendering practice should be followed in consideration of time of year and application times.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### SIKA LIMITED

Watchmead  
Welwyn Garden City  
Hertfordshire, AL7 1BQ  
Tel: 01707 394444  
Web: [www.sika.co.uk](http://www.sika.co.uk)  
Twitter: @SikaLimited



**Product Data Sheet**  
SikaWall®-571 One Coat Dash Receiver  
September 2024, Version 02.01  
02181020000000057

SikaWall-571OneCoatDashReceiver-en-GB-(09-2024)-2-1.pdf