

## PRODUCT DATA SHEET

# Sikafloor®-375

## 2-PART PUR TOUGH ELASTIC, CRACK-BRIDGING COATING

## PRODUCT DESCRIPTION

Sikafloor®-375 is a two part, solvent free, low viscosity, tough elastic, crack-bridging polyurethane resin.

#### **USES**

Sikafloor®-375 may only be used by experienced professionals.

- For crack bridging, trafficable, slip resistant wearing layers
- For car park decks, garage floors and bridges

## **CHARACTERISTICS / ADVANTAGES**

- Good crack bridging ability
- Mechanically resistant if broadcast
- Watertight
- Easy application
- Solvent free

#### **ENVIRONMENTAL INFORMATION**

#### **LEED rating:**

Sikafloor®-375 conforms to the requirements of LEED EQ Credit 4.2: Low-Emitting Materials: Paints & Coatings

EPA Reference Test Method 24 VOC Content < 100 g/l

## **APPROVALS / STANDARDS**

- Coating for concrete protection according to EN 1504-2:2004 and the EN 13813:2002, Declaration of Performance 0208010401100000051008, certified by notified factory production control body 0921 and provided with the CE marking.
- Certified as part of the Surface Protection System OS 11a according to DIN EN 1504- 2 and DIN V 18026.
- Certified as part of the Surface Protection System OS 13 according to DIN EN 1504-2 and DIN V 18026.
- Reaction to Fire classification according to DIN EN 13501-1. Test institute Hoch Report No. KB-Hoch-101213.

#### PRODUCT INFORMATION

Chemical Base	Polyurethane	Polyurethane					
Packaging	Part A	24.0 kg co	24.0 kg containers				
	Part B	6.0 kg con	6.0 kg containers				
	Part A+B 30		30.0 kg ready to mix units				
Appearance / Colour	Beige						
Shelf Life	12 months from date of production						
Storage Conditions	The packaging must be stored properly in original, unopened and undamaged sealed packaging, in dry conditions at temperatures between +5°C and +30°C.						
Density	Part A	~ 1.66 kg/l	(DIN EN ISO 2811-1)				
	Part B	~ 1.24 kg/l					
	Mixed resin	~ 1.55 kg/l					
	All Density values a	t +23°C					

Product Data Sheet Sikafloor®-375 February 2017, Version 01.01 020812040020000015

Solid content by weight	~100 %							
Solid content by volume	~100 %							
TECHNICAL INFORMATIO	N							
Tensile Strength	~11 N/mm² (14 days / +23 °C)				(DIN 53504)			
Elongation at Break	~110 % (14 days / +23 °C)					(DIN 53504)		
SYSTEM INFORMATION								
Systems	Please refer to the System Data Sheet of:							
	Sikafloor® MultiFlex PB-21 UV Bro		Broadcast u ance polyu	Broadcast unicolour high performance polyurethane floor covering with UV sealer				
APPLICATION INFORMAT	ION							
Mixing Ratio	Part A : part B = 80 : 20 (by weight)							
Consumption	~ 1.5 kg/m²/mm. Please refer to the respective System Data Sheet.							
Ambient Air Temperature	+10 °C min. / +30 °C max.							
Relative Air Humidity	80 % r.h. max.							
Dew Point	Beware of condensation!  The substrate and uncured floor must be at least 3 °C above dew point to reduce the risk of condensation or blooming on the floor finish.							
Substrate Temperature	+10 °C min. / +30 °C max.							
Substrate Moisture Content	< 4 % pbw moisture content.  Test method: Sika®-Tramex meter, CM - measurement or Oven-dry-method.  No rising moisture according to ASTM (Polyethylene-sheet).							
Pot Life	Temperatures			Time				
	+10 °C		~ 60 minutes					
	+20 °C +30 °C			~ 25 minutes ~ 15 minutes				
	+50 C			13 Illillutes				
Curing Time	Before overcoating Sikafloor®-375 allow:							
	Substrate temp	erature			Maximu	m		
	+10 °C 24 hours		· -	48 hours				
	+20 °C			24 hours				
	+30 °C 8 hours 16 hours  Times are approximate and will be affected by changing ambient condi-							
	Times are appro tions particularly					bient condi-		
Applied Product Ready for Use	Temperature		traffic	Light traffic		II cure		
	+10 °C		hours	~ 72 hours		' days		
	+20 °C	~ 12 hours		~ 30 hours ~ 5 days		<u> </u>		
	+30 °C	~ 5 hours		~ 24 hours ~ 4 days				
	Note: Times are					·		

Note: Times are approximate and will be affected by changing ambient conditions



Product Data Sheet Sikafloor®-375 February 2017, Version 01.01 020812040020000015

## **APPLICATION INSTRUCTIONS**

#### **SUBSTRATE QUALITY / PRE-TREATMENT**

The surface must be clean, dry and free of all contaminants such as dirt, oil, grease, coatings and surface treatments, etc. All dust, loose and friable material must be completely removed from all surfaces before application of the product, preferably by vacuum. Pull of strength shall not be less than 1.5 N/mm². If in doubt apply a test area first.

#### **MIXING**

Prior to mixing, stir part A mechanically. When all of part B has been added to part A, mix continuously for 2 minutes until a uniform mix has been achieved. For the addition of quartz sand: When parts A and B have been mixed, add the quartz sand 0.1 - 0.3 mm and mix for a further 2 minutes until a uniform mix has been achieved. To ensure thorough mixing pour materials into another container and mix again to achieve a consistent mix. Over mixing must be avoided to minimise air entrainment.

#### **Mixing Tools:**

Sikafloor®-375 must be thoroughly mixed using a low speed electric stirrer (300 - 400 rpm) or other suitable equipment.

#### **APPLICATION**

Prior to application, confirm substrate moisture content, relative humidity and dew point. Sikafloor®-375 is poured and spread evenly with a serrated / notched trowel. Then, level and remove entrained air with a spiked roller and broadcast with quartz sand, at first lightly and then to excess.

#### **CLEANING OF TOOLS**

Clean all tools and application equipment with Thinner C immediately after use. Hardened and/or cured material can only be removed mechanically.

#### **FURTHER DOCUMENTS**

#### **Substrate quality & Preparation**

Please refer to Sika Information Manual: "EVALU-ATION AND PREPARATION OF SURFACES FOR FLOOR-ING SYSTEMS".

#### **Application instructions**

Please refer to Sika Information Manual: "MIXING & APPLICATION OF FLOORING SYSTEMS".

#### Maintenance

Please refer to "Sikafloor®- CLEANING REGIME".

#### **LIMITATIONS**

- Do not apply Sikafloor®-375 on substrates with rising moisture.
- Freshly applied Sikafloor®-375 must be protected from damp, condensation and water for at least 24 hours.
- Uncured material reacts in contact with water (foaming). During application care must be taken that no sweat drops into fresh Sikafloor®-375 (wear head and

- wrist bands).
- The incorrect assessment and treatment of cracks may lead to a reduced service life and reflective cracking.
- If heating is required do not use gas, oil, paraffin or other fossil fuel heaters, these produce large quantities of both CO<sub>2</sub> and H<sub>2</sub>O water vapour, which may adversely affect the finish. For heating use only electric powered warm air blower systems.

### **VALUE BASE**

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## **LOCAL RESTRICTIONS**

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## **ECOLOGY, HEALTH AND SAFETY**

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

Product Data Sheet Sikafloor®-375 February 2017, Version 01.01 020812040020000015

3/4



#### **DIRECTIVE 2004/42/CE - LIMITATION OF EMISSIONS** OF VOC

According to the EU-Directive 2004/42, the maximum allowed content of VOC (Product category IIA / j type sb) is 550 / 500 g/I (Limits 2007 / 2010) for the ready to use product.

The maximum content of Sikafloor®-375 is < 500 g/l VOC for the ready to use product.

#### **LEGAL NOTES**

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA LIMITED Watchmead

Welwyn Garden City Hertfordshire, AL7 1BQ Tel: 01707 394444 Web: www.sika.co.uk

Twitter: @SikaLimited





SIKA IRELAND LIMITED **Ballymun Industrial Estate** 

Ballymun Dublin 11, Ireland Tel: +353 1 862 0709 Web: www.sika.ie Twitter: @SikaIreland



Sikafloor-375\_en\_GB\_(02-2017)\_1\_1.pdf

**Product Data Sheet** Sikafloor®-375 February 2017, Version 01.01 020812040020000015

