

# Technical Data

## HYBRIFLEX 55

Building and Construction Adhesive/Sealant



### Description

HYBRIFLEX 55 is a one part, neutral cure, hybrid polymer based adhesive/sealant which adheres to most common building substrates. Used for general bonding and sealing in industry, engineering, construction, automotive, marine and O.E.M markets.

### Benefits

- High bond strength.
- Permanently Flexible.
- Over paintable with most common paint types.
- Can be applied to wet surfaces.
- Chemical resistant to acids/alkalis, petrol etc
- Excellent initial grab properties.

### Recommended For

Bonding and sealing in construction joints. Automotive seam sealing and bonding. Jointing cladding panels. Internal/external pointing of window and door frames. For expansion joints in brick, stone and concrete. Parapet and roofline sealing. Weather sealing in most external applications.

### Specification Compliances

HYBRIFLEX 55 has excellent primerless adhesion to most common building substrates. When overpainting, a compatibility test should be carried out prior to full application. Neutral cure system, silicone, halogen and Isocyanate free.



### Available in

600ml Foil Packs, available in the following colours:

White  
Grey

### Storage

Store in cool, dry conditions between +5°C and +25°C. Storage outside these parameters will dramatically reduce shelf life.

### Shelf Life

12 months from date of manufacture when stored as directed.

## HYBRIFLEX 55

Building and Construction Adhesive/Sealant

### Health & Safety

Consult MSDS for full list of hazards.

### Specific Data

Sg	Approx 1.5g/cm <sup>3</sup>
Cure Rate	Approx 2-3mm/24 hours
Solvent content;	Nil
Colour	White
Shrinkage (ISO 10563)	< 2%
Viscosity: (HBDVII+/S70/10rpm)	Ca: 170,000-300,000cps (high)
Tack free	Ca. 20-90 mins at 23°C and 50% RH
Skin Formation time / 20°C/50% RH	30-45 mins
Modulus at 100% elongation	1 MPa
Elongation at break	>100%
Tensile strength at break	1.5 MPa
Elastic Recovery	>75%
Hardness (shore A)	55-60(1 week)
Chemical resistance (hypochlorite; dilute acid; dilute alkali; detergent; saline 2 weeks immersion)	Excellent
Humidity and water resistance	Excellent
Application temps	+5-+35°C
Temperature resistance	-40 to +150°C

### Joint Dimensions

For maximum movement accommodation, it is recommended that:

1. The sealant joint depth should be no less than 5mm
2. Joint depth should be 5mm for joints up to 10mm wide
3. Joints above 10mm in width should be half the width in depth up to 20mm and minimum 10mm for wider joints

Joint depth may be adjusted to the correct size using EVERBUILD JOINT BACKER ROD or BOND BREAKING TAPE in cases where there is not enough depth to use Backer Rod.

### Joint Width Calculation

Joint widths are calculated as in BS6213:

$$\text{Width} = \frac{M \times 100}{F} + M$$

Where M = movement and F = movement accommodation Factor

### Primer

Priming is not always necessary; but if in doubt use a suitable primer as directed prior to application; especially when joints are to be immersed or require a high movement capability.

### Coverage

Joint Size (mm)	Litre per metre run	Metres per 600ml Foil
5 x 5	0.025	24.00
5 x 10	0.050	12.00
10 x 10	0.100	6.00
15 x 10	0.150	4.00
20 x 10	0.200	3.00

### Surface Preparation

All surfaces must be cleaned and be free from dust, grease and frost. For most substrate, priming is not required, (except when area is intermittently or permanently immersed).

Non porous surfaces should be cleaned and degreased with a suitable proprietary cleaner such as Everbuild Surface Cleaner.

If priming is required prepare the substrate using Everbuild Primer P1 for porous surfaces or Everbuild Primer NP2 for Non Porous surfaces.

If in doubt contact Technical Services for advice.

### Limitations

- Do not use on surfaces that bleed oils or plasticizers.
- Do not use in conjunction with bitumen or asphalt.
- Do not use in aquaria.
- Test compatibility with all substrates and paint systems prior to full scale use. May increase drying time of alkyd paints.
- Glazing applications: Maximum UV resistance will be achieved by overpainting with suitable paint
- Always use in conjunction with mechanical fixings for overhead applications.
- Do not use on Polypropylene, Polyethylene or Teflon.
- Use against natural stone: this product may cause some staining. Always check compatibility before use. If in doubt; use HYBRIFLEX NS
- Do not use on polythene backed safety mirrors.
- As quality of uPVC; ABS and most plastics varies dramatically, always carry out adhesion tests prior to full scale use. It is the user's responsibility to determine suitability for use. If in doubt, please contact Technical Services for advice.

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.