

PRODUCT DATA SHEET

Cromar® Contractor G 25 Resin

Contractors Grade GRP Liquid Resin

PRODUCT DESCRIPTION

Cromar® Contractor G 25 Resin is a professional roofing system designed for durable, high performance, flat roofing applications. It comprises Cromar® Contractor G 25 Resin and the Cromar® Contractor G 25 Topcoat.

Cromar® Contractor G 25 Resin is a specially formulated, pre-accelerated resin, designed for roofing applications. Formulated with a very low styrene emission. Ideal for small and large flat roofs. Can be applied in 1 or 2 coats. It is heat resistant, stormproof, frost proof and impact resistant.

USES

- Specifically engineered for flat roof applications; however it is also suitable for virtually all roof types.

CHARACTERISTICS / ADVANTAGES

- Cold applied - no heat required.
- Easy to form around complex situations.
- Very durable - resists foot traffic.
- Can be incorporated into non-slip walkways.
- Long lasting performance.
- Impact resistant due to its ultra hard finish.

PRODUCT INFORMATION

Packaging	Labelled tins available in 10 kg and 20 kg
Colour	Blue/ Clear
Shelf Life	6 months
Storage Conditions	The product must be stored properly in original, unopened and undamaged packaging, in dry conditions at temperatures between +5 °C and +20 °C
Flash Point	+32 °C
Viscosity	400 - 600 cPs at +25 °C (rotameter spindle 2 at 20 rpm)
Curing Time	8 - 16 minutes

VALUE BASE

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LIMITATIONS

Cromar® Contractor G 25 Resin is not recommended for use in conditions under +5 °C.

ECOLOGY, HEALTH AND SAFETY

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in the product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0,1 % (w/w).

APPLICATION INSTRUCTIONS

Resin Application;

Mix the resin with the appropriate MEKP catalyst (the PRO GRP Hardener is compatible for use) to achieve correct curing.

Apply evenly over the top of chopped strand matting to consolidate and wet it through to achieve 0.5 to 0.6 mm wet film thickness for correct performance.

Ensure substrate is clean, dry and between +5 °C and +30 °C before coating. Pre-install all trims. Where trims meet the deck, 100 mm of 450 g bandage should be applied. Apply resin onto the trim join, with half on trim, half on deck. Unroll the bandage onto the resin.

Impregnate the bandage with a further coat of resin. For wider roof / deck apply one third resin, then matting, and then the remaining two thirds resin. Use a bubble buster roller to get an even distribution.

Apply roofing following current British Standard Codes of conduct.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA LIMITED

Watchmead
Welwyn Garden City
Hertfordshire, AL7 1BQ
Tel: 01707 394444
Web: www.sika.co.uk
Twitter: @SikaLimited



Product Data Sheet
Cromar® Contractor G 25 Resin
May 2026, Version 01.01
020915953000247683

CromarContractorG25Resin-en-GB-(05-2026)-1-1.pdf