

PRODUCT DATA SHEET

SikaSeal®-629 Fire Wrap

FIRE RESISTANT PIPE WRAP ON A ROLL

PRODUCT DESCRIPTION

SikaSeal®-629 Fire Wrap is a fire resistant flexible pipe wrap on a roll for interior and exterior penetration sealing applications that pass through floor and wall service openings. It is ready to use and can be cut to suit varying pipe diameters. SikaSeal®-629 Fire Wrap is designed to provide a high volume expansion and pressure seal during a fire to combustible pipes.

USES

- Restores the fire resistance performance of a floor or wall which incorporates service openings containing plastic or composite pipes
- Internal-fit application (installed in the wall/floor) in combination with Sikacryl®-621 Fire
- Can be combined with SikaSeal®-626 Fire Board

CHARACTERISTICS / ADVANTAGES

- Pipe diameter range 32–250 mm
- Cut and use direct from roll
- Highly intumescent – Volume expansion 20 times original size
- Invisible installation in walls and floors
- Up to 4 hours fire resistance

APPROVALS / STANDARDS

- CE Marking and Declaration of Performance to European Technical Assessment ETA 18/1046, based on EAD 350454-00-1104:2017 - Fire stopping and fire sealing products, penetration seals
- Fire Resistance Performance Classification EN 1366-3, SikaSeal®-629 Fire Wrap, warringtonfire, Classification report No. 401159/G
- Fire Wrap for Fire Protection EN 1366-3, SikaSeal®-629 Fire Wrap, warringtonfire, Approval No. CF 5712
- Fire Wrap for Fire Stopping EN 1366-3, EN 13501-1, EN 13501-2, ETAG 026-2, SikaSeal®-629 Fire Wrap, UL, Certificate No. UL-EU-01096-CPR

PRODUCT INFORMATION

Chemical Base	Graphite based, intumescent wrap
Packaging	25 m roll, box with 1 roll. Refer to current price list for packaging variations.
Appearance / Colour	Anthracite
Shelf Life	5 years from the date of production.
Storage Conditions	The product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between -20 °C and +70 °C. Always refer to packaging.
Dimensions	40 mm wide, 2 mm thick, 25 m long

TECHNICAL INFORMATION

Resistance to fire

Refer to 'Approvals / Certificates', Sika Passive Fire Protection Handbook or contact Sika Technical Services for specific information.

Service Temperature

-20 °C min. / +70 °C max.

APPLICATION INFORMATION

Consumption	Pipe Diameter	Layers of SikaSeal®-629 Fire Wrap
	32–50 mm	1
	50–82 mm	2
	82–115 mm	3
	115–160 mm	4
	160–200 mm	5
	200–250 mm	6

APPLICATION METHOD / TOOLS

Reference must be made to the Sika Method Statement: SikaSeal®-629 Fire Wrap

FURTHER DOCUMENTS

- Sika Method Statement: SikaSeal®-629 Fire Wrap
- Sika Passive Fire Protection Handbook
- Fire resistance classification reports

LIMITATIONS

- Limitations regarding dimensions and configuration described in the relevant fire resistance classification reports must be considered.

VALUE BASE

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

ECOLOGY, HEALTH AND SAFETY**REGULATION (EC) NO 1907/2006 - REACH**

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use.

A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in this product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0.1 % (w/w)

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA LIMITED

Watchmead
Welwyn Garden City
Hertfordshire, AL7 1BQ
Tel: 01707 394444
Web: www.sika.co.uk
Twitter: @SikaLimited

SIKA IRELAND LIMITED

Ballymun Industrial Estate
Ballymun
Dublin 11, Ireland
Tel: +353 1 862 0709
Web: www.sika.ie
Twitter: @SikaIreland

**Product Data Sheet**

SikaSeal®-629 Fire Wrap
June 2020, Version 02.01
020515100000000015

SikaSeal-629FireWrap-en-GB-(06-2020)-2-1.pdf

