

PRODUCT DATA SHEET

SikaCem[®]-4 A

Water plug

PRODUCT DESCRIPTION

SikaCem[®]-4 A is a rapid-setting waterproofing admixture. When mixed with Ordinary Portland Cement and water, it sets rapidly to seal areas of severe water infiltration through concrete, rock or masonry.

USES

SikaCem[®]-4 A is used for preliminary waterproofing work on wet surfaces or where there is general infiltration of water, prior to the application of subsequent cementitious render or gunite. Typical applications are tunnels and culverts, mine galleries, water reservoirs, concrete pipes and manholes. It can also be used in quick-setting mortar for assembly work, e.g. for fixing anchors, bolts and other fittings subject to early loading in rock or concrete.

CHARACTERISTICS / ADVANTAGES

- Rapid setting for fast leak plugging and/or fixing.
- Ready to use, just add clean water and Ordinary Portland Cement.
- Does not contain chlorides.
- Solvent-free.

PRODUCT INFORMATION

Chemical Base	Blend of inorganic chemicals
Packaging	1L jerry can
Appearance / Colour	Clear liquid
Shelf Life	12 months from the date of manufacture.
Storage Conditions	Store properly in undamaged, original sealed packaging in dry cool conditions at temperatures between 5°C and 30°C. Protect from direct sunlight, frost and contamination.
Density	~1.25 g/cm ³
pH-Value	~12
Total Chloride Ion Content	≤ 0.1 %

APPLICATION INFORMATION

Recommended Dosage	SikaCem [®] -4 A : water = 1 :1 to 1:4, depending on the application Cement : liquid = 3 : 1 approx.
---------------------------	--

Ambient Air Temperature +5°C min / +35°C max

Substrate Temperature +5°C min / +35°C max

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

Surfaces to be treated with SikaCem®-4 A should be thoroughly cleaned, roughened, and washed with fresh, clean water to remove any dirt, debris, loose particles or contaminants. Level off any sharp surface protrusions. Cracks may need to be enlarged to increase the bond.

MIXING

- Wear suitable protective clothes, gloves and goggles whilst working with the material.
- Mix SikaCem®-4 A with clean water at the desired dilution rate, depending on the application and water pressure.
- Pour the liquid into a clean mixing container.
- Quickly pour the cement in until the liquid is covered (approximately 3 parts of cement to 1 part liquid).
- Mix the materials quickly and thoroughly into a paste and use immediately. Do not mix more product than that which can be placed immediately.

APPLICATION METHOD / TOOLS

- Mould the SikaCem®-4 A paste by gloved hand into a plug and place it immediately into the hole, pressing firmly until the mix has set.
- Cover the paste with a subsequent coating of Sika® waterproofing mortar.
- In areas of medium to heavy water infiltration, divert the water to discharge points formed of short lengths of plastic tube bonded into drilled holes using SikaCem®-4 A. This will reduce the pressure until the waterproofing final render has fully hardened. The plastic tubes can then be removed and the holes plugged using a mix of SikaCem®-4 A (diluted 1:1 with water) with cement. Do not apply the final render layer until the discharge tubes have been removed and water infiltration has stopped.
- Where high water pressures are experienced, the prepared area around the discharge tubes may need to be increased to provide a larger surface area for bonding the SikaCem®-4 A paste.

LIMITATIONS

Only use with fresh Ordinary Portland Cement. Setting times will be affected by ambient temperature, water and SikaCem®-4 A temperature, supplier and age of Ordinary Portland Cement.

Trials are recommended varying the SikaCem®-4 A water dosage, temperature and type of Ordinary Portland Cement until the required performance is achieved.

VALUE BASE

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

EVERBUILD BUILDING PRODUCTS LTD

Site 41, Knowsthorpe Way
Cross Green Industrial Estate
Leeds, LS9 0SW
Tel: 0113 240 3456
Web: www.everbuild.co.uk
Twitter: @everbuild

SIKA LIMITED

Watchmead
Welwyn Garden City
Hertfordshire, AL7 1BQ
Tel: 01707 394444
Web: www.sika.co.uk
Twitter: @SikaLimited

Product Data Sheet

SikaCem[®]-4 A
September 2018,
Version 01.01
020705040020000015

3 / 3



BUILDING TRUST

