

PRODUCT DATA SHEET

Sikafloor® Comfort Porefiller

2-COMPONENT PUR PART OF THE SIKA®-COMFORTFLOOR® FLOORING RANGE

PRODUCT DESCRIPTION

Sikafloor®-Comfort Porefiller is a two-part, total solid, low VOC, PUR used for sealing and levelling.

USES

Sikafloor® Comfort Porefiller may only be used by experienced professionals.

- Is a durable high quality compound used for sealing and levelling of the permeable surface of prefabricated granular rubber sheets.
- Particularly suitable for hospitals, schools, sales premises, showrooms, entrance halls, lobbies, open-plan offices, museums, etc.
- For interior use only.

CHARACTERISTICS / ADVANTAGES

- Good bonding properties
- Low VOC
- Non flammable
- No shrinking after curing
- Easy to apply

APPROVALS / STANDARDS

- Coating for concrete protection according to the requirements of EN 1504-2:2004), DoP 010801040400000031041 certified by Factory Production Control Body, 0620 and provided with the CE-mark.
- Fire classification acc. to EN 13501-1, Test report 08-198, Ghent University.
- Emission tested according to AgBB-scheme and guidelines of the DiBt. According to ISO-16000, Eurofins Report No. 771284A.

PRODUCT INFORMATION

Chemical Base	PUR	
Packaging	Part A:	16 kg containers
	Part B:	4 kg containers
	Part A+B:	20.0 kg ready to mix units
Shelf Life	12 months from date of production	
Storage Conditions	The packaging must be stored properly in original, unopened and undamaged sealed packaging, in dry conditions at temperatures between +5°C and +30°C.	
Appearance / Colour	Resin - part A:	light grey, liquid
	Hardener - part B:	brown, transparent, liquid
Density	Mixed resin	~ 1.30 kg/l (DIN EN ISO 2811-1)
	All Density values at +23°C	

TECHNICAL INFORMATION

Tensile Strength	~ 5.0 N/mm ² (14 days / +23°C)	(DIN 53504)
Elongation at Break	~ 60% (14 days / +23°C)	(DIN 53504)

SYSTEM INFORMATION

Systems	Please refer to the System Data Sheet of:	
	Sika Comfortfloor® PS-65	Seamless, smooth, low voc, elastic, polyurethane floor covering with optional colour flakes
	Sika Comfortfloor® PS-66	Seamless, smooth, low voc, elastic, polyurethane floor covering with optional colour flakes

APPLICATION INFORMATION

Mixing Ratio	Part A : part B = 80 : 20 (by weight)		
Consumption	Depending on the Shockpad structure. Approximately 0.4 kg/m ² for the Comfort Regupol 4580 Approximately 0.5 kg/m ² for the Comfort Regupol 6015 H		
Ambient Air Temperature	+10°C min. / +30°C max.		
Relative Air Humidity	80% r.h. max.		
Dew Point	Beware of condensation! The substrate and uncured floor must be at least 3°C above dew point to reduce the risk of condensation or blooming on the floor finish.		
Substrate Temperature	+10°C min. / +30°C max.		
Substrate Moisture Content	< 3% pbw moisture content. Test method: Sika®-Tramex meter, CM - measurement or Oven-dry-method. No rising moisture according to ASTM (Polyethylene-sheet).		
Pot Life	Temperatures	Time	
	+10°C	~ 36 minutes	
	+20°C	~ 20 minutes	
	+30°C	~ 12 minutes	
Curing Time	Before overcoating Sikafloor®-Comfort Porefiller allow:		
	Substrate temperature	Minimum	Maximum
	+10°C	12 hours	72 hours
	+20°C	8 hours	60 hours
	+30°C	6 hours	48 hours
Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity.			
Applied Product Ready for Use	Substrate temperature	Foot traffic	Full cure
	+10°C	12 hours	72 hours
	+20°C	8 hours	60 hours
	+30°C	6 hours	48 hours
	Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity.		

VALUE BASE

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER DOCUMENTS

▪ Substrate Quality and Preparation

Please refer to Sika Information Manual: "EVALUATION AND PREPARATION OF SURFACES FOR FLOORING SYSTEMS".

▪ Application Instructions

Please refer to Sika Information Manual: "MIXING & APPLICATION OF FLOORING SYSTEMS".

▪ Maintenance

Please refer to "Sikafloor®- CLEANING REGIME".

LIMITATIONS

Do not apply Sikafloor®-Comfort Porefiller substrates with rising moisture. Uncured material reacts in contact with water (foaming). During application care must be taken that no sweat drops into fresh Sikafloor®- Sikafloor® Comfort Porefiller (wear head and wrist bands).

If heating is required do not use gas, oil, paraffin or other fossil fuel heaters, these produce large quantities of both CO₂ and H₂O water vapour, which may adversely affect the finish. For heating use only electric powered warm air blower systems.

ECOLOGY, HEALTH AND SAFETY

Regulation (EC) No 1907/2006 (REACH) - Mandatory training

As from 24 August 2023 adequate training is required before industrial or professional use of this product. For more information and a link to the training visit www.sika.com/pu-training.



DIRECTIVE 2004/42/CE - LIMITATION OF EMISSIONS OF VOC

According to the EU-Directive 2004/42, the maximum allowed content of VOC (Product category IIA / j type sb) is 500 g/l (Limit 2010) for the ready to use product. The maximum content of Sikafloor®-Comfort Porefiller is < 500 g/l VOC for the ready to use product.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

The surface must be clean, dry and free of all contaminants such as dirt, oil, grease, coatings and surface treatments, etc. All dust, loose and friable material must be completely removed from all surfaces before application of the product, preferably by vacuum. Pull of strength shall not be less than 1.5 N/mm². If in doubt apply a test area first.

MIXING

Premix the A Component and check the condition of the material. Add the complete contents of the B Component and mix A and B thoroughly to a homogeneous mixture. Do not dilute!

Over mixing must be avoided to minimise air entrainment.

Mixing Tools

Sikafloor®-Comfort Porefiller must be thoroughly mixed using a low speed electric stirrer (300 - 400 rpm) or other suitable equipment.

APPLICATION

Sikafloor®-Comfort Porefiller is poured and spread evenly by means of a metal trowel.

CLEANING OF TOOLS

Clean all tools and application equipment with Thinner C immediately after use. Hardened and/or cured material can only be removed mechanically.

Please refer to the Sika Method Statement Mixing & Application

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA LIMITED

Watchmead
Welwyn Garden City
Hertfordshire, AL7 1BQ
Tel: 01707 394444
Web: www.sika.co.uk
Twitter: @SikaLimited



Product Data Sheet
Sikafloor® Comfort Porefiller
August 2023, Version 02.01
020812040020000019

SikafloorComfortPorefiller-en-GB-(08-2023)-2-1.pdf