

## PRODUCT DATA SHEET

# SikaShield® E79 MG SA 4 mm

Self-adhesive bituminous membrane surfaced with granules and flexible at -25 °C

### PRODUCT DESCRIPTION

SikaShield® E79 MG SA 4 mm is an SBS modified bituminous roof waterproofing membrane with a thickness of 4 mm. It is reinforced with a dimensionally stable composite inlay of a fiberglass mat compressed between two layers of non-woven spunbond polyestser fabric and is flexible at -25 °C. The top surface is coated with mineral granules, which allows the permanent exposure to UV radiation. The underside has a removable liner over the adhesive compound for an easy application.

### USES

The Product is used as a waterproofing membrane for:

- Balconies and terraces
- Flat or sloped roofs with up to 15 % gradient
- Exposed single-layer or as a top sheet in a multi-layer roofing system

### PRODUCT INFORMATION

<b>Chemical Base</b>	Composition	SBS modified bitumen	
	Reinforcing material	Composite inlay of a fibreglass matt compressed between two layers of non-woven spunbond polyester fabric	
<b>Packaging</b>	Roll width	1.0 m	(EN 1848-1)
	Roll length	6.0 m	
	Refer to the current price list for available packaging variations.		
<b>Shelf Life</b>	12 months from date of production		

### CHARACTERISTICS / ADVANTAGES

- Flame-free application
- Highly flexible in cold temperatures
- High adhesion in cold temperatures
- Fully bonded
- High durability
- Fast and easy installation
- Good adhesion in cold temperatures
- Very good mechanical properties (tensile, tear, shear)

### APPROVALS / STANDARDS

- CE marking and declaration of performance based on EN 13707:2004+A2:2009 Flexible sheets for waterproofing — Reinforced bitumen sheets for roof waterproofing — Definitions and characteristics
- BBA Certified (19/5716)

<b>Storage Conditions</b>	The Product must be stored in original unopened and undamaged packaging in dry conditions and temperatures between +5 °C and +35 °C. Store in a vertical position. Do not stack pallets of the rolls on top of each other, or under pallets of any other materials during transport or storage. Always refer to packaging.		
<b>Appearance / Colour</b>	Top surface	Mineral Granules	
	Bottom Surface	Removable foil	
	Top layer colour	Refer to current price list for color variations	
<b>Effective Thickness</b>	Effective thickness	4.0 mm ± 0.2 mm	(EN 1849-2)

## TECHNICAL INFORMATION

<b>Maximum tensile force</b>	Longitudinal (MD)	750 N/50 mm ± 150 N/50 mm	(EN 12311-1)
	Transversal (CMD)	650 N/50 mm ± 130 N/50 mm	
<b>Elongation at maximum tensile force</b>	Longitudinal (MD)	50 % ± 15 %	(EN 12311-1)
	Transversal (CMD)	50 % ± 15 %	
<b>Resistance to Tearing (nail shank)</b>	Longitudinal (MD)	250 N ± 75 N	(EN 12310-1)
	Transversal (CMD)	250 N ± 75 N	
<b>Joint Shear Resistance</b>	Longitudinal (MD)	650 N/50 mm ± 130 N/50 mm	(EN 12317-1)
	Transversal (CMD)	550 N/50 mm ± 110 N/50 mm	
<b>Flexibility at low temperature</b>	≤ -25 °C		(EN 1109)
<b>Water Tightness</b>	Method B, 24 hours at 60 kPa	Pass	(EN 1928)
<b>Reaction to Fire</b>	Class E		(EN 13501-1)

## VALUE BASE

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## ECOLOGY, HEALTH AND SAFETY

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in the product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above

0,1 % (w/w).

## APPLICATION INSTRUCTIONS

Please refer to the SikaShield® Installation Guide

## MAINTENANCE

Check the functionality of the auxiliary works, flashings, drainage outlets, overflow pipes etc. Remove any leaves, moss and other vegetation, which could cause ponding on the roof and overload the drainage system. To maintain the function of the roof waterproofing membrane during its lifespan, it is advisable to arrange periodically for inspection of the membrane and detailing.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### SIKA LIMITED

Watchmead  
Welwyn Garden City  
Hertfordshire, AL7 1BQ  
Tel: 01707 394444  
Web: [www.sika.co.uk](http://www.sika.co.uk)  
Twitter: @SikaLimited



**Product Data Sheet**  
SikaShield® E79 MG SA 4 mm  
July 2023, Version 07.02  
020920011980000104

SikaShieldE79MGSA4mm-en-GB-(07-2023)-7-2.pdf