

PRODUCT DATA SHEET

Mineral Fidia P 4,5 kg/m²

Plastomeric bituminous membrane surfaced with mineral granules and flexible at -10 °C

PRODUCT DESCRIPTION

Mineral Fidia P 4,5 kg/m² is an APP modified bituminous roof waterproofing membrane with a weight of 4.5 kg/m². It is reinforced with a non-woven polyester fabric dimensionally stabilised with glass fibre and is flexible at -10 °C. The top surface is coated with mineral granules, which allows the permanent exposure to UV radiation. The underside of the product has a burn-off film for easy torch-application.

USES

The Product is used as a waterproofing membrane for:

- Balconies and terraces
- Flat or sloping roofs with up to 15 % pitch

The Product is used as a:

- Exposed cap sheet in a multi-layer system

PRODUCT INFORMATION

Chemical Base	Composition Reinforcing material	APP modified bitumen non-woven polyester fabric dimensionally stabilised with glass fibre
Packaging	Roll width	1.0 m (EN 1848-1)
	Roll length	8.0 m
	Refer to current price list for packaging variations.	
Appearance / Colour	Top surface	Mineral Granules
	Bottom surface	Polyethylene film
	Top layer colour	Refer to current price list for color variations
Shelf Life	24 months from date of production	
Storage Conditions	Product must be stored in original unopened and undamaged sealed packaging in dry conditions, away from the elements and at temperatures between +5 °C and +30 °C. Store in a vertical position. Do not stack pallets of the rolls on top of each other, or under pallets of any other materials during transport or storage.	

Mass per unit area	Mass per unit area	4.5 kg/m ² ± 0.45 kg/m ²	(EN 1849-1)
--------------------	--------------------	--	-------------

TECHNICAL INFORMATION

Resistance to Tearing (nail shank)	Longitudinal (MD)	150 N ± 45 N	(EN 12310-1)
	Transversal (CMD)	150 N ± 45 N	
Joint Shear Resistance	Longitudinal	350 N/50 mm ± 70 N/50 mm	(EN 12317-1)
	Transversal	300 N/50 mm ± 60 N/50 mm	
Reaction to Fire	Class E		(EN 13501-1)
Water Tightness	Method B: 24 hours at 60 kPa	Pass	(EN 1928)
Flexibility at low temperature	≤ -10 °C		(EN 1109)
Maximum tensile force	Longitudinal (MD)	450 N/50 mm ± 90 N/50 mm	(EN 12311-1)
	Transversal (CMD)	400 N/50 mm ± 80 N/50 mm	
Elongation at maximum tensile force	Longitudinal (MD)	40 ± 15 [%]	(EN 12311-1)
	Transversal (CMD)	40 ± 15 [%]	

APPLICATION INFORMATION

Ambient Air Temperature	+5 °C min. / +50 °C max.
Relative Air Humidity	80 % max
Substrate Temperature	+5 °C min. / +50 °C max.

VALUE BASE

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ulation or on the candidate list published by the European Chemicals Agency in concentrations above 0,1 % (w/w).

ECOLOGY, HEALTH AND SAFETY

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in the product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0,1 % (w/w).

REGULATION (EC) NO 1907/2006 - REACH

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in the product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH reg-

APPLICATION INSTRUCTIONS

Please refer to Installation Guide

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA LIMITED

Watchmead
Welwyn Garden City
Hertfordshire, AL7 1BQ
Tel: 01707 394444
Web: www.sika.co.uk
Twitter: @SikaLimited



Product Data Sheet
Mineral Fidia P 4,5 kg/m²
February 2025, Version 02.01
020920011990000927

MineralFidiaP45kgm-en-GB-(02-2025)-2-1.pdf