

PRODUCT DATA SHEET

Parex Standard Mortar - Walling

Brick Pointing Mortar

DESCRIPTION

Designed for gun-injection, Parex Standard Mortar provides a clean, quick, lasting solution for pointing sound brickwork or masonry.

USES

Consistent in both colour and finish, Parex Standard Mortars are pumped deep into the joint, providing a complete fill to create high strength joints. The finished joints are highly resistant to weather and freeze-thaw action. Parex Standard Mortar can be injected into joints as narrow as 5 mm and will penetrate to a depth in excess of 100 mm, allowing for the deepest of joints.

CHARACTERISTICS / ADVANTAGES

- Fast Application
- Cost Effective
- High Strength
- Complete Joint Fill
- Stain-free & Colour Consistent

PRODUCT INFORMATION

Composition	Cement, aggregate and additives for performance
Packaging	25 kg Bag
Shelf life	6 Months from date of manufacture
Storage conditions	Dry frost free conditions
Appearance and colour	Available in a range of colours. Please contact for further information.
Compressive strength	Class M5
Thermal conductivity	P=50 % 1.23 W(m.K), P=90 % 1.34 W(m.K)
Water absorption	0.03 kg (m ² min ^{0.5})
Permeability to water vapour	μ 15/35
Reaction to fire	Class A1
Mixing ratio	4.0 to 4.25 L of water per bag
Consumption	Coverage will vary according to the width and depth of the joint (E.g. on

brickwork with 10 mm joints filled to a depth of 15 mm, 1 bag of mortar will cover approximately 5.5 m² of wall area)

Pot Life	45 Minutes
-----------------	------------

Initial set time	2.5 Hours
-------------------------	-----------

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION

Instructions for Use

Joint Preparation

In order to ensure adequate bonding of the new mortar to the masonry, it is important that the old mortar is removed and that any residual dust is removed from the joint. Cut out defective mortar to a minimum depth 1.5 times joint width. Flush out with compressed air or water and leave surface damp.

Mixing

Mix whole bag of powder. Place 4-4.25 L of clean water in a mixing tub and gradually add dry Parex Standard Mortar whilst mixing (the quantity of water will vary with the colour used). Mix using a low speed/paddle mixer with clean water to produce a mortar with a consistency of finishing plaster. Allow to stand for 5 minutes and remix. To check consistency, fill the pointing gun to within 12 mm of the top and shake. Check correct consistency by filling the tube, the mortar should hang from the end of the nozzle when the tube is shaken. A ribbon of mortar should appear from the nozzle.

Placing

Keeping the nozzle just clear of the wall, inject the mortar into the joint, slightly overfilling, working from the top of the wall downwards. The mortar should be tooled off after it has formed a semi-dry surface skin and lost its initial sheen. The time this takes depends upon the absorbency of the masonry. Place the nozzle the face of the joint and inject the mortar filling the perpendiculars first and starting from the bottom of each joint. Finish the horizontal joints after 1-2 metres have been completed to the required profile. Parex® Standard Mortar may be placed at temperatures between +5 °C and +35 °C. Do not carry out jointing work if rain is expected.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA LIMITED

Watchmead
Welwyn Garden City
Hertfordshire, AL7 1BQ
Tel: 01707 394444
Web: www.sika.co.uk
Twitter: @SikaLimited