# Sikafloor<sup>®</sup> Marine KG-202 N Lightweight primary deck covering mortar

# **Technical Product Data**

Chemical base	Polymer modified cement mortar
Colour	Grey
Cure mechanism	Hydraulic
Mixing ratio with cold, potable water per 17 kg bag	4.2 - 5.1 litres
Density fresh mixed (CQP <sup>1</sup> 599-3)	1.1 g/cm <sup>3</sup> approx.
Density cured <sup>2</sup> (CQP 599-4)	0.9 g/cm <sup>3</sup> approx.
Substrate temperature	5 - 35 °C
Application thickness	8 - 100 mm
Coverage per 17 kg bag (layer thickness 1 mm)	18 m <sup>2</sup> approx.
Working time <sup>3</sup> (CQP 599-9)	30 minutes approx.
Ready to walk on <sup>3</sup> (CQP 600-3) depending on humidity and ventilation	10 hours approx.
Compressive strength <sup>4</sup> (CQP 599-2)	12 MPa approx.
Flexural strength <sup>4</sup> (CQP 599-1)	5 MPa approx.
Modulus of elasticity in compression <sup>4</sup> (CQP 599-6)	2.9 GPa approx.
Linear shrinkage <sup>4</sup> (CQP 599-5)	0.03 % approx.
Shelf life (CQP 600-1) Stored in a cool, dry place below 25 °C	12 months
<sup>1)</sup> Corporate Quality Procedure <sup>2)</sup> After 7 days <sup>3)</sup> 23 °C / 50 % r.h. <sup>4)</sup> After 28 days	

<sup>7</sup> Corporate Quality Procedure <sup>27</sup> After 7 days <sup>37</sup> 23 °C / 50 % r.h.

## Description

Equipment Directives.

Sikafloor<sup>®</sup> Marine KG-202 N is a one component light weight leveling mortar based on polymer modified cement. Sikafloor<sup>®</sup> Marine KG-202 N is manufactured in accordance with ISO 9001 / 14001 quality assurance and tested according to FTP Code system and approved according to the IMO Marine

## **Product Benefits**

- Lightweight leveling mortar
- Low E-modulus
- One component, ready to mix
- Easy applicable
- Also suitable for sloped surfaces
- Can be pumped

## Areas of Application

Sikafloor<sup>®</sup> Marine KG-202 N is applied on interior decks, to level the surface prior to the application of deck finishing materials such as: carpets, tiles, parquet, rubber and vinyl. It is suitable for application in wet and dry accommodation areas. For wet areas prior to tiles application, the substrate has to be additionally treated with a water resistant membrane (e.g. Sikafloor<sup>®</sup> Marine Elastic). Before application of vinyl and carpet coverings, we recommend to apply a self-leveling mortar such as Sikafloor<sup>®</sup> Marine 100 to obtain a smooth surface.

This product is suitable for professional experienced users only. Tests with actual substrates and conditions have to be performed to ensure adhesion and material compatibility.





## **Cure Mechanism**

Sikafloor<sup>®</sup> Marine KG-202 N cures by way of hydraulic curing.

#### Method of Application

Surface preparation

The surface has to be clean, free from dust, grease, oils and other substances, which may impair the adhesion. Rust has to be removed with a steel brush or other appropriate means, followed by a vacuum cleaning.

The surface has to be primed with Sikafloor<sup>®</sup> Marine Primer-C using a long hair roller. After the drying of the primer Sikafloor<sup>®</sup> Marine KG-202 N may be applied.

For the Sikafloor<sup>®</sup> Marine KG-202 N application on aluminum or zinc rich shop primer coated decks, a tie coat of SikaCor<sup>®</sup> ZP Primer or another suitable tie coat is required prior the priming step with Sikafloor<sup>®</sup> Marine Primer-C.

For further information please contact the Technical Department of Sika Industry.

#### Mixing process

A bag of Sikafloor® Marine KG-202 N is mixed with 4.2 to 5.1 litres of cold, potable water. The mixing time is approx. 3 minutes at low speed (with drilling machine) or with a cement mixer for larger amounts until a homogenous mortar is obtained. If mixed by hand ensure the powder is mixed completely (bottom and side walls of the bucket).

#### Application

Apply the mortar with a steel board or a straight edge.

Sikafloor<sup>®</sup> Marine KG-202 N has to be applied within 30 minutes after mixing. At temperatures above 35 °C the open time will be reduced to 10 minutes or less. For advice on selecting and setting up a suitable pump system please contact the System Engineering Department of Sika Industry. *Curing* After application, the finished areas have to be protected against direct heat (e.g. cutting or welding from beneath), sunlight and draught during the curing process for at least one day after application. Before covering Sikafloor<sup>®</sup> Marine KG-202 N with dense materials such as vinyl, epoxy coatings, etc., ensure that the remaining moisture

level is below 4 %. Test procedure to determine the

- dryness (according ASTM D 4263) - put a PE-plastic foil 1 m x 1 m on the surface of the applied mortar
- floor - tape the perimeter and leave for
- one day

The curing is complete if there is no water condensation on the foil or a visible color difference between covered and uncovered surface.

#### Removal

Excess material can best be removed before curing with a trowel wipe.

Uncured Sikafloor<sup>®</sup> Marine KG-202 N may be removed from tools and equipment with water. Once cured, the material can only be removed mechanically. Exposed hands and skin should be washed immediately with water. It is recommended to use a suitable skin protection hand cream.

#### **Further information**

Copies of the following publications are available on request:

- Safety Data Sheet
- Application Guide Sikafloor<sup>®</sup> Marine KG-202 N

#### **Packaging Information**

Bag	17 kg
-----	-------

### Value Bases

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## Health and Safety Information

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safetyrelated data.

#### Legal Notes

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



Further information available at: www.sika.co.uk

Sika Limited Industry Watchmead Welwyn Garden City Herts, AL7 1BQ Tel, +44 (0)1707 394444

