

## PRODUCT DATA SHEET

# Sika® Ucrete® PFS

(formerly Ucrete® PFS)

Rapid curing slurry primer for Sika® Ucrete® flooring

### PRODUCT DESCRIPTION

Sika® Ucrete® PFS is a rapid curing slurry primer applied by squeegee and trowel to prepared concrete substrates. It provides a smooth, even and completely sealed substrate prior to overlaying with Sika® Ucrete® industrial flooring.

### USES

Sika® Ucrete® PFS is used as a primer for Sika® Ucrete® industrial flooring systems.

Sika® Ucrete® PFS is used within wet and dry process areas including the following application areas:

- Food and beverage facilities
- Pharmaceutical facilities
- Chemical and processing facilities
- Manufacturing facilities and workshops

Please note:

- The Product may only be used by experienced professionals.

### CHARACTERISTICS / ADVANTAGES

- Expert installation by fully trained and licensed applicators
- Suitable for application on to 7-day-old concrete and 3-day-old polymer screed
- Overcoating time of approximately 3 hours at +20 °C
- Long open time
- Low VOC emissions
- Good adhesion to green or hardened damp concrete
- Good temperature resistance
- Non-tainting from the end of mixing

### APPROVALS / STANDARDS

- Halal Certification Europe (HCE), Sika® Ucrete®, WHFC, Certificate No. 21453-2/1/1/Y1
- Food and Beverage Facilities Suitability, Sika® Ucrete®, HACCP, Test Report No. I-PE-769-SA-2-RG-06b
- Indoor Air Comfort Gold EN 16516, Sika® Ucrete®, eurofins, Certificate No. IACG-321-01-01-2023

### PRODUCT INFORMATION

<b>Chemical Base</b>	Water-based polyurethane cement hybrid
<b>Packaging</b>	12.69 kg Refer to the current price list for available packaging variations.
<b>Shelf Life</b>	Always refer to the best-before date of the individual packaging.
<b>Storage Conditions</b>	The Product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +30 °C. Always refer to the packaging. Refer to the current Safety Data Sheet for information on safe handling and storage.

### TECHNICAL INFORMATION

Tensile adhesion strength > 2.0 N/mm<sup>2</sup> (concrete failure) (EN 1542)

Chemical Resistance Laboratory-defined resistance to many individual chemicals. Before proceeding, contact Sika Technical Service for specific information.

## APPLICATION INFORMATION

Consumption 0.6-2.0 kg/m<sup>2</sup>

Layer Thickness 0.3 mm to 1.0 mm

Product Temperature	Maximum	+20 °C
	Minimum	+10 °C

Ambient Air Temperature	Maximum	+30 °C
	Minimum	+5 °C

Dew Point Beware of condensation. The substrate and uncured applied product must be at least +3 °C above the dew point to reduce the risk of condensation or blooming on the surface of the applied product. Low temperatures and high humidity conditions increase the probability of blooming.

Substrate Temperature	Maximum	+30 °C
	Minimum	+5 °C

Waiting Time / Overcoating	+5 °C and 50 % r.h.	6 hours
	+10 °C and 50 % r.h.	3 hours
	+20 °C and 50 % r.h.	2 hours
	+30 °C and 50 % r.h.	2 hours

Note: Times are approximate and will be affected by changing ambient conditions, particularly temperature and relative humidity.

## VALUE BASE

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

### Regulation (EC) No 1907/2006 (REACH) - Mandatory training

As from 24 August 2023 adequate training is required before industrial or professional use of this product. For more information and a link to the training visit [www.sika.com/pu-training](http://www.sika.com/pu-training).



## APPLICATION INSTRUCTIONS

### SUBSTRATE PREPARATION

#### IMPORTANT

#### Reduced service life due to incorrect treatment of cracks

The incorrect assessment and treatment of cracks may lead to a reduced service life and reflective cracking.

1. For static cracks, ensure the width is suitable for overcoating with Sika® Ucrete® PFS.
2. For dynamic cracks, ensure the movement is within the movement capacity of Sika® Ucrete® PFS.

#### TREATMENT OF JOINTS AND CRACKS

Construction joints and existing static surface cracks in substrate require pre-treating before full layer application. Use Sikadur® or Sikafloor® resins.

The Product can be applied on green or damp concrete with no standing water. Allow for at least 3 days for early concrete shrinkage to occur to prevent shrinkage cracks from appearing on the wearing surface.

Cementitious substrates must be structurally sound and of sufficient compressive strength (minimum 30 N/mm<sup>2</sup>) with a minimum tensile strength of 1.5 N/mm<sup>2</sup>.

Substrates must be clean, dry and free of contaminants such as dirt, oil, grease, coatings, laitance, surface treatments and loose friable material.

## APPLICATION

Application must be undertaken by a fully trained and licensed Sika® Ucrete® applicator.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### SIKA LIMITED

Watchmead  
Welwyn Garden City  
Hertfordshire, AL7 1BQ  
Tel: 01707 394444  
Web: [www.sika.co.uk](http://www.sika.co.uk)  
Twitter: @SikaLimited



### Product Data Sheet

Sika® Ucrete® PFS  
July 2024, Version 01.01  
02081400000002023

SikaUcretePFS-en-GB-(07-2024)-1-1.pdf