Sarnafil[®] G 410-12EL Felt

Polymeric membrane for roof waterproofing

Product Description	Sarnafil [®] G 410-12EL Felt (thickness 1.2 mm) is a multi-layer, synthetic roof waterproofing sheet based on premium-quality polyvinyl chloride (PVC) with inlay of glass non-woven and with a polyester fleece backing. Sarnafil [®] G 410-12EL Felt contains ultraviolet light stabilizers and flame retardant according to EN 13956.		
	Sarnafil [®] G 410-12EL Felt is a hot air weldable roof membrane, formulated for direct exposure and designed to use in all global climatic conditions. Sarnafil [®] G 410-12EL Felt is produced with an integral glass non-woven carrier for dimensional stability. Sarnafil [®] G 410-12EL Felt is used with the Adhered System.		
	Sarnafil [®] G 410-12EL Felt has a unique lacquer coating applied to the top of the membrane to resist staining from airborne dirt and pollutants.		
	Sarnafil [®] G 410-12EL Felt has no built-in stress at the time of production and has a fully encapsulated carrier with no risk to delamination or water-wicking. The dimensional stability of Sarnafil [®] G 410-12EL Felt is excellent. Sarnafil [®] G 410-12EL Felt is excellent. Sarnafil [®] G 410-12EL Felt is excellent. Sarnafil [®]		
Uses	Roof waterproofing membrane for exposed flat roofs:		
	 Fully bonded roof surfaces with contact adhesive Sarnacol[®] 2170 or Sarnacol[®] 2142S depending on substrates. 		
Characteristics / Advantages	 Outstanding resistance to weathering, including permanent UV irradiation Excellent flexibility in cold temperatures No built-in stress at the time of production High dimensional stability High water vapour permeability Excellent weldability No risk of delamination or water-wicking Can be produced also in a variety of colours Lacquer coated surface Recyclable 		
Approval / Standards	Sarnafil [®] G 410-12EL Felt is designed and manufactured to meet most international recognised standards.		
	Polymeric sheets for roof waterproofing according to EN 13956, certified by notified body 1213-CPD-3916 and provided with the CE-mark.		
	Reaction to fire according to EN 13501-1.		
	External fire performance tested according to EN 1187 and classified according to EN 13501-5: B _{ROOF} (t1).		
	 Official Quality Approvals and Agrement Certificates and approvals. 		
	 Monitoring and assessment by approved laboratories. 		
	Quality Management system in accordance with EN ISO 9001/14001.		



0

Appearance / Colours	Surface:	matt
	Colours:	
	Top surface:	light grey (nearest RAL 7047) lead grey (Sika colour no. 9500) copper patina (Sika colour no. 6525) window grey (nearest RAL 7040) copper brown (nearest RAL 8004) azure blue (nearest RAL 5009) traffic white (nearest RAL 9016) Top surface in other colours available on request, subject to small minimum order quantities.
	Bottom surface:	dark grey
Packaging	Sarnafil [®] G 410-12EL Felt standard rolls are wrapped individually in a blue PE-foil.	
	Packing unit: Roll length: Roll width: Roll weight:	up to 27 rolls per pallet 20.00 m 2.00 m 72.00 kg
Storage Conditions / Shelf-Life	Rolls must be stored in a horizontal position on pallet and protected from direct sunlight, rain and snow. Product does not expire if correctly stored.	

Technical Data

Technical Data		
Product Declaration	EN 13956	
Visible defects	Pass	EN 1850-2
Length	20m (-0% / +5%)	EN 1848-2
Width	2m (-0.5% / +1%)	EN 1848-2
Straightness	\leq 30 mm	EN 1848-2
Flatness	$\leq 10mm$	EN 1848-2
Effective thickness	1.2mm(-5% / +10%)	EN 1849-2
Mass per unit area	1.8 kg/m² (-5% / +10%)	EN 1849-2
Water tightness	Pass	EN 1928
Effects of liquid chemicals, including water	On request	EN 1847
External fire performance:		EN 1187
Part 1-4	$B_{ROOF}(t1) < 20^{\circ}$	EN 13501-5
Reaction to fire	E	EN ISO 11925-2, classification to EN 13501-1
Hail resistance:		EN 13583
rigid substrate flexible substrate	≥ 17 m/s ≥ 25 m/s	
Joint peel resistance	\geq 300 N/50 mm	EN 12316-2
Joint shear resistance	\geq 600 N/50 mm	EN 12317-2
Water vapour transmission properties	μ = 15'000	EN 1931
Tensile strength, longitudinal (md) ¹⁾ transversal (cmd) ²⁾	≥ 650 N/50 mm ≥ 650 N/50 mm	EN 12311-2
Elongation, longitudinal (md) ¹⁾ transversal (cmd) ²⁾	$\geq 65\%$ $\geq 65\%$	EN 12311-2
Resistance to impact, hard substrate soft substrate	≥ 500 mm ≥ 1250 mm	EN 12691
Resistance to static load, soft substrate rigid substrate	≥ 20 kg ≥ 20 kg	EN 12730
Dimension stability, longitudinal (md) ¹⁾ transversal (cmd) ²⁾	≤ 0.2 % ≤ 0.1 %	EN 1107-2
Foldability at low temperature	≤ -25 °C	EN 495-5
UV exposure	Pass (> 5000 h)	EN 1297
	¹⁾ md = machine direction	

 $^{2)}$ cmd = cross machine direction

System Information	
System Structure	Wide range of accessories is available e.g. prefabricated parts, roof drains, scuppers, walkway pad, decor profiles and protection sheets.
	The following materials are strongly recommended: Sarnafil [®] G 410-12EL Sheet for detailing Sarnafil [®] G 410-12EL for Coverstrips Sarnafil [®] Metal Sheet Sarnabar Peelstops Sarna Seam Cleaner Sarnacol [®] 2170 (contact adhesive) Sarna Cleaner
Application Details	
Substrate Quality	The substrate surface must be uniform, smooth and free of any sharp protrusions or burrs, etc.
	The supporting layer must be compatible to the membrane, solvent resistant, clean, dry and free of grease and dust. Metal sheets must be degreased with Sarna Cleaner before adhesive is applied.
Application Conditions / Limits	
Temperature	The use of Sarnafil [®] G 410-12EL Felt membrane is limited to geographical locations with average monthly minimum temperatures of -50 °C. Permanent ambient temperature during use is limited to +50 °C.
Compatibility	Not compatible with direct contact to other plastics, e.g. EPS and XPS. not resistant to tar, bitumen, oil and solvent containing materials.

Installation Instructions	
Installation Method / Tools	Installation procedure: According to the valid installation instructions for Sarnafil [®] G 410-EL types system fully bonded for exposed roofs.
	Fully adhered roof surfaces and junction areas: The roof waterproofing membrane is bonded to substrate by contact adhesive Sarnacol [®] 2170 or PUR adhesive Sarnacol [®] 2142S depending on the type and slope of substrate. Seam overlaps are welded by hot air.
	Adhering flashings Sarnafil [®] G 410-12EL Felt is adhered to substrate layers such as reinforced concrete, rendering, timber panels, metal sheets etc. using Sarnacol [®] 2170 adhesive.
	Welding Method: Overlap seams are welded by electric heat welding equipment, such as manual hot air welding machines and pressure rollers or automatic hot air welding machines with controlled hot air temperature.
	Recommended type of equipment: manual: Leister Triac PID / automatic: Sarnamatic 661 ^{plus} .
	Welding parameters including temperature, machine speed, air flow, pressure and machine settings must be evaluated, adapted and checked on site according to the type of equipment and the climatic situation prior to welding. The effective width of welded overlaps by hot air should be minimum 20 mm.
	The seams must be mechanically tested with screw drivers to ensure the integrity / completion of the weld. Any imperfections must be rectified by hot air welding.
Notes on Installation / Limits	Installation works must be carried out only by Registered Sarnafil Contractors.
	Temperature limits for the installation of the membrane:
	Substrate temperature: -30 °C min. / +60 °C max. Ambient temperature: -20 °C min. / +60 °C max.
	Installation of some ancillary products, e.g. contact adhesives / cleaners is limited to temperatures above +5 °C. Please observe information given by Product Data Sheets.
	Special measures may be compulsory for installation below +5 °C ambient temperature due to safety requirements in accordance with national regulations.

nical data stated in this Product Data Sheet are based on laboratory tests. neasured data may vary due to circumstances beyond our control.	
Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.	
duct does not fall within the EC-regulation of hazardous goods. sult, a material safety data sheet following EC-Guideline 91/155 EWG is not to bring the product to the market, transport or use it. duct does not damage the environment when used as specified.	
r ventilation must be ensured, when working (welding) in closed rooms.	
fety regulations must be observed.	
duct is not classified as hazardous good for transport.	
erial is recyclable. Disposal must be in accordance with Regulatory es.	

All data in our product information are based on our current knowledge and experience. They do not release users from careful testing of the application and strict observation of the relevant processing regulations because of the wide range of possible influences during the application and use of our products. Legally valid assurances of specific characteristics or suitability for special purposes of application other than those provided in our documentation for the specific product cannot be inferred from our information. Any protective rights or existing laws and provisions must be followed by the recipient or processor of our products at their own responsibility. Moreover our general terms and conditions of sale and guarantee are valid.

Sika Ltd, Bankside 300, Peachman Way, Broadland Business Park, Norwich, NR7 0WF.

Tel: 01603 709360 Fax: 01603 433436 Email: sarnafilroofing@uk.sika.com

Registered Office: Sika Ltd, Watchmead, Welwyn Garden City, Hertfordshire, AL7 1BQ Registered in England: 226822





Sarnafil® G 410-12EL Felt