

PRODUCT DATA SHEET

SikaShield® RoofPro T-03 E42

Elastomeric torch applied bituminous roof membrane surfaced with mineral granules and flexible at -15 °C

PRODUCT DESCRIPTION

SikaShield® RoofPro T-03 E42 is an SBS modified bituminous roof waterproofing membrane which is torch applied and flexible at -15 °C. It is reinforced with a nonwoven polyester fabric. The underside has a burn-off film for easy application.

USES

Roof waterproofing membrane for:

- Flat and sloping roofs
- New buildings and refurbishment projects
- As a cap sheet in a two layer roofing system in conjunction with SikaShield® RoofPro T-03 E40 or as an exposed single-layer roofing system

CHARACTERISTICS / ADVANTAGES

- Top surface finish: decorative mineral granules
- Good watertightness
- Good elongation and cold flexibility
- Thickness: 4,2 mm
- High mechanical properties (tensile, tear)
- Easy to install by torching method

APPROVALS / STANDARDS

- BROOF (t1) External fire resistance to EN 13501-5
- Class E Reaction to fire to EN 13501-1
- Declaration of Performance to EN 13707 - Reinforced bitumen sheets for roof waterproofing

PRODUCT INFORMATION

Chemical Base	SBS modified bitumen	
Reinforcing Material	Non-woven polyester fabric	
Packaging	Roll Size	
	Length	7.5m
	Width	1m
Appearance / Colour	Top surface	Mineral granules
	Backing	Polyethylene film
Shelf Life	36 months from date of production	
Storage Conditions	Product must be stored in original unopened and undamaged packaging in dry conditions and temperatures between +5 °C and +35 °C. Store in a vertical position. Do not stack pallets of the rolls on top of each other, or under pallets of any other materials during transport or storage. Always refer to packaging.	
Length	7,5 m ± 1,0 %	(EN 1848-1)
Width	1 m ± 1,0 %	(EN 1848-1)

Effective Thickness 4,2 mm ± 0,2 mm (EN1849-1)

TECHNICAL INFORMATION

Tensile Strength	Longitudinal	900 ± 250 N/50 mm	(EN 12311-1)
	Transversal	800 ± 250 N/50 mm	
Elongation	Longitudinal	50 % ± 10 %	(EN 12311-1)
	Transversal	50 % ± 10 %	
Flexibility at low temperature	≤ -15 °C		(EN 1109)
Flow resistance	≥ +90 °C		(EN 1110)
Water Tightness	200 kPa (Test method B)		(EN 1928)
External Fire Performance	Broof (t1) - depending on system		(EN 13501-5)
Reaction to Fire	Class E		(EN 13501-1)

APPLICATION INFORMATION

Ambient Air Temperature +5 °C min. / +50 °C max.

Relative Air Humidity 80 % max.

Substrate Temperature +5 °C min. / +50 °C max.

VALUE BASE

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LIMITATIONS

- At low temperatures, take care unrolling to avoid damaging the membrane.
- Use suitable footwear to avoid puncturing the membrane.
- Do not apply to wet, damp or unclean surfaces.
- Do not over-torch the membrane otherwise the polyester reinforcement (which melts at +260 °C) will be damaged making the membrane un-useable.
- If membrane is insufficiently heated, this can cause reduced adhesion to the substrate, between layers or on the overlaps. If this occurs, un-bonded areas must be lifted and re-torched.
- If a seasonal symbol is printed on the roll's label, it is advisable to use the membrane during the indicated season.

ECOLOGY, HEALTH AND SAFETY

REGULATION (EC) NO 1907/2006 - REACH

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in the product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0,1 % (w/w).

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

- The supporting structure must be of sufficient structural strength to apply all new and existing layers of the roof build-up.
- The complete roof system must be designed and secured against wind uplift loadings.
- The substrate must be uniform, firm, smooth and free of any sharp protrusion or burrs, clean, dry, free of grease, bitumen, oil, dust and loosely adhering particles.

SUBSTRATE PREPARATION

Use the appropriate preparation equipment to achieve the required substrate quality.

APPLICATION METHOD / TOOLS

Installation procedure

Strictly follow installation procedures as defined in method statements, application manuals and working instructions which must always be adjusted to the actual site conditions

Priming

Apply the appropriate primer from the Igoflex® P range, at the correct consumption to the prepared dry surface and allow to dry before next application stage. Refer to the individual Product Data Sheets.

Alignment

Unroll, align and re-roll correctly before torching.

Overlaps

Side: 100mm. End: 150 mm.

Overlaps must be restricted to 3 membrane sheets, which can form a 'T' overlap. 4 membrane sheets forming a 'Cross' overlap must be avoided.

Torching

Use a gas burner to heat the substrate and the backing film on the underside of membrane. When the backing film starts to melt, the membrane is ready to stick. Roll the membrane forward and press firmly against the substrate to bond. Ensure a bead of melted bitumen is visible along the full length of the overlap sides and ends when laying.

Detailing

All details such as internal and external corners, up-stands, vent pipes, drains, support metalwork etc. must be cut and sealed effectively. Detailing must follow the recommended guidelines and good practice for torch-applied membranes.

Protection

The membrane must be protected from damage during any ongoing site activities.

MAINTENANCE

To maintain the function of the roof during its lifespan, it is advisable to arrange periodically for inspection of the membrane and detailing. Check the functionality of the auxiliary works, flashings, drainage outlets, overflow pipes etc. including removing leaves, moss and other vegetation, which could cause ponding on the roof and overload the drainage system.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA LIMITED

Watchmead
Welwyn Garden City
Hertfordshire, AL7 1BQ
Tel: 01707 394444
Web: www.sika.co.uk
Twitter: @SikaLimited



Product Data Sheet
SikaShield® RoofPro T-03 E42
March 2021, Version 01.01
020920011990001597

SikaShieldRoofProT-03E42-en-GB-(03-2021)-1-1.pdf