

PRODUCT DATA SHEET

Sika® Deep Fill Rapid Repair Mortar

Rapid setting sand & cement

PRODUCT DESCRIPTION

Sika® Deep Fill Rapid Repair Mortar is a specially formulated, cement-based mix containing fine sharp sand, designed for filling deep holes and voids from 25 mm to 150 mm in depth (1-6 inches). It is formulated to set hard in approx. 30 minutes and is ideal for patching deep repairs on walls and floors.

USES

Suitable for making rapid repairs to a wide variety of masonry surfaces:

- Repairs cracks and holes in concrete, stone and brick.
- Suitable for patch repairs to steps, kerbstones, and window sills.
- For use on internal and external walls and floors.
- Weatherproof.
- Seals and joints drains and pipes.
- Bedding of sanitary ware (sinks, WCs, etc.).
- Fills gaps around pipes and service penetrations.
- Suitable for repairing pointing.
- Sets railings, posts and street ironwork.
- Resets bolts and brackets.
- Suitable for virtually any application where a sand and cement mixture would be used.

CHARACTERISTICS / ADVANTAGES

- Rapid setting (30 minutes, depending on ambient temperature and conditions).
- Easy mixing, just add water.
- Fills from 25 mm to 150 mm in one application (for smaller holes < 25 mm use Sika® Rapid Repair Cement).
- Sets in the cold and wet.

APPROVALS / STANDARDS

Conforms to EN 1504-3 Class R3.

PRODUCT INFORMATION

Chemical Base	Cement and aggregates.
Packaging	2 kg & 6 kg bags.
Colour	Grey.
Shelf Life	12 months from date of manufacture in original unopened bag. Any opened bag should be used within 1 month.
Storage Conditions	Store in cool dry conditions between +5 °C and +25 °C. Storage outside these parameters will significantly reduce shelf life.

VALUE BASE

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LIMITATIONS

- In warm conditions cover with polythene to assist curing.
- For repairs to fish ponds and pools, use Sika® Water-proof Rapid Repair Cement and seal with a suitable paint before refilling.
- For the maximum carbonation resistance for steel work, and to further reduce capillary water absorption, overcoat with a protective system conforming to EN1504-2.
- For load-bearing applications use Sika AnchorFix®, and for applications requiring chemical resistance use the Sika® Epoxy Mortar Repair Kit.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

Before application, ensure the repair area is clean and free from grease, dust, dirt and debris. Thoroughly wet the surface to be treated to improve adhesion.

APPLICATION

- Always use clean, dry tools and add approximately 3-parts powder to 1-part clean, cold water by volume.
- Mix quickly to form a smooth paste.
- IMPORTANT: Do not mix more cement than can be used within 5–10 minutes.
- Apply the mixture immediately with a trowel or filling knife, working it well into area.
- Level with the surrounding surface, as the mixture will begin to set within 10 minutes.
- Once the product begins to stiffen, do not use any remaining residue or add further water to the mix, as this will reduce its strength.
- In warm conditions, cover with polythene to assist curing.

CLEANING OF TOOLS

Clean all tools immediately with warm water before the repair mortar dries.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA LIMITED

Watchmead
Welwyn Garden City
Hertfordshire, AL7 1BQ
Tel: 01707 394444
Web: www.sika.co.uk
Twitter: @SikaLimited



Product Data Sheet

Sika® Deep Fill Rapid Repair Mortar
October 2026, Version 02.01
020201010030265408

SikaDeepFillRapidRepairMortar-en-GB-(10-2026)-2-1.pdf