

SYSTEM DATA SHEET

Sikafloor® MultiDur WT-10

TEXTURED WATER BASED EPOXY FLOOR COVERING

PRODUCT DESCRIPTION

Sikafloor® MultiDur WT-10 is a textured, coloured, water dispersed epoxy floor covering

USES

Sikafloor® MultiDur WT-10 may only be used by experienced professionals.

- Can be subjected to normal up to medium heavy mechanical and chemical loading
- For production areas, warehouses, car park decks, garages, etc.

CHARACTERISTICS / ADVANTAGES


- Good chemical and mechanical resistance
- Water vapour permeable
- Can be diluted with water
- Odourless
- Easy application

APPROVALS / STANDARDS

- Fire classification in accordance with EN 13501-1, Report-No. PB-Hoch-130019, Germany, January 2013.

SYSTEM INFORMATION

System Structure



Sikafloor® MultiDur WT-10 system (~ 0.4-0.6 mm)

1. Primer	Sikafloor®-2540 W+5% wt. water
2. Top coat	Sikafloor®- 2540 W + Extender T

Composition	Epoxy waterborne
Appearance	Textured, semi-gloss finish
Colour	Available in various colour shades.
Nominal Thickness	~ 0.4–0.6mm

TECHNICAL INFORMATION

Reaction to Fire	Bfl-S1	(EN 13501-1)								
Chemical Resistance	Contact Sika technical service for specific information									
Thermal Resistance	<table border="1"> <thead> <tr> <th>Exposure*</th> <th>Dry heat</th> </tr> </thead> <tbody> <tr> <td>Permanent</td> <td>+60 °C</td> </tr> <tr> <td>Short-term max. 7 d</td> <td>+80 °C</td> </tr> <tr> <td>Short-term max. 12 h</td> <td>+100 °C</td> </tr> </tbody> </table> <p>Short-term moist/wet heat* up to +80 °C where exposure is only occasional (i.e. during steam cleaning etc.) *No simultaneous chemical and mechanical exposure.</p>	Exposure*	Dry heat	Permanent	+60 °C	Short-term max. 7 d	+80 °C	Short-term max. 12 h	+100 °C	
Exposure*	Dry heat									
Permanent	+60 °C									
Short-term max. 7 d	+80 °C									
Short-term max. 12 h	+100 °C									

APPLICATION INFORMATION

Consumption	Sikafloor® MultiDur WT-10 system (~ 0.4-0.6 mm)		
	Coating System	Product	Consumption
	Primer	1 × Sikafloor®-2540 W + 5 % wt. water	~0.2–0.3 kg/m ²
	Top coat	1-2 × Sikafloor®- 2540 W + 2 % Extender T	~0.2–0.3 kg/m ² per layer
Product Temperature	Please refer to the individual Product Data Sheets		
Ambient Air Temperature	+10 °C min. / +30 °C max.		
Relative Air Humidity	75 % r.h. max., adequate fresh air ventilation must be provided to remove excess moisture during curing.		
Dew Point	Beware of condensation!		

The substrate and uncured floor must be at least 3 °C above dew point to reduce the risk of condensation or blooming on the floor finish.

Substrate Temperature	+10 °C min. / +30 °C max.		
Substrate Moisture Content	When performing application work with Sikafloor® MultiDur WT-10, the substrate moisture content must not exceed 6 % pbw measured by Tramex. Test method: Sika®-Tramex meter, CM - measurement or Oven-dry-method. No rising moisture according to ASTM (Polyethylene-sheet).		
Waiting Time / Overcoating	Before applying Sikafloor®-2540 W on Sikafloor®-2540 W allow:		
	Substrate temperature	Minimum	Maximum
	+10 °C	48 hours	7 days
	+20 °C	20 hours	6 days
	+30 °C	10 hours	3 days
	Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity. When relative air humidity is ≥ 75% the waiting time is increased by at least 24 hours.		
Applied Product Ready for Use	Temperature	Foot traffic	Light traffic
	+10 °C	~ 48 hours	~ 5 days
	+20 °C	~ 20 hours	~ 3 days
	+30 °C	~ 10 hours	~ 2 days
			Full cure
			~ 10 days
			~ 7 days
			~ 5 days

PRODUCT INFORMATION

Packaging	Please refer to the individual Product Data Sheets
Shelf Life	Please refer to the individual Product Data Sheets
Storage Conditions	Please refer to the individual Product Data Sheets

MAINTENANCE

CLEANING

Please refer to Sikafloor®- Cleaning Regime

FURTHER DOCUMENTS

Please refer to :

- Sika® Information Manual Mixing & Applications of Flooring Systems
- Sika® Information Manual Evaluation and Preparation of Surfaces for Flooring Systems

LIMITATIONS

- Do not apply on substrates with rising moisture.
- Freshly applied Sikafloor® MultiDur WT-10 should be protected from damp, condensation and water for at

least 24 hours.

- Always ensure adequate fresh air ventilation when using Sikafloor® MultiDur WT-10 in confined spaces to avoid curing problems.
- The “gloss” of the finish can vary with temperature, humidity and the absorbency of the substrate.
- With light colour shades (e.g. yellow or orange) it may be necessary to apply several coats of Sikafloor®-2540 W to achieve full opacity (hiding power).
- Under direct sun radiation there may be some discoloration and colour deviation, this has no influence on the function and performance of the coating.
- The incorrect assessment and treatment of cracks may lead to a reduced service life and reflective cracking.
- For exact colour matching, ensure the Sikafloor®-2540 W in each area is applied from the same control batch numbers.
- Under certain conditions, underfloor heating or high ambient temperatures combined with high point

loading, may lead to imprints in the resin.

- If heating is required do not use gas, oil, paraffin or other fossil fuel heaters, these produce large quantities of both CO₂ and H₂O water vapour, which may adversely affect the finish. For heating use only electric powered warm air blower systems.

VALUE BASE

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA LIMITED

Watchmead
Welwyn Garden City
Hertfordshire, AL7 1BQ
Tel: 01707 394444
Web: www.sika.co.uk
Twitter: @SikaLimited



System Data Sheet
Sikafloor® MultiDur WT-10
February 2020, Version 01.02
020811900000000051

SikafloorMultiDurWT-10-en-GB-(02-2020)-1-2.pdf