

## PRODUCT DATA SHEET

## Sikaflex®-508

Low emission multipurpose STP sealant

## TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)

Chemical base		Silane Terminated Polymer
Colour (CQP001-1)	Black <sup>A</sup>	Black <sup>A</sup>
Cure mechanism		Moisture-curing
Density (uncured)		1.4 kg/l
Non-sag properties		Good
Application temperature	ambient	5 – 40 °C
Skin time (CQP019-1)		55 minutes <sup>B</sup>
Curing speed (CQP049-1)		(see diagram)
Shrinkage (CQP014-1)		1 %
Shore A hardness (CQP023-1 / ISO 48-4)		30
Tensile strength (CQP036-1 / ISO 527)		1.5 MPa
Elongation at break (CQP036-1 / ISO 527)		250 %
Tear propagation resistance (CQP045-1 / ISO 34)		4 N/mm
Service temperature (CQP513-1)		- 50 – 80 °C
Shelf life	Drum Unipack Cartridge	9 months <sup>C</sup> 15 months <sup>C</sup> 15 months <sup>C</sup>

CQP = Corporate Quality Procedure

A) Other colors available on request

B) 23°C / 50% r.h.

C) Storage below 25°C

## DESCRIPTION

Sikaflex®-508 is a low emission one-component isocyanate free sealant based on the Sika Silane Terminated Polymer (STP) technology which cures on exposure to atmospheric humidity.

Sikaflex®-508 meets the most severe environment, health and safety standards and sets a new benchmark in this technology.

## PRODUCT BENEFITS

- Very low emission
- Compatible with foamed polysterene (XPS)
- Bonds well to a wide variety of substrates without the need for special pre-treatments
- Easy to process
- Low odour
- Isocyanate, phtalate, plasticizer, solvent and PVC free

## AREAS OF APPLICATION

Sikaflex®-508 is a low modulus multipurpose sealant for internal and external applications. It adheres well to a wide variety of substrates and is especially compatible with foamed polystyrene foams (XPS).

Seek manufacturer's advice and perform tests on original substrates before using Sikaflex®-508 on materials prone to stress cracking.

This product is suitable for experienced professional users only. Tests with actual substrates and conditions have to be performed ensuring adhesion and material compatibility.

## PRODUCT DATA SHEET

Sikaflex®-508

Version 03.01 (04 - 2024), en\_GB

012201205080001000

## CURE MECHANISM

Sikaflex®-508 cures by reaction with atmospheric moisture. At low temperatures the water content of the air is generally lower and the curing reaction proceeds somewhat slower (see diagram 1).




Diagram 1: Curing speed Sikaflex®-508

## CHEMICAL RESISTANCE

Sikaflex®-508 is generally resistant to fresh water, seawater, diluted acids and diluted caustic solutions; temporarily resistant to fuels, mineral oils, vegetable and animal fats and oils; not resistant to organic acids, glycolic alcohol, concentrated mineral acids and caustic solutions or solvents.

The above information is offered for general guidance only. Advice on specific applications will be given on request.

## METHOD OF APPLICATION

### Surface Preparation

Surfaces must be clean, dry and free from grease, oil, dust and contaminants.

Surface treatment depends on the specific nature of the substrates and is crucial for a long lasting bond. Suggestions for surface preparation may be found on the current edition of the appropriate Sika® Pre-Treatment Chart. Consider that these suggestions are based on experience and have in any case to be verified by tests on original substrates.

## Application

Place the unipack in the application gun and snip off the closure clip. Cut off the tip of the nozzle to suit desired joint and apply the sealant with a suitable caulking gun. Take care to avoid air entrapment in the joint.

Sikaflex®-508 is processed between 5 °C and 40 °C (change in reactivity needs to be considered). The optimum temperature for substrate and sealant is between 15 °C and 25 °C. For advice on selecting and setting up a suitable pump system, contact the System Engineering Department of Sika Industry.

## Tooling and finishing

Tooling and finishing must be carried out within the skin time of the sealant. It is recommended using Sika® Tooling Agent N. Other finishing agents must be tested for suitability and compatibility prior the use.

## Removal

Uncured Sikaflex®-508 can be removed from tools and equipment with Sika® Remover-208 or another suitable solvent. Once cured, the material can only be removed mechanically. Hands and exposed skin have to be washed immediately using Sika® Cleaner-350H or a suitable industrial hand cleaner and water. Do not use solvents on skin!

## Overpainting

Sikaflex®-508 can be overpainted within the skin formation time. 2 component epoxy paints are usually suitable. Other paints must be tested for compatibility by carrying out preliminary trials under manufacturing conditions. The elasticity of paints is usually lower than of elastomers what could lead to cracking of the paint film in the joint area.

## FURTHER INFORMATION

Copies of the following publications are available on request:

- Safety Data Sheets
- Sika® Pre-treatment Chart  
For Silane Terminated Polymers
- General Guidelines  
for Bonding and Sealing with 1-component Sikaflex®

## PACKAGING INFORMATION

Cartridge	300 ml
Unipack	600 ml
Drum	195 l

## BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## HEALTH AND SAFETY INFORMATION

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

## DISCLAIMER

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

## PRODUCT DATA SHEET

Sikaflex®-508  
Version 03.01 (04 - 2024), en\_GB  
012201205080001000

## SIKA LIMITED

Watchmead  
Welwyn Garden City  
Hertfordshire, AL7 1BQ  
Tel: 01707 394444  
Web: www.sika.co.uk  
Twitter: @SikaLimited

