

## PRODUCT DATA SHEET

# SikaShield® P65 T 3 mm

Plastomeric bituminous underlay membrane surfaced with talc and flexible at -20 °C

### PRODUCT DESCRIPTION

SikaShield® P65 T 3 mm is an APP modified bituminous underlay membrane with a thickness of 3 mm. It is reinforced with a non-woven polyester fabric dimensionally stabilised with glass fibre and is flexible at -20 °C. The top surface is coated with talc, which ensures the bond of the subsequent cap sheet. The underside of the product has a burn-off film for easy torch-application.

### USES

SikaShield® P65 T 3 mm is used as a base sheet in multi-layer systems

### CHARACTERISTICS / ADVANTAGES

- Easy to install by torching method
- Fully bonded

### APPROVALS / STANDARDS

- CE marking and declaration of performance based on EN 13707:2004+A2:2009 Flexible sheets for waterproofing — Reinforced bitumen sheets for roof waterproofing — Definitions and characteristics

### PRODUCT INFORMATION

<b>Chemical Base</b>	Composition Reinforcing material	APP modified bitumen non-woven polyester fabric dimensionally stabilised with glass fibre
<b>Packaging</b>	Roll width	1.0 m (EN 1848-1)
	Roll length	8.0 m
Refer to the current price list for available packaging variations.		
<b>Appearance / Colour</b>	Top surface	Talc
	Bottom Surface	Polyethylene film
<b>Shelf Life</b>	36 months from date of production	
<b>Storage Conditions</b>	The Product must be stored in original unopened and undamaged packaging in dry conditions and temperatures between +5 °C and +35 °C. Protect the Product from direct weather exposure and sunlight. Store in a vertical position.	
<b>Thickness</b>	3.0 mm ± 0.2 mm	(EN 1849-1)

## TECHNICAL INFORMATION

<b>Resistance to Impact</b>	≥ 1250 mm	(EN 12691)
<b>Joint Shear Resistance</b>	Longitudinal (MD)	750 N/50 mm ± 150 N/50 mm (EN 12317-1)
	Transversal (CMD)	600 N/50 mm ± 120 N/50 mm
<b>External Fire Performance</b>	Broof (t4) (as part of a system build up)	(EN 13501-5)
<b>Reaction to Fire</b>	Class E	(EN 13501-1)
<b>Water Tightness</b>	Method B, 24 hours at 60 kPa	Pass (EN 1928)
<b>Flexibility at low temperature</b>	≤ -20 °C	(EN 1109)
<b>Maximum tensile force</b>	Longitudinal (MD)	850 N/50 mm ± 170 N/50 mm (EN 12311-1)
	Transversal (CMD)	700 N/50 mm ± 140 N/50 mm
<b>Elongation at maximum tensile force</b>	Longitudinal (MD)	(50 ± 15) % (EN 12311-1)
	Transversal (CMD)	(50 ± 15) %

## APPLICATION INFORMATION

<b>Ambient Air Temperature</b>	Maximum	+40 °C
	Minimum	+5 °C
<b>Relative Air Humidity</b>	Maximum	80 %
<b>Substrate Temperature</b>	Maximum	+40 °C
	Minimum	+5 °C

## VALUE BASE

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## ECOLOGY, HEALTH AND SAFETY

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in the product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0,1 % (w/w).

## APPLICATION INSTRUCTIONS

Please refer to the SikaShield® Installation Guide

### SIKA LIMITED

Watchmead  
Welwyn Garden City  
Hertfordshire, AL7 1BQ  
Tel: 01707 394444  
Web: [www.sika.co.uk](http://www.sika.co.uk)  
Twitter: @SikaLimited



Product Data Sheet  
SikaShield® P65 T 3 mm  
February 2025, Version 01.01  
020920011990002227

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SikaShieldP65T3mm-en-GB-(02-2025)-1-1.pdf