

PRODUCT DATA SHEET

SikaForce®-424 L180

2-component gelling assembly adhesive with long open time

TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)

Properties	Component A SikaForce®-424 L180	Component B SikaForce®-010
Chemical base	Polyols	Isocyanate derivatives
Colour (CQP001-1)	Beige	Brown
	mixed Beige	
Cure mechanism	Polyaddition	
Density (uncured)	1.59 g/cm ³	1.23 g/cm ³
	mixed (calculated) 1.53 g/cm ³	
Solid content	100 %	100 %
Mixing ratio	by volume 100 : 22	
	by weight 100 : 17	
Viscosity (CQP029-4)	Rheometer, PP25, shear rate 10 s ⁻¹ , d=1 mm 25 000 mPa·s ^A	300 mPa·s ^A
	mixed Gel ^A	
Application temperature	15 – 30 °C	
Pot-life (CQP536-3)	at 23 °C	180 minutes
Open time (CQP526-3)	at 23 °C at 45 °C	200 minutes 65 minutes
Press time (CQP590-4)	time to reach 1 MPa at 23 °C time to reach 1 MPa at 45 °C	350 minutes 110 minutes
Shore D hardness (CQP023-1 / ISO 868)	50 ^B	
Tensile strength (CQP543-1 / ISO 527)	6 MPa ^B	
Elongation at break (CQP543-1 / ISO 527)	35 % ^B	
Tensile lap-shear strength (CQP546-1 / ISO 4587)	6 MPa ^B	
Shelf life	12 months	9 months

CQP = Corporate Quality Procedure

A) 23 °C

B) 1 d 23 °C / 3 d 60 °C / 2 d 23 °C

DESCRIPTION

SikaForce®-424 L180 is a gelling, long open time 2-component polyurethane adhesive for assembling sandwich panels and similar constructions of various materials.

PRODUCT BENEFITS

- Chemical gelling
- Non sagging
- Solvent free
- Good gap filling property

AREAS OF APPLICATION

SikaForce®-424 L180 is used primarily for assembling of profiles and sandwich constructions of e.g. glass fibre reinforced plastic, wood, metal, ceramic materials and pre-treated plastic materials.

This product is suitable for experienced professional users only. Tests with actual substrates and conditions have to be performed, ensuring adhesion and material compatibility.

CURE MECHANISM

The curing of SikaForce®-424 L180 takes place by a chemical reaction of the two components. Higher temperatures speed up the curing process and lower slow it down.

CHEMICAL RESISTANCE

In case of chemical or thermal exposure, conduct project related testing.

METHOD OF APPLICATION

Product preparation

Component A must be stirred thoroughly before use.

Surface Preparation

Surfaces must be clean, dry and free from grease, oil, dust and contaminants. After the cleaning process, a physical or chemical pretreatment might be required, depending on surface and type of material. The type of pretreatment must be determined by tests.

Application

Volume and positioning of the adhesive must be defined in a way that the intended gap is sufficiently filled after joining the parts. The specific applied quantity and position must be determined by tests.

The procedure for manual application is as follows: Ensure that the A-component is stirred thoroughly to avoid any sediment or separation, taking care not to stir too vigorously as this may introduce air into the product. Add the B-component in the specified ratio and stir thoroughly, ensuring a homogeneous mixture is achieved.

Apply before reaching half of the pot-life and join parts together within the open time. Consider that, if mixed in larger amounts, the exothermic reaction can reduce the pot-life and open time significantly.

For automated applications, contact the System Engineering Department of Sika Industry.

Pressing

An adequate bonding pressure is necessary to obtain a voidless contact between the substrates and the adhesive. The specific pressure is, however, dependent on the core material and must be determined by tests. The pressure must always be below the maximum compressive strength of the core. After starting the press process, do not release the pressure until the press time has elapsed.

Removal

Uncured SikaForce®-424 L180 may be removed from tools and equipment with SikaForce®-096 Cleaner. Once cured, the material can only be removed mechanically.

Hands and exposed skin have to be washed immediately using hand wipes such as Sika® Cleaner-350H or a suitable industrial hand cleaner and water.

Do not use solvents on skin.

STORAGE CONDITIONS

SikaForce®-424 L180 has to be kept between 10 °C and 30 °C in a dry place. Do not expose it to direct sunlight or frost. After opening of the packaging, the content has to be protected against humidity.

The lowest allowed temperature during transportation is -20 °C for max. 7 days.

FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are available on request:

- Safety Data Sheets

BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

HEALTH AND SAFETY INFORMATION

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

DISCLAIMER

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

PRODUCT DATA SHEET

SikaForce®-424 L180
Version 03.01 (04 - 2023), en_GB
012104544240001000

SIKA LIMITED

Watchmead
Welwyn Garden City
Hertfordshire, AL7 1BQ
Tel: 01707 394444
Web: www.sika.co.uk
Twitter: @SikaLimited

