

## SYSTEM DATA SHEET

# Sikafloor® MultiDur ES-39 ECF

SMOOTH, TOUGH-ELASTIC, UNICOLOUR CONDUCTIVE EPOXY FLOOR COVERING WITH HIGH CHEMICAL RESISTANCE

### PRODUCT DESCRIPTION

Sikafloor® MultiDur ES-39 ECF is a two part, electrostatic conductive self-smoothing, tough-elastic, coloured epoxy flooring system with high chemical resistance. "Total solid epoxy composition acc. to the test method Deutsche Bauchemie e.V. (German Association for construction chemicals)".

### USES

Sikafloor® MultiDur ES-39 ECF may only be used by experienced professionals.

It is used as:

- Crack-bridging and chemically resistant coating for concrete and screed surfaces in bund areas for the protection against water contaminating liquids (according resistance table)
- Electrostatic conductive wearing course for areas subject to chemical exposure which are likely to crack

### CHARACTERISTICS / ADVANTAGES

- High chemical resistance
- Crack-bridging
- Liquid proof
- Electrostatic conductive

### ENVIRONMENTAL INFORMATION

Conforms to AgBB (2012) for use in indoor environment. Test report No. 392-2015-00129301\_02. Eurofins Product Testing.


### APPROVALS / STANDARDS

- Self-smoothing, coloured epoxy resin coating according to EN 1504-2: 2004 and EN 13813, DoP 02 08 01 02 020 000008 2017, certified by Factory Production Control Body No. 0921, certificate 2017, and provided with the CE-mark
- Particle emission certificate Sikafloor®-390 ECF CSM Statement of Qualification - ISO 14644-1, class 1 and GMP class A, Report No. SI 1204-593
- Outgassing emission certificate Sikafloor®-390 ECF CSM: CSM Statement of Qualification - ISO 14644-8, class -9.6 - Report No. SI 1204-593
- Biological Resistance in accordance with ISO 846, CSM Report No. SI 1204-593
- Fire classification in accordance with DIN 4102 part 1 and part 14, Report-No. 130682-2, class B1, Institute Hoch, Germany, June 2013
- Spark resistance in accordance with UFGS-09 97 23 of coating systems, Test report P 8625-E, Kiwa Polymer Institut, March 2014
- National technical approval for water polluton control acc. DIBt (German Institute for Structural Engineering) Registration Number: Z-59.12-393, February 2014
- Varnishability test according to VW-standard PV 3.10.7 (paint wetting impairment substances (PWIS)) like silicones, HQM GmbH, Test Report 14-04-142018712-3, 05.2014

# SYSTEM INFORMATION

## System Structure

### Sikafloor® MultiDur ES-39 ECF:



1. Primer + Earthing connection	Sikafloor®-150/-151 + Sika® Earthing Kit
2. Conductive primer	Sikafloor®-220 W Conductive
3. Final conductive coating	Sikafloor®-390 ECF

The system configuration as described must be fully complied with and may not be changed.

<b>Composition</b>	Epoxy
<b>Appearance</b>	Self-smoothing system – gloss finish
<b>Colour</b>	Almost unlimited choice of colour shades. Due to the nature of carbon fibres providing the conductivity, it is not possible to achieve exact colour matching. With very bright colours (such as yellow and orange), this effect is increased. Under direct sunlight there may be some variations and colour variation, this has no influence on the function and performance of the coating.
<b>Nominal Thickness</b>	~ 1.5 mm
<b>Volatile organic compound (VOC) content</b>	Very low content of volatile organic compounds. Sikafloor®-390 ECF, the finishing layer of the Sikafloor® MultiDur ES-39 ECF System, has been awarded the Fraunhofer IPA CSM Certificate of Qualification with the report number SI 1204-593. The Outgassing test was performed in accordance with CSM procedures. TVOC: ISO-AMC Class -9.6 (see ISO 14644-8). The Sikafloor® MultiDur ES-39 ECF System fulfils the stringent demands for indoor air quality and low VOC emitting products AgBB see the test report no. 392-2014-00129301_02.

## TECHNICAL INFORMATION

<b>Shore D Hardness</b>	~ 60	(14 days / +23 °C)	(DIN 53 505)
<b>Abrasion Resistance</b>	~ 75 mg	(CS 10/1000/1000) (8 days / +23 °C)	(DIN 53109 Taber Abraser Test)
<b>Tensile Strength</b>	~ 10 N/mm <sup>2</sup>	(8 days / +23 °C)	(DIN 53455)
<b>Elongation at Break</b>	~ 20%	(18 days / +23 °C)	(53455)
<b>Crack Bridging Ability</b>	Static crack bridging of cracks ~ 0.25 mm		
<b>Chemical Resistance</b>	Resistant to many chemicals. Contact Sika technical service for specific information		

**Thermal Resistance**

Exposure*	Dry heat
Permanent	+50 °C
Short-term max. 7 d	+80 °C

Short-term moist/wet heat\* up to +80 °C where exposure is only occasional (i.e. during steam cleaning etc.)

\*No simultaneous chemical and mechanical exposure.

**USGBC LEED Rating**

Conforms to the requirements of LEED EQ Credit 4.2: Low-Emitting Materials: Paints & Coatings SCAQMD Method 304-91 VOC Content <100 g/l

**Electrostatic Behaviour**

Resistance to ground <sup>1</sup>	$R_g < 10^9 \Omega$	(IEC 61340-4-1)
Typical average resistance to ground <sup>2</sup>	$R_g < 10^6 \Omega$	(DIN EN 1081)

<sup>1</sup> In accordance with IEC 61340-5-1 and ANSI/ESD S20.20.

<sup>2</sup> Readings may vary, depending on ambient conditions (i.e. temperature, humidity) and measurement equipment.

**APPLICATION INFORMATION****Consumption**

Coating	Product	Consumption
Primer	Sikafloor®-150/-151	1-2 x ~ 0.3 - 0.5 kg/m <sup>2</sup>
Levelling (if required)	Sikafloor®-150/-151 levelling mortar	Refer to PDS of Sikafloor®-150/-151
Earthing connection	Sika® Earthing Kit	1 earthing point per approx. 200 -300 m <sup>2</sup> , min. 2 per room.
Conductive Primer	Sikafloor®-220 W Conductive	1 x 0.08 - 0.10 kg/m <sup>2</sup>
Final conductive coating	Sikafloor®-390 ECF	2.5 kg/m <sup>2</sup>

These figures are theoretical and do not allow for any additional material due to surface porosity, surface profile, variations in level or wastage etc.

**Ambient Air Temperature**

+10 °C min. / +30 °C max.

**Relative Air Humidity**

80 % r.h. max.

**Dew Point**

Beware of condensation!

The substrate and uncured floor must be at least 3 °C above dew point to reduce the risk of condensation or blooming on the floor finish.

**Substrate Temperature**

+10 °C min. / +30 °C max.

**Substrate Moisture Content**

<4 % pbw moisture content.

Test method: Sika Tramex Meter, CM-measurement or Oven-Dry-Method. No rising moisture according to ASTM (Polyethylene-sheet).

**Waiting Time / Overcoating**

Before applying Sikafloor®-220 W Conductive on Sikafloor®-150/151 allow:

Substrate temperature	Minimum	Maximum
+10°C	24 hours	4 days
+20°C	12 hours	2 days
+30°C	8 hours	1 days

Before applying Sikafloor®-390 ECF on Sikafloor®-220 W Conductive allow:

Substrate temperature	Minimum	Maximum
+10°C	26 hours	7 days
+20°C	17 hours	5 days
+30°C	12 hours	4 days

Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity.

**Applied Product Ready for Use**

Temperature	Foot traffic	Light traffic	Full cure
+10°C	~ 48 hours	~ 6 days	~ 14 days
+20°C	~ 30 hours	~ 4 days	~ 10 days
+30°C	~ 20 hours	~ 3 days	~ 7 days

## PRODUCT INFORMATION

<b>Packaging</b>	Please refer to individual Product Data Sheet.
<b>Shelf Life</b>	Please refer to individual Product Data Sheet.
<b>Storage Conditions</b>	Please refer to individual Product Data Sheet.

## MAINTENANCE

To maintain the appearance of the floor after application, Sikafloor®-390 ECF must have all spillages removed immediately and must be regularly cleaned using rotary brush, mechanical scrubbers, scrubber dryer, high pressure washer, wash and vacuum techniques etc. using suitable detergents.

### CLEANING

Please refer to the Sikafloor® Cleaning Regime.

## FURTHER DOCUMENTS

Please refer to:

- Sika® Information Manual Mixing and Application of Flooring Systems
- Sika® Information Manual Surface Evaluation & Preparation

## LIMITATIONS

- This system may only be used by experienced professionals.
- Due to the nature of carbon fibres providing the conductivity, surface irregularities might be possible. This has no influence on the function and performance of the coating.
- Do not apply the Sikafloor® MultiDur ES-39 ECF System on substrates in which significant vapour pressure may occur.
- Do not blind the primer.
- The freshly applied final conductive coating of the Sikafloor® MultiDur ES-39 ECF system must be protected from damp, condensation and water for at least 24 hours.
- Only start application of Sikafloor® conductive primer after the priming coat has dried tack-free all over. Otherwise there is a risk of wrinkling or impairing of the conductive properties.
- Maximum layer thickness of final conductive coating: ~ 1.5 mm. Excessive thickness (more than 2.5 kg/m<sup>2</sup>) causes reduced conductivity.
- Under certain conditions, underfloor heating com-

lined with high point loading, may lead to imprints in the resin.

- If heating is required do not use gas, oil, paraffin or other fossil fuel heaters, these produce large quantities of both CO<sub>2</sub> and H<sub>2</sub>O water vapour, which may adversely affect the finish. For heating use only electric powered warm air blower systems.
- The incorrect assessment and treatment of cracks may lead to a reduced service life and reflective cracking - reducing or breaking conductivity.
- For exact colour matching, ensure the final conductive coating of the Sikafloor® MultiDur ES-39 ECF system in each area is applied from the same control batch numbers.
- ESD clothing, ambient conditions, measurement equipment, cleanliness of the floor and the test person have a substantial influence on the measurement results.

All measurement values for the Sikafloor® MultiDur ES-39 ECF system stated in the system data sheet (apart from the ones referring to proof statements) were measured under the following conditions:

<u>Ambient conditions:</u>	<u>+23 °C/50%</u>
<u>Measurement device for the Resistance to Ground:</u>	<u>Metriso 2000 (Warmbier) or comparable</u>
<u>Surface resistance probe:</u>	<u>Carbon Rubber electrode. Weight: 2.50 kg / Tripod electrode acc. Din EN 1081</u>
<u>Rubber pad hardness:</u>	<u>Shore A 60 (± 10)</u>

The number of conductivity measurements is strongly recommended to be as shown in the table below:

<u>Ready applied area</u>	<u>Number of measurements</u>
<u>&lt; 10 m<sup>2</sup></u>	<u>6 measurements</u>
<u>&lt; 100 m<sup>2</sup></u>	<u>10-20 measurements</u>
<u>&lt; 1000 m<sup>2</sup></u>	<u>50 measurements</u>
<u>&lt; 5000 m<sup>2</sup></u>	<u>100 measurements</u>

In case of values lower/higher as required, additional measurements has to be carried out, approx. 30 cm around the point with insufficient readings. If the newly measured values are in accordance with the requirements, the total area is acceptable.

Installation of earthing points: Please refer to the Information Manual: "MIXING & APPLICATION OF

## FLOORING SYSTEMS”.

Numbers of earth connections: Per room at least 2 earthing points. The optimum number of earth connections depends on the local conditions and should be specified using available drawings.

## VALUE BASE

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika’s current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika’s recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product’s suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### SIKA LIMITED

Watchmead  
Welwyn Garden City  
Hertfordshire, AL7 1BQ  
Tel: 01707 394444  
Web: [www.sika.co.uk](http://www.sika.co.uk)  
Twitter: @SikaLimited



System Data Sheet  
Sikafloor® MultiDur ES-39 ECF  
February 2020, Version 01.03  
020811900000000016

SikafloorMultiDurES-39ECF-en-GB-(02-2020)-1-3.pdf