

Sika® peelstop

Fastening Profile for Sika-Trocal® adhered systems

Product Description	Folded hot dipped galvanized steel profile.
Uses	Peelstop is used in Sika-Trocal adhered systems – SGK membrane.
Characteristics / Advantages	<ul style="list-style-type: none"> ■ Ease of application ■ Recyclable
Tests	
Approval / Standards	■ Quality Management system in accordance with EN ISO 9001/14001.
Product Data	
Form	
Appearance	Textured surface
Delivery Packaging	Maximum 100 lengths per pack, 10 pieces wide, 10 pieces high in alternating rows
Storage	
Storage conditions	Peelstop should be stored in dry conditions,
Shelf-life	Peelstop should be stored in dry conditions.
Technical Data	
Material basis	Hot dipped galvanized steel DX51D+275 N-A-C (0.8 mm +/- 0.07mm) (BS EN 10327:2004 and BS EN 10143:2006)
Width	30mm
Thickness	2mm
Height	7.0mm
Mass per unit area	0.74kg/m
Corrosion resistance	60+ year for C1 category and 30+ years for C2 category according to BS EN ISO 12944-2:1998



Sika Limited
 Watchmead
 Welwyn Garden City
 Hertfordshire
 AL7 1BQ
 United Kingdom
 Phone +44 1707 394444
 Telefax +44 1707 329129
www.sika.co.uk
 email: sika-trocal@uk.sika.com



Certificate No. EMS 4308



Certificate No. FM 12504



Types	Type	Length	Hole Diameter	Hole Spacing
	Peelstop	2000mm (1/-3mm)	Alternating 6.5 and 15mm	Like holes 50mm unlike 25mm
Marked with branding every 250mm (letters 4mm high and 22mm long)				

Sika Limited
 Watchmead
 Welwyn Garden City
 Hertfordshire
 AL7 1BQ
 United Kingdom
 Phone +44 1707 394444
 Telefax +44 1707 329129
www.sika.co.uk
 email: sika-trocal@uk.sika.com



Certificate No. EMS 4308



Certificate No. FM 12504

Application**Conditions / Limits**

Temperature

The use of Peelstop is limited to geographical locations with average monthly minimum temperatures of -50 °C. Permanent ambient temperature during use is limited to +50 °C.

Notes on installation limits

Installation

Installation works to be carried out only by Sika Licensed Contractors.

Temperature limits for the installation of the Sarnabar:

Substrate temperature: -30 °C min. / +60 °C max.

Ambient temperature: -20 °C min. / +60 °C max.

Special measures may be compulsory for installation below +5 °C ambient temperature. All works in accordance with regulatory requirements.

Value Base

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

Local Restrictions

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

Sika Limited
Watchmead
Welwyn Garden City
Hertfordshire
AL7 1BQ
United Kingdom
Phone +44 1707 394444
Telefax +44 1707 329129
www.sika.co.uk
email: sika-trocal@uk.sika.com



Certificate No. EMS 4308



Certificate No. FM 12504

Roofing

Ecology, Health and Safety Information	The product does not fall within the EC-regulation of hazardous goods. As a result, a material safety data sheet following EC-Guideline 91/155 EWG is not needed to bring the product to the market, transport or use it. The product does not damage the environment when used as specified.
Protective Measures	Fresh air ventilation must be ensured, when working (welding) in closed rooms. Local safety regulations must be observed.
Transportation Class	The product is not classified as hazardous good for transport.
Value Base	All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.
Disclaimer	The information, and, in particular, the recommendations relating to the application and end- use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



Sika Limited
Watchmead
Welwyn Garden City
Hertfordshire
AL7 1BQ
United Kingdom
Phone +44 1707 394444
Telefax +44 1707 329129
www.sika.co.uk
email: sika-trocal@uk.sika.com



Certificate No. EMS 4308



Certificate No. FM 12504