

## SYSTEM DATA SHEET

# Sikafloor® MultiDur ET-14 ECC

### TEXTURED UNICOLOUR EPOXY FLOOR COVERING OVER EPOXY HYBRID SCREED

#### PRODUCT DESCRIPTION

Sikafloor® MultiDur ET-14 ECC is a coloured rigid epoxy floor covering with textured properties based on epoxy resins for industrial floors on damp substrates.

#### USES

Sikafloor® MultiDur ET-14 ECC may only be used by experienced professionals.

- for concrete and cement screeds with normal up to medium heavy wear e.g. storage and assembly halls, maintenance workshops, garages and loading ramps.
- for multi-storey and underground car parks, maintenance hangars and for wet process areas, e.g. beverage and food industry.
- for areas where slip resistance and easy cleanability is required

#### CHARACTERISTICS / ADVANTAGES

- Good mechanical resistance
- Good chemical resistance
- Medium thermal shock resistance
- Fast and easy application
- Thermal expansion properties similar to concrete
- Excellent bond to green or hardened concrete whether damp or dry
- Excellent early and final mechanical strengths
- Excellent resistance to water and oils
- For internal use
- Contains no solvents
- Will not corrode reinforcement steel


#### APPROVALS / STANDARDS

- Cleanability "Excellent" (VDMA "Riboflavin test for low germ or sterile process technologies" tested).
- Slip resistance class R9 in accordance with DIN 51130 and BGR 181.
- Conforms to the requirements of EN 13813 and EN 1504-2

## SYSTEM INFORMATION

### System Structure

Sikafloor® MultiDur ET-14 ECC



Layer	Product
1. Primer	Sikafloor®-155 WN
2. Levelling screed	Sikafloor®-81 EpoCem®
3. Top coat	1-2 x Sikafloor®-264 Thixo

<b>Composition</b>	Epoxy
<b>Appearance</b>	Textured, gloss finish
<b>Colour</b>	Almost unlimited choice of colour shades.
<b>Nominal Thickness</b>	~ 2-4mm

## TECHNICAL INFORMATION

<b>Shore D Hardness</b>	~76 (7 days / +23 °C)	(DIN 53 505)								
<b>Tensile Adhesion Strength</b>	> 1.5 N/mm <sup>2</sup> (failure in concrete)	(ISO 4624)								
<b>Chemical Resistance</b>	Please refer to the chemical resistance chart of Sikafloor®- 264 Thixo									
<b>Thermal Resistance</b>	<table border="1"> <thead> <tr> <th>Exposure*</th> <th>Dry heat</th> </tr> </thead> <tbody> <tr> <td>Permanent</td> <td>+50 °C</td> </tr> <tr> <td>Short-term max. 7 d</td> <td>+80 °C</td> </tr> <tr> <td>Short-term max. 12 h</td> <td>+100 °C</td> </tr> </tbody> </table> <p>Short-term moist/wet heat* up to +80°C where exposure is only occasional (steam cleaning etc.) *No simultaneous chemical and mechanical exposure.</p>	Exposure*	Dry heat	Permanent	+50 °C	Short-term max. 7 d	+80 °C	Short-term max. 12 h	+100 °C	
Exposure*	Dry heat									
Permanent	+50 °C									
Short-term max. 7 d	+80 °C									
Short-term max. 12 h	+100 °C									
<b>Skid / Slip Resistance</b>	R9	(DIN 51130)								

## APPLICATION INFORMATION

<b>Consumption</b>	Sikafloor® MultiDur ET-14 ECC		
	<b>Coating System</b>	<b>Product</b>	<b>Consumption</b>
	1. Primer	1 x Sikafloor®-155 WN	~ 0.3-0.5 kg/m <sup>2</sup> thinned with 10 % water
	2. Levelling screed	1 x Sikafloor®-81 EpoCem®	~2.25 kg/m <sup>2</sup> /mm
	3. Top coat	1-2 x Sikafloor®-264 Thixo	~0.5-0.8 kg/m <sup>2</sup> per layer
<b>Product Temperature</b>	Please refer to the individual Product Data Sheet		
<b>Ambient Air Temperature</b>	+10 °C min. / +30 °C max.		

<b>Relative Air Humidity</b>	80 % r.h. max.																						
<b>Dew Point</b>	Beware of condensation! The substrate and uncured floor temperature must be at least 3 °C above the dew point to reduce the risk of condensation or blooming on the floor finish.																						
<b>Substrate Temperature</b>	+10 °C min. / +30 °C max.																						
<b>Substrate Moisture Content</b>	When performing application work with Sikafloor® MultiDur ET-14 ECC, the substrate moisture content must not exceed 4 % pbw measured by Tramex. Test method: Sika®-Tramex meter, CM - measurement or Oven-dry-method. No rising moisture according to ASTM (Polyethylene-sheet).																						
<b>Waiting Time / Overcoating</b>	Before applying Sikafloor®-81 EpoCem® on Sikafloor®-155 WN allow: <table border="1"> <thead> <tr> <th><b>Substrate temperature</b></th> <th><b>Minimum</b></th> <th><b>Maximum</b></th> </tr> </thead> <tbody> <tr> <td>+10 °C</td> <td>12 hours</td> <td>72 hours</td> </tr> <tr> <td>+20 °C</td> <td>6 hours</td> <td>48 hours</td> </tr> <tr> <td>+30 °C</td> <td>4 hours</td> <td>24 hours</td> </tr> </tbody> </table> Sikafloor®-81 EpoCem® can be overcoated with vapour tight coatings when the surface humidity falls below 4%! Not earlier than : <table border="1"> <thead> <tr> <th><b>Substrate Temperature</b></th> <th><b>Waiting Time</b></th> </tr> </thead> <tbody> <tr> <td>+10°C</td> <td>2 days</td> </tr> <tr> <td>+20°C</td> <td>1 day</td> </tr> <tr> <td>+30°C</td> <td>1 day</td> </tr> </tbody> </table>			<b>Substrate temperature</b>	<b>Minimum</b>	<b>Maximum</b>	+10 °C	12 hours	72 hours	+20 °C	6 hours	48 hours	+30 °C	4 hours	24 hours	<b>Substrate Temperature</b>	<b>Waiting Time</b>	+10°C	2 days	+20°C	1 day	+30°C	1 day
<b>Substrate temperature</b>	<b>Minimum</b>	<b>Maximum</b>																					
+10 °C	12 hours	72 hours																					
+20 °C	6 hours	48 hours																					
+30 °C	4 hours	24 hours																					
<b>Substrate Temperature</b>	<b>Waiting Time</b>																						
+10°C	2 days																						
+20°C	1 day																						
+30°C	1 day																						
<b>Applied Product Ready for Use</b>	<table border="1"> <thead> <tr> <th><b>Temperature</b></th> <th><b>Foot traffic</b></th> <th><b>Light traffic</b></th> <th><b>Full cure</b></th> </tr> </thead> <tbody> <tr> <td>+10 °C</td> <td>~ 72 hours</td> <td>~ 6 days</td> <td>~ 10 days</td> </tr> <tr> <td>+20 °C</td> <td>~ 24 hours</td> <td>~ 4 days</td> <td>~ 7 days</td> </tr> <tr> <td>+30 °C</td> <td>~ 18 hours</td> <td>~ 2 days</td> <td>~ 5 days</td> </tr> </tbody> </table>	<b>Temperature</b>	<b>Foot traffic</b>	<b>Light traffic</b>	<b>Full cure</b>	+10 °C	~ 72 hours	~ 6 days	~ 10 days	+20 °C	~ 24 hours	~ 4 days	~ 7 days	+30 °C	~ 18 hours	~ 2 days	~ 5 days						
<b>Temperature</b>	<b>Foot traffic</b>	<b>Light traffic</b>	<b>Full cure</b>																				
+10 °C	~ 72 hours	~ 6 days	~ 10 days																				
+20 °C	~ 24 hours	~ 4 days	~ 7 days																				
+30 °C	~ 18 hours	~ 2 days	~ 5 days																				

## PRODUCT INFORMATION

<b>Packaging</b>	Please refer to the individual Product Data Sheet
<b>Shelf Life</b>	Please refer to the individual Product Data Sheet
<b>Storage Conditions</b>	Please refer to the individual Product Data Sheet

## MAINTENANCE

### CLEANING

Refer to Sikafloor®-Cleaning Regime

### FURTHER DOCUMENTS

- Sika® Information Manual Mixing & Applications of Flooring systems
- Sika® Information Manual Evaluation and Preparation of Surfaces for Flooring systems

### LIMITATIONS

- Always ensure good ventilation when using Sikafloor® MultiDur ET-14 ECC in a confined space to remove excess moisture.
- Freshly applied Sikafloor® MultiDur ET-14 ECC must be protected from damp, condensation and water for at least 24 hours.
- Prevent premature drying by protecting from strong

wind and do not expose to direct sun light while fresh.

- Applications under extreme conditions (high temperature and low humidity) which can cause fast drying of the products must be avoided as the product does not allow the use of curing compounds.
- Static cracks: Prefill and level with Sikadur® or Sikafloor® epoxy resin
- For exact colour matching, ensure the Sikafloor®-264 Thixo in each area is applied from the same control batch numbers.
- Under certain conditions, underfloor heating or high ambient temperatures combined with high point loading, may lead to imprints in the resin.
- If heating is required do not use gas, oil, paraffin or other fossil fuel heaters, these produce large quantities of both CO<sub>2</sub> and H<sub>2</sub>O water vapour, which may adversely affect the finish. For heating use only electric powered warm air blower systems.

## VALUE BASE

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### SIKA LIMITED

Watchmead  
Welwyn Garden City  
Hertfordshire, AL7 1BQ  
Tel: 01707 394444  
Web: [www.sika.co.uk](http://www.sika.co.uk)  
Twitter: @SikaLimited

### SIKA IRELAND LIMITED

Ballymun Industrial Estate  
Ballymun  
Dublin 11, Ireland  
Tel: +353 1 862 0709  
Web: [www.sika.ie](http://www.sika.ie)  
Twitter: @SikaIreland



System Data Sheet  
Sikafloor® MultiDur ET-14 ECC  
May 2017, Version 01.01  
020811900000000003

SikafloorMultiDurET-14ECC-en-GB-(05-2017)-1-1.pdf