

PRODUCT DATA SHEET

Sarnacol®-2142 V

VOC free adhesive for Sarnafil® felt backed roof waterproofing membranes

PRODUCT DESCRIPTION

Sarnacol®-2142 V is a VOC free, 1-part, polyurethane based moisture curing adhesive.

USES

Bonding Sarnafil® G Felt-type and Sikaplan® SGK type membranes to roof substrates.

Bonding substrates:

- Concrete, lightweight concrete, plaster
- Oriented fibre strand boards, plywood panels
- Fibre cement boards
- Slated/mineralized bitumen sheets; new and aged
- Mineral fibre boards: product specific approval with sufficient compressive strength and appropriate surface for bonding
- PUR/PIR insulation boards with lamination (glass or mineral fibre fleece)
- EPS insulation boards: Slap stock foaming cut, compressive strength ≥ 100 kPa
- Steel panels: product specific approval (e.g. Brucha Panels WP)

CHARACTERISTICS / ADVANTAGES

- VOC free
- Adheres to solid, rough, clean, dry or slightly moist surfaces
- Application by roller
- Good adhesion to different substrates

PRODUCT INFORMATION

Chemical Base	Polyurethane moisture curing	
Packaging	One way container:	10 kg
	Packing unit:	Euro pallet or single container
	Refer to current price list for packaging variations	
Shelf Life	12 months from date of production.	
Storage Conditions	The product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between + 5 °C and + 25 °C. Always refer to packaging.	
Density	~1,12 kg/l (+20 °C)	
Consistency	Liquid	

Volatile organic compound (VOC) content	VOC-CH	0,0 %
	VOC-EU	0,0 %

SYSTEM INFORMATION

Compatibility	Incompatible substrates:	
	▪ Single ply waterproofing membranes (thermoplastics/elastomers)	
	▪ Sheet metal	
	▪ Talcum coated bituminous sheets	

APPLICATION INFORMATION

Consumption	Consumption depends on the roughness and absorbency of the substrate. Recommended consumption of Sarnacol®-2142 V on different substrates (+20 °C / 50 % r.h.)		
	Substrate	g/m²	
	Mineral-fibre board: Rockwool Bondrock MV, Multifix	350–800	
	Bituminous sheet: New/Aged: Slated/mineral surface	250–400	
	PUR/PIR: Type Kingspan TR 27 with glass tissue facing	250–400	
	Timber: OSB3	250–400	
	EPS: Prefabricated roof insulation sheets: e.g. ISOBOUW	250–400	
	Sandwich panel	250–400	
	Concrete	250–400	
	These figures are theoretical and do not allow for any additional material due to surface porosity, surface profile, variations in level or wastage etc.		
	Ambient Air Temperature	+5 °C min	
	Substrate Temperature	+5 °C min	

VALUE BASE

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER DOCUMENTS

- Installation instructions: Sarnafil® G 410-EL Felt or Sarnafil® TG 76 Felt system fully bonded for exposed roofs

LIMITATIONS

- The use of some ancillary products such as adhesives, cleaners and solvents is limited to temperatures above + 5 °C. Observe temperature limitations in the appropriate Product Data Sheets
- Special measures may be compulsory for installation below + 5 °C ambient temperature due to safety requirements in accordance with national regulations

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

Regulation (EC) No 1907/2006 (REACH) - Mandatory training

As from 24 August 2023 adequate training is required before industrial or professional use of this product. For more information and a link to the training visit www.sika.com/pu-training.



APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

The substrate must offer sufficient strength and adhesion to resist the forces generated by wind suction.

SUBSTRATE PREPARATION

The substrate must be firm, clean, dry or slightly moist, free from oil, grease, dust, stripping agents, standing water, bitumen residue and loose friable particles.

APPLICATION

Reference must be made to further documentation where applicable, such as relevant method statement, application manual and installation or working instructions.

General information

Sarnacol®-2142 V must be stirred carefully before use. Keep adhesive container closed whenever adhesive is not being used to prevent surface skinning. To improve the workability of the adhesive at low temperatures, the closed container can be placed in warm water (max. +40 °C). Adhesive residue on Sarnafil® G Felt must be cleaned with Sarna Cleaner. Adhesive residue on Sarnafil® T Felt, must be cleaned with Sarnafil® T Clean.

General bonding procedure - Wet bonding

The adhesive is spread evenly onto the substrate by using a synthetic application roller directly from the container and ensuring there are no lumps in the applied layers.

Bonding to PVC Membranes

Apply adhesive onto the substrate. Do not apply the adhesive to an area greater than can be covered within 15 minutes. Do not pour out the adhesive and roll in a second stage. After a few minutes (before the adhesive forms a skin), place the felt-backed membrane in position onto the wet substrate adhesive. Press down firmly on the membrane using a suitable pressure roller such as a water-filled, or heavy steel roller 40–50 kg.

Bonding to EPS insulation board

Apply adhesive onto the substrate in a thin layer (~250 g/m²).

Bonding to very absorbent substrates (Mineral fibre boards)

Apply 2 coats of adhesive. The first coat ~800 g/m². Allow the adhesive to dry completely. Apply a second coat ~400 g/m² max.

CLEANING OF TOOLS

Clean all tools and application equipment with Sarna Cleaner or Sarnafil® T immediately after use. Hardened material can only be mechanically removed.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA LIMITED

Watchmead
Welwyn Garden City
Hertfordshire, AL7 1BQ
Tel: 01707 394444
Web: www.sika.co.uk
Twitter: @SikaLimited



Product Data Sheet

Sarnacol®-2142 V
July 2023, Version 02.02
020945072000000045

Sarnacol-2142V-en-GB-(07-2023)-2-2.pdf